

INDEX

ALLOY LISTING [24](#)
ALLOY SPECIFICATIONS [25](#)
ALUMINUM BRASS [11](#)
ALUMINUM BRONZE [16](#), [17](#), [18](#)

BERYLLIUM ALLOY [4](#)
BISMUTH BRASS [11](#)
BISMUTH BRONZE [18](#)
BRASS [9](#), [10](#), [11](#), [13](#), [14](#), [15](#)
BRONZE [15](#), [16](#), [17](#), [18](#)

CARTRIDGE BRASS [11](#), [12](#)
CHROMIUM COPPER [4](#)
CONVERTER COPPER [5](#)
COPPER [2](#), [3](#), [4](#)
COPPER ALLOYS [23](#)
COPPER IN VARIOUS FORMS [2](#)
COPPER WIRE [2](#)

ENVIROBRASS [7](#)

FEDERALLOY [7](#)
FREE CUTTING BRASS [12](#)

GILDING METAL [5](#)
GLOBULE ARC [2](#)
GUN METAL [5](#)

HIGH TENSILE BRASS [15](#)

LEADED BRASS [12](#), [13](#)
LEADED BRONZE [20](#), [21](#), [22](#)
LEADED TIN BRONZE [20](#), [21](#), [22](#)

MAGNESIUM ALLOY [5](#)
MANGANESE ALLOY [5](#)
MANGANESE BRASS [13](#)
MANGANESE BRONZE [18](#)

NAVAL BRASS [13](#)
NICKEL ALLOY [6](#), [7](#)
NICKEL BRASS [14](#)
NICKEL BRONZE [18](#)

PHOSPHOR BRASS [14](#)
PHOSPHOR BRONZE [19](#)
PHOSPHORUS ALLOY [8](#)
PHOSPHORUS DEOXIDIZED [2](#)

ROD [2](#), [4](#), [5](#), [13](#), [22](#)

SEBILOY [7](#)
SILICON BRASS [14](#)
SILICON BRONZE [19](#)
SILVER ALLOY [8](#)

TIN BRONZE [20](#), [21](#), [22](#)
TIN COPPER [8](#)

WIRE [2](#)

XRF [23](#)

CRM PURITY COPPER DISCS AND RODS

listed in mg/kg		IMN in SETS only, as grouped					IMN CS: 40mm Ø x 25mm or 6mm Ø x 100mm					VS: ~40-45mm Ø x ~25mm									
Number	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	P	Pb	S	Sb	Se	Si	Sn	Te	Zn	Other		
AVAILABLE INDIVIDUALLY																					
VS M04-K3	299	310	124	285	98	115	419	296	551	261	495	70	332	287	93	489	289	293			
VS M04-K2.2	51.5	54.4	33.0	29.2	31.8	23.7	48.3	35.2	59.8	41.1	54.8	34	42.6	37.7	29.7	43	40	50.4			
VS M04-K2.1	50.9	51.9	32.8	29.2	28.2	30.5	56.8	55.1	72.2	41.9	50.3	41	45.9	62.6	.	55	34.9	49.1			
VS M04-7	50.7	50.5	27.6	26.5	30.6	41.3	84.8	53.0	75.6	39.0	26.8	36.6	60.8	.	13.3	45.4	27.0	68.1			
VS M04-5	30.1	11.0	5.2	1.0	1.0	0.8	5.1	6.4	4.4	0.93	1.9	2.9	8.3	6.1	3.1	2.0	2.9	16.9			
VS M04-6 *	21.0	19.8	10.7	10.0	9.2	11.1	40.4	20.0	32.4	14.0	60	19	22.4	10.6	21	14.6	8	32.4	* SET ONLY		
VS M04-K1	15.3	16.0	17.4	15.3	15.2	11.7	25.6	17.5	13.7	12.1	22.4	14.5	17.0	10.3	24.9	10.0	9.6	18.0			
VS M04-1 *	11.2	0.96	.	0.19	.	.	2.0	0.97	0.34	.	1.1	2.9	2.8	3.2	0.7	.	.	.	* SET ONLY		
VS M04-4 *	10.4	4.0	2.6	3.1	4.9	3.2	15.4	4.7	16.0	1.1	0.82	3.0	3.5	2.4	2.2	4.8	4.3	7.8	* SET ONLY		
VS M04-8 *	5.0	2.4	1.1	0.49	3.0	.	29.1	3.5	1.8	1.3	9.6	8.7	5.8	0.73	4.6	0.96	0.8	3.2	* SET ONLY		
VS M04-3 *	2.9	.	0.11	.	0.30	.	3.9	0.49	0.73	.	4.2	4.4	0.55	.	.	0.48	.	0.97			
VS M04-2 *	0.88	0.6	0.63	0.14	0.26	1.0	40.5	1.1	1.1	2.1	13.2	12.8	0.8	0.7	7.1	1.1	.	2.4			
AVAILABLE INDIVIDUALLY EXCEPT CS3 WHICH IS SET ONLY																					
IMN CS1	53.1	2.0	1.1	1.0	0.6	(0.3)	18.4	29.0	46.8	57.7	60.5	65.9	3.0	61.5	(3.0)	52.9	2.1	24.1	B: (1.1)		
IMN CS2	45.6	7.4	6.2	7.4	3.6	35.8	30.5	35.3	26.7	33.8	38.6	44.9	7.5	39.0	(9.4)	33.7	5.6	8.9	B: (2.8)		
IMN CS3	38.9	13.8	12.2	13.4	7.4	10.9	28.3	12.6	11.1	12.1	13.3	18.8	13.0	15.4	(22.2)	13.3	10.6	31.3	B: (4.2)		
IMN CS4	237	42.2	39.6	35.5	24.3	7.0	82.0	8.3	7.2	6.3	7.6	41.3	36.8	6.7	(46.5)	6.2	32.9	44.0	B: (21.7)		
IMN CS5	320	70.5	59.7	66.1	37.5	1.0	90.9	4.3	4.4	2.0	5.0	12.0	63.9	0.9	(54.8)	0.9	49.8	101	B: (35.2)		
Number	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	P	Pb	S	Sb	Se	Si	Sn	Te	Zn	Other		

CRM ELECTROLYTIC COPPER ROD SET

available in SET/6 ONLY				listed in mg/kg			3 or 6 mm Ø x 100 mm			
Number	Ag	As	Bi	Fe	Ni	Pb	Sb	Sn	Zn	Cu
IMN CF1	45.0	6.7	12.5	42.0	29.0	33.0	24.0	21.0	57.0	Rem
IMN CF2	9.0	1.1	.	2.8	0.7	0.6	1.4	.	2.2	Rem
IMN CF3	3.2	1.8	.	20.0	6.4	8.9	2.2	3.2	3.4	Rem
IMN CF4	18.0	43.0	1.2	3.7	7.8	1.1	11.0	1.0	31.0	Rem
IMN CF5	12.0	2.3	0.25	98.0	3.0	3.2	1.9	1.3	4.7	Rem
IMN CF6	12.0	0.32	(0.012)	1.0	(0.4)	1.8	0.2	(0.06)	.	Rem

CRM COPPER

analysis listed in mg/kg		40 mm Ø x 30 mm	
Number	Fe	P	Sn
BAM 391	0.90	3.3	(<0.1)
BAM 390	0.79	1.3	(<0.1)
BAM 392	0.80	7.0	(<0.1)

COPPER WIRE FOR GLOBULE ARC WORK

analysis listed in mg/kg		wire form,intended for globule arc work								C1C: CRM		all others: RM					5 rods 3 mm Ø x 80 mm				
Number	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	Pb	Sb	Se	Sn	Te	Zn	O	P	S	Si		
38X C1B	13	0.8	0.1	<0.01	0.03	0.06	1.2	1.2	1.0	0.8	0.6	.	<0.3	0.3	0.45	.	.	.	last		
38X C1C	11	0.19	0.10	<0.01	.	<0.005	1.7	(0.005)	0.27	(0.05)	0.10	(0.25)	(0.01)	(0.21)	<0.1	266	<0.05	2.0	<0.1		

CHILL CAST PHOSPHORUS DEOXIDIZED COPPER

= Class, where 1 = CRM and 2 = RM, typical analysis

#	Number	P	Cu	Ag	Fe	Al	As	Co	Mn	Ni	Pb	Sb	Sn	Zn
2	CURM 09.01	0.151	99.82	0.011	0.0019	<0.0005	<0.001	<0.0003	<0.0003	<0.0003	<0.0005	<0.0005	<0.001	0.0008
2	CURM 09.02	0.078	99.90	0.0055	0.0042	<0.0005	<0.001	<0.0005	<0.0005	<0.0005	<0.001	<0.0005	<0.001	<0.001
1	SRM C1253a	0.0561	99.46	0.0494	0.0290	0.0176	0.0436	0.0454	0.0357	0.0491	0.0243	0.0139	0.0499	0.0329
1	SRM C1251a	0.0420	99.89	0.0080	0.0285	(<0.0020)	0.0016	0.00132	0.00046	0.00236	0.00235	0.00149	0.0016	0.0024
1	SRM C1252a	0.0125	99.87	0.0158	0.0072	(<0.0020)	0.0118	0.0087	0.0043	0.0128	0.0060	0.0042	0.0120	0.00694
	Number	Au	Bi	Cd	Cr	Mg	S	Se	Si	Te	Units			
	CURM 09.01	.	<0.0003	.	.	.	.	.	<0.001	.	50 mm Ø x 10-12 mm			
	CURM 09.02	.	<0.0005	.	.	.	.	.	<0.002	.	50 mm Ø x 10-12 mm			
	SRM C1253a	0.0072	(0.0056)	0.0070	0.0260	(0.0150)	(0.0050)	0.0136	(0.0580)	0.0168	32 mm x 32 mm x 19 mm			
	SRM C1251a	0.00155	0.00037	(<0.0003)	(0.0003)	(<0.0020)	(0.0035)	0.0011	(<0.0050)	0.0016	32 mm x 32 mm x 19 mm			
	SRM C1252a	0.00339	(0.0019)	0.00169	0.0019	(<0.0020)	(0.0070)	0.0056	(<0.0100)	0.00546	32 mm x 32 mm x 19 mm			

CRM COPPER IN VARIOUS FORMS

analysis listed in mg/g			each of the blow available in 3 forms										A: disc 39 mm Ø x 30 mm					B: Rod 8 mm Ø x 100 mm					C: Chips 50 g				
Number	Ag	Al	As	Au	Be	Bi	Cd	Co	Cr	Fe	In	Mg	Mn	Ni	P	Pb	S	Sb	Se	Si	Sn	Te	Ti	Zn	Zr		
ERM-EB075			3.18	1.46	1.08	1.79	2.69	2.64	1.4	9.3	1.83	7	1.35	2.18	2.59	4.8	25	2.93	1.69	2.6	2.13	1.78	3.2	6.51	.		
ERM-EB074			1.23	0.52	0.31	0.51	0.4	0.83	0.37	5.8	0.49	2.03	0.93	0.61	1.53	2.7	(3.3)	0.57	0.55	.	(1.5)	0.5	0.97	2.2	(8.8)		
1.03	.																										

COPPER

= class, where 1 = CRM and 2 = RM

39X: ~38-42 mm Ø x ~15-20 mm BS: 38 mm Ø x ~7 or 19+ mm IARM: 31 mm Ø x 2 or 18 mm
BAM, BCR, ERM: 38-40 mm Ø x 27-30 mm CTIF: 40 mm Ø x 18 mm IMN, VS: 40 mm Ø x 23-27 mm

#	Number	Al	As	Bi	Cd	Co	Cr	Fe	Mg	Mn	Ni	P	Pb	S
1	IMN CCD6	1.076	.	0.00960	0.0469	0.1966	.	0.853	.	.	0.532	(0.048)	0.1109	.
1	IMN CCD5	0.521	.	0.0093	0.0328	0.1499	.	0.331	.	.	0.329	(0.031)	1.68	.
1	IMN CCD3	0.252	.	0.00368	0.00910	0.0318	.	0.0332	.	.	0.0639	(0.045)	3.28	.
1	IMN CCD4	0.0893	.	0.0182	0.01786	0.0840	.	4.61	.	.	0.00476	(0.11)	0.0674	.
1	IMN CCD2	0.0380	.	0.00120	0.00474	0.0168	.	2.17	.	.	0.0222	(0.053)	0.66	.
1	39X 17869AG	0.0186	0.0104	0.0401	0.0027	0.0084	0.0199	0.0365	0.0103	0.0325	0.0111	0.0245	0.0714	0.0069
1	39X 17871D	0.0150	.	0.052	0.0027	.	.	0.0019	.	.	0.0412	0.020	0.050	0.0052
1	39X 17870AJ	0.0047	0.0056	0.0476	0.0029	0.0042	0.0009	0.0416	0.020	0.0387	0.0079	0.0203	0.047	0.0037
1	39X 17866AH	0.0028	0.0435	0.0109	0.0410	0.0273	0.0316	0.0075	0.0041	0.0147	0.0511	0.0125	0.0501	0.052
1	BAM M386a	0.00269	0.00208	0.00095	0.00054	0.00049	0.00115	0.00593	0.00767	0.00111	0.00211	0.00065	0.00198	0.00159
1	IARM 279A	(0.002)	(0.002)	(0.001)	.	(0.002)	0.86	0.025	.	(0.002)	0.014	(0.005)	(0.01)	0.0015
1	BS Cu997	(0.002)	(0.0008)	.	.	(0.001)	(0.0003)	0.0032	(0.0005)	(0.001)	0.0004	0.0055	0.0008	(0.006)
1	IARM 70C	(0.0014)	(0.0009)	(0.002)	(0.0008)	(0.0014)	(0.0002)	(0.0016)	(0.0003)	(0.0002)	(0.0004)	(0.0014)	(0.0013)	0.0008
1	BAM 370	0.00126	.	.	.	.	.	.	.	.	.	0.00117	0.0016	.
1	39X 17867AE	0.0012	0.039	0.012	0.0061	0.0126	.	0.0097	0.0053	0.0016	0.0394	0.0242	0.0097	0.024
1	BAM M383d	0.00102	<0.0001	0.000082	0.000062	0.000130	0.000077	0.00224	0.00017	0.000097	0.00047	<0.0001	0.00078	0.00035
1	BS 110C	(0.0009)	(0.0001)	.	.	(0.001)	(0.0004)	(0.002)	(0.0005)	(0.0004)	(0.0005)	0.0016	(0.0003)	0.0008
1	BS 14500a	(0.0007)	.	Ca: (0.0004)	N: (0.0006)	(0.0005)	.	(0.001)	(0.0006)	(0.0004)	0.0026	0.010	0.0031	0.035
1	BS 14500	(<0.0006)	(<0.0005)	.	.	(<0.0001)	(<0.0001)	0.0041	(<0.0003)	0.00004	(<0.0003)	0.0075	0.0008	0.0033
1	IMN CCD1	(0.00039)	.	(0.00031)	0.00115	0.00096	.	0.0116	.	.	0.1038	(0.033)	0.0063	.
1	BAM M384c	<0.0002	0.00029	0.00038	0.00050	0.00040	(0.00047)	0.00330	0.00018	0.00057	0.00057	<0.0001	0.00072	0.00040
1	BAM M382a	<0.0002	0.000073	0.000075	0.000050	0.000092	0.000024	0.00103	0.00019	0.00025	0.00027	<0.0002	0.00022	0.00067
1	39X 27866A	.	0.0383	0.0047	0.0139	0.0308	0.0012	0.0030	.	.	0.0487	0.0147	0.0054	0.0469
1	39X 27869A	.	0.0098	0.0376	0.0028	0.0036	(0.0002)	0.0030	.	.	0.0190	0.0119	0.0225	0.0112
1	IMN CS5	.	0.00705	0.00597	0.00661	0.00375	0.00010	0.00909	.	0.00043	0.00044	0.00020	0.00050	0.00120
1	IMN CT6	.	0.0054	0.0040	.	0.011	.	0.014	.	.	0.011	0.011	0.0014	0.0069
1	IMN CS4	.	0.00422	0.00396	0.00355	0.00243	0.00070	0.00820	.	0.00083	0.00072	0.00063	0.00076	0.00413
1	IARM Cu101-18	.	0.00015	0.00005	.	.	.	0.00030	.	0.00003	0.00027	.	0.00012	0.00050
1	IARM Cu110-18	.	0.00013	.	.	.	(0.00009)	0.00034	0.00010	0.00006	(0.00006)	0.00160	(0.00005)	0.00060
1	BAM 372	.	0.00103	.	0.000163	.	.	.	.	0.00114	0.0012	.	.	.
1	IMN CS2	.	0.00074	0.00062	0.00074	0.00036	0.00358	0.00305	.	0.00353	0.00267	0.00338	0.00386	0.00449
1	IMN CS1	.	0.00020	0.00011	0.00010	0.00006	(0.00003)	0.00184	.	0.00290	0.00468	0.00577	0.00605	0.00659
1	IMN CS7 D	.	0.00009	<0.00005	(0.000002)	0.000009	0.00197	0.00049	.	0.00022	0.00044	(0.00024)	(0.00009)	0.00070
1	IMN CS6	.	0.00002	<0.00005	(0.000006)	(0.00002)	0.00002	0.00208	.	0.00007	0.00008	(0.00015)	(0.00004)	0.00054
1	BAM 381	.	<0.0001	<0.0001	<0.00004	<0.00004	0.000013	0.00028	(0.000034)	0.000027	0.000073	.	0.00005	(0.00029)
1	BAM 369	.	.	0.00097	.	0.00104	0.00092	.	0.00036	.	.	.	.	.
1	BAM 371	.	.	.	.	.	.	0.0018	.	.	.	.	.	0.0013

continued analysis listed in mass % except * which is mg/kg

Number	Sb	Se	Si	Sn	Te	Ti	Zn	Zr	Ag*	Au*	C*	Be*	Cu	In*	O*	Other
IMN CCD6	0.2019	.	.	0.547	.	.	0.320	.	512	.	.	.	.	.	.	.
IMN CCD5	0.131	.	.	1.072	.	.	0.0841	.	313	.	.	.	.	.	.	.
IMN CCD3	0.01886	.	.	0.258	.	.	1.61	.	598	.	.	.	.	.	.	.
IMN CCD4	0.0791	.	.	0.1090	.	.	0.1565	.	1528	.	.	.	.	.	.	.
IMN CCD2	0.00479	.	.	0.0552	.	.	0.756	.	208	.	.	.	.	.	.	.
39X 17869AG	0.0375	0.0197	0.0117	0.070	0.0392	.	0.0261	.	399	22	Ge: 0.0047	.	26	.	.	.
39X 17871D	0.0141	0.0310	0.0014	0.105	0.0137	.	0.091	.	309	5	.	.	32	.	Ge*: (9)	.
39X 17870AJ	0.0490	0.0111	0.0048	0.0100	0.040	.	0.0125	.	480	7	Ge: 0.0149	.	100	.	.	.
39X 17866AH	0.0095	0.0053	0.0111	0.0614	0.0065	.	0.0840	.	86	(4)	Ge: 0.0052	.	97	.	.	.
BAM M386a	0.00252	0.00097	(0.0012)	0.00216	0.00311	0.00347	0.00367	.	44.2	.	.	.	.	.	.	.
IARM 279A	(0.004)	.	0.020	0.021	.	.	(0.01)	0.012	(30)	.	(20)	.	99.1	.	(10)	XRF only
BS Cu997	(0.0002)	.	(0.0009)	0.0003	.	17025, 17034	0.0006	(0.007)	.	7	.	.	99.7	.	39	17025
IARM 70C	(0.003)	(0.001)	(0.0006)	0.0005	(0.001)	.	(0.002)	(0.001)	.	.	.	.	99.94	<1	.	.
BAM 370	0.0015	.	(0.0019)	0.00165	.	.	.	.	.	.	.	.	.	.	.	.
39X 17867AE	0.013	0.0061	0.0081	0.043	0.0072	B:0.0042	0.0381	.	148	11	Ge:0.0104	.	45	.	.	.
BAM M383d	0.00018	(0.00006)	.	0.00038	0.000047	0.00012	0.000108	<0.0001	.	As*:1.20	.	.	.	.	.	.
BS 110C	(0.0003)	.	(0.0009)	(0.0002)	.	17025, 17034	(0.004)	.	.	(20)	.	99.97	.	9	Ca*: (2)	.
BS 14500a	(0.005)	.	(0.002)	0.0028	0.51	17025, 17034	0.0053	(0.001)	.	(30)	.	99.6	.	17	.	.
BS 14500	(<0.001)	.	(<0.002)	0.0002	0.53	17025	0.004	.	(<2)	5	(<1)	99.4	.	7	last	.
IMN CCD1	(0.00022)	.	.	0.00088	.	.	0.0101	.	153	.	.	.	.	.	.	.
BAM M384c	0.00098	0.00029	.	0.00006	0.00061	<0.00002	0.00010	<0.00003	14.8	.	.	.	.	.	.	.
BAM M382a	0.000087	0.000077	.	0.00047	0.000072	0.000057	0.00076	.	29	.	.	.	.	.	.	.
39X 27866A	0.0052	0.0028	.	0.0448	0.0032	.	0.0287	.	57	16	.	.	437	.	Ge*: 29	.
39X 27869A	0.0362	0.0127	.	0.0106	0.0153	.	0.0065	.	349	80	.	.	90	.	Ge*: 123	.
IMN CS5	0.00639	0.00009	(0.00548)	0.00009	0.00498	.	0.0101	.	320	.	.	.	.	.	B*: (35.2)	.
IMN CT6	0.011	0.011	.	0.013	0.012	.	0.030	.	39	.	.	.	.	.	B*: 60	.
IMN CS4	0.00368	0.00067	(0.00465)	0.00062	0.00329	.	0.00440	.	237	.	.	.	.	.	B*: (21.7)	.
IARM Cu101-18	0.00014	.	.	0.00020	.	.	0.00008	.	13.0	.	.	.	.	.	.	.
IARM Cu110-18	.	(0.00020)	.	(0.00020)	.	.	0.00010	.	13.0	.	(18)	.	.	10.0	.	.
BAM 372	.	0.00076	.	.	.	.	.	.	.	.	.	.	.	.	.	.
IMN CS2	0.00075	0.00390	(0.00094)	0.00337	0.00056	.	0.00089	.	45.6	.	.	.	.	.	B*: (2.8)	.
IMN CS1	0.00030	0.00615	(0.00030)	0.00529	0.00021	.	0.00241	.	53.1	.	.	.	.	.	B*: (1.1)	.
IMN CS7 D	0.00010	<0.00010	<0.00010	0.00005	<0.000005	.	.	.	13.7	.	.	.	.	.	B*: <0.5	.
IMN CS6	0.00010	<0.00010	.	0.00106	<0.000005	.	0.00014	.	85	.	.	.	.	.	B*: <0.5	.
BAM 381	<0.00015	<0.0001	<0.0005	0.00040	.	<0.00005	0.000522	<0.0009	.	.	.	.	.	.	.	.
BAM 369	.	.	.	.	.	.	0.0022	.	.	.	.	.	.	.	.	.
BAM 371	.	.	.	.	0.0014	0.00132	.	.	.	.	.	11.5	.	.	.	.

Number	Sb	Se	Si	Sn	Te	Ti	Zn	Zr	Ag*	Au*	C*	Be*	Cu	In*	O*	Other
--------	----	----	----	----	----	----	----	----	-----	-----	----	-----	----	-----	----	-------

CRM	COPPER RODS										analysis listed in mg/kg				IMN: 6 mm Ø x 100 mm				SRM: ~6.5 mm Ø x 103 mm				
Number	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	O	P	Pb	S	Sb	Se	Sn	Te	Zn	Cu				
SRM 494	50	2.6	0.35	.	0.5	2.0	.	3.7	11.7	.	.	26.5	15	4.5	2.00	70	0.58	400	99.91				
IMN CS7R	13.7	0.9	<0.5	(0.02)	0.09	19.7	4.9	2.2	4.4	.	(2.4)	(0.9)	7.0	1.0	<1.0	0.5	<0.05	.	.				
SRM 495	12.2	1.6	0.50	.	.	6.0	.	5.3	5.4	.	.	3.2	13	8.0	0.63	1.5	0.32	12	99.94				
SRM 457	8.086	<2	0.22	<1	0.227	<2	2.4	<0.1	0.67	367	.	0.512	4	0.214	4.05	<0.1	0.296	<3	99.97				
SRM 457 also contains Au:<0.05), Cd Si and Ti:<1)										IMN CS7R also contains B:<0.5 and Si:<1.0													

SRM 457 also contains Au:<(0.05), Cd Si and Ti:<1) IMN CS7R also contains B:<0.5 and Si:<1.0

BERYLLIUM ALLOY

= class, where 1 = CRM and 2 = RM

17025, 17034

#	Number	Be	Co	Ag	Al	Cr	Cu	Fe	Ni	Pb	Si	Sn	Zn	Alloy	Notes
2	CTIF CuBeCo1	3.31	0.192	.	0.034	(0.017)	(94.5)	0.214	1.51	0.0368	(0.35)	0.025	0.0984		Typical Analysis
2	CTIF 4584	2.53	0.04	.	0.033	.	97.05	0.120	0.015	(0.002)	0.166	0.022	0.022		Typical Analysis
2	CTIF 4872	1.93	0.400	.	0.059	(0.04)	97.00	0.107	0.103	0.019	0.16	0.044	0.119	172	Typical Analysis
2	BS 172Be-1	1.89	0.206	.	(0.02)	0.0032	97.68	0.052	0.039	(0.002)	0.055	0.033	0.0070	172	last of stock
1	IARM Cu172-19	1.89	0.0017	0.0011	0.032	0.001 7	(97.6)	0.071	0.237	.	0.045	0.0007	.	172	
1	36X CBC4E	1.869	0.215	.	0.0258	.	97.47	0.0274	0.0080	0.329	0.048	0.002	0.003	173	
1	36X CBC3D	1.840	0.209	.	0.019	.	97.77	0.046	0.007	0.0025	0.039	0.0021	0.004		
1	BS 172Be-2	1.83	(0.06)	.	0.032	0.015	97.7	0.127	0.165	0.041	(0.029)	0.015	0.0057	172	17025
2	CTIF 4766	1.58	0.64	.	0.027	(0.2)	96.83	0.165	0.203	0.053	0.11	0.100	0.070		Typical Analysis
2	CTIF CuBeCo6	1.5	(1.90)	1.37	0.135	0.0576	93.09	0.12	(1.45)	0.0397	0.26	0.0135	0.0330		
2	CTIF 4583	0.84	(0.002)	.	0.029	.	96.35	(0.15)	2.02	0.084	0.08	0.25	0.094		Typical Analysis
1	36X CBC6A	0.507	1.045	0.0015	0.0490	.	97.11	0.0243	1.132	0.0014	0.0263	0.0041	0.0010		
2	CTIF CuBeCo4	0.44	1.56	0.468	0.131	0.011	(96.2)	0.0138	0.905	0.0716	(0.05)	0.095	0.061		
1	36X CBC2F	0.439	2.22	0.0013	0.0097	.	97.15	0.0076	0.121	(0.0008)	0.0257	(0.0007)	0.0018		Typical Analysis
1	36X CBC5B	0.404	0.0084	0.0011	0.0104	.	97.61	0.0108	1.905	0.0015	0.004	0.0013	0.0010	175.1	
1	BS 17510	0.35	(0.024)	0.0014	0.042	(0.015)	97.6	0.042	1.70	0.0014	0.137	(0.004)	(0.005)	175.1	17304
2	CTIF 4873	0.10	0.86	.	0.069	0.080	98.60	0.135	0.050	(0.003)	0.071	(0.007)	(0.003)		Typical Analysis

w = wrought and c = cast; D = disc and M = mushroom

Number	As	C	Ca	Mg	Mn	O	P	S	Sb	Te	Zr	Form	Units
CTIF CuBeCo1	.	.	.	.	0.0303	.	.	.	.	.	.	c	M 60 mm Ø x 5 mm
CTIF 4584	.	.	.	.	(0.002)	.	.	.	.	.	.	c	M 60 mm Ø x 5 mm
CTIF 4872	.	.	.	.	0.008	.	.	.	.	.	.	c	M 60 mm Ø x 5 mm
BS 172Be-1	(0.001)	(0.001)	.	.	0.0010	.	0.003	<(0.0002)	.	.	.	w	D 38 mm Ø x ~7 mm last
IARM Cu172-19	.	.	.	0.112	0.0019	.	0.0036	0.0010	0.0007	.	.	D	~38 mm Ø x ~3 or ~19 mm
36X CBC4E	.	.	.	0.0035	.	.	0.0027	.	.	.	.	w	D ~38 mm Ø x ~15 mm
36X CBC3D	.	.	.	0.0040	.	.	.	.	.	.	.	w	D 41 mm Ø x 15 mm
BS 172Be-1	(0.00014)	(0.002)	(0.0008)	(0.01)	0.0070	(0.0008)	0.0014	(0.0003)	.	last	(0.0003)	w	D 38 mm Ø x ~7 or ~10 mm
CTIF 4766	.	.	.	.	0.007	.	.	.	.	.	.	c	M 60 mm Ø x 5 mm
CTIF CuBeCo6	.	.	.	.	0.0173	.	.	.	.	.	.	c	M 60 mm Ø x 5 mm
CTIF 4583	.	.	.	.	0.064	.	.	.	.	.	.	c	M 60 mm Ø x 5 mm
36X CBC6A	.	.	.	0.0070	.	.	0.0016	.	.	.	0.0553	w	D ~40 mm Ø x ~15 mm
CTIF CuBeCo4	.	.	.	.	0.0507	.	.	.	.	.	.	c	M 60 mm Ø x 5 mm
36X CBC2F	.	.	.	0.0036	.	.	0.0067	.	.	.	(0.0006)	w	D ~40 mm Ø x ~15 mm
36X CBC5B	.	.	.	0.0009	.	.	.	.	.	.	.	w	D ~40 mm Ø x ~15 mm
BS 17510	<0.005	(0.003)	<0.005	(0.007)	0.0020	.	(0.005)	<0.05	0.0024	.	0.0011	c	D 38 mm Ø x ~7 or 19+ mm
CTIF 4873	.	.	.	.	(0.002)	.	.	.	.	.	.	c	M 60 mm Ø x 5 mm

CHROMIUM COPPER

= class, where 1 = CRM and 2 = RM

#	Number	Cr	Ag	Al	Fe	Mn	Ni	Pb	Si	Sn	Zn	Zr	Cu
1	IARM Cu182-18	1.09	0.0008	0.0031	0.041	0.0007	0.0007	0.0019	(0.09)	(0.002)	0.010	0.063	98.8
1	IARM 158C	1.04	(0.01)	0.002	0.090	0.019	0.32	0.01	0.02	0.01	0.014	.	98.5
1	BS 18150A	0.79	.	0.0023	0.007	0.0010	0.0019	0.0011	0.027	0.0144	0.0006	0.203	[98.9]
1	BS 18150	0.74	.	0.0009	0.0047	0.0010	0.0010	0.0005	0.019	0.0097	0.0006	0.113	[99.1]
2	HRT CU2019	0.73	.	.	(0.005)	.	.	.	0.030	0.011	.	0.17	98.97
1	36X 274B	0.333	0.0016	0.0011	0.0165	0.0004	2.59	0.0011	0.645	(0.0008)	(0.0009)	.	96.44

Number	As	C	Co	Mg	N	O	P	S	Sb	Units
IARM Cu182-18	.	.	0.00013	0.0019	.	.	0.0012	0.0018	.	38 mm Ø x 3 or 19 mm
IARM 158C	(0.001)	0.002	0.002	.	<0.0005	0.002	0.005	0.003	0.002	31 mm Ø x 2 or 18 mm
BS 18150A	(0.0003)	0.0010	(0.0003)	.	.	(0.0008)	0.0045	0.0007	(0.0002)	38 mm Ø x ~7 or 19 mm
BS 18150	(0.0004)	0.0009	(0.0002)	.	.	(0.0006)	0.0037	0.0007	(0.0001)	38 mm Ø x ~7 or 19+ mm
HRT CU2019	.	.	.	.	.	.	(0.005)	.	(0.006)	40 mm Ø x 20 mm
36X 274B	.	.	0.0042	.	.	.	0.0015	.	.	~40 mm Ø x ~15 mm

Need a larger size?
Most BS items are
available in any height.

CRM CONVERTER COPPER DISC AND ROD SETS

analysis listed in mass %

AVAILABLE IN SETS ONLY, AS GROUPED

10 mm Ø x 100 mm

Number	Ag	As	B	Bi	Co	Cu	Fe	Ni	P	Pb	S	Sb	Se	Sn	Te	Zn
IMN CP1	0.057	0.32	0.024	0.010	0.051	.	0.17	0.40	0.002	0.013	0.054	0.33	0.002	0.24	0.053	0.20
IMN CP2	0.042	0.32	0.032	0.013	0.032	.	0.10	0.20	0.050	0.086	0.036	0.24	0.041	0.14	0.036	0.19
IMN CP3	0.026	0.11	0.00003	0.0067	0.012	.	0.082	0.12	0.038	0.21	0.012	0.11	0.018	0.070	0.022	0.11
IMN CP4	0.016	0.050	0.0042	0.0042	0.011	.	0.045	0.040	0.020	0.88	0.0060	0.040	0.011	0.028	0.011	0.046
IMN CP5	0.0062	0.0056	(0.011)	0.0011	0.0061	.	0.016	0.0005	0.0050	(1.48)	0.0024	0.010	0.0060	0.0070	0.0064	0.0008
IMN CH6	0.18	.	.	.	0.18	Rem	0.028	0.40	.	0.50	.	.	.	.	.	0.19
IMN CH7	0.40	.	.	.	0.11	Rem	0.11	0.18	.	1.01	.	.	.	.	.	0.047
IMN CH8	0.039	.	.	.	0.020	Rem	0.0012	0.036	.	1.49	.	.	.	.	.	0.077
IMN CH9	0.010	.	.	.	0.0060	Rem	0.0060	0.010	.	1.97	.	.	.	.	.	0.015
IMN CG1	0.011	.	.	.	0.17	Rem	0.013	0.036	.	0.60	.	.	.	.	.	0.016
IMN CG2	0.25	.	.	.	0.098	Rem	0.015	0.011	.	0.30	.	.	.	.	.	0.026
IMN CG3	0.040	.	.	.	0.045	Rem	0.030	0.39	.	0.22	.	.	.	.	.	0.14
IMN CG4	0.10	.	.	.	0.057	Rem	0.25	0.23	.	0.11	.	.	.	.	.	0.12
IMN CG5	0.41	.	.	.	0.0079	Rem	0.069	0.10	.	0.053	.	.	.	.	.	0.18

CRM GILDING METAL

Number	Cu	Fe	Ni	P	Pb	Sn	Zn	method	Units
SRM 1114	96.4	0.01	0.021	0.009	0.012	0.02	3.4	wrought	31 mm Ø x 19 mm
SRM 1113	95.0	0.04	0.057	0.008	0.026	0.06	4.8	wrought	31 mm Ø x 19 mm
SRM 1112	93.3	0.07	0.10	0.009	0.057	0.12	6.3	wrought	31 mm Ø x 19 mm

CRM GILDING METAL SET

available individually or as a set

wrought 40 mm Ø x 25 mm

Number	Ag	Al	As	Be	Bi	Cd	Cu	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Te	Zn
IMN M11	0.0038	0.0400	0.0720	0.000091	0.00063	0.0230	95.69	0.2500	0.0030	0.0059	0.0280	0.0060	0.0430	0.000044	0.0032	0.1500	0.0065	3.57
IMN M12	0.0090	0.0550	0.0540	0.00085	0.00056	0.0160	93.35	0.1600	0.0081	0.0180	0.0220	0.0160	0.0490	0.0019	0.0120	0.1000	0.0110	6.19
IMN M13	0.0200	0.0150	0.0340	0.0019	0.0026	0.0110	91.46	0.0860	0.0350	0.0730	0.0150	0.0420	0.0230	.	0.0310	0.0670	0.0031	8.01
IMN M14	0.0260	0.0079	0.0031	0.0065	0.0026	0.0054	88.35	0.0410	0.0500	0.1400	0.0073	0.0700	0.0120	0.0006	0.0600	0.0130	0.0021	11.13
IMN M15	0.0330	0.0021	0.0150	0.0072	0.0043	0.0012	94.71	0.0150	0.0690	0.2500	0.0026	0.0960	0.0019	0.0096	0.0820	0.0040	.	4.44

GUN METAL

C, CURM: 50 mm Ø x 10 - 12 mm

33X GM29: wrought 33 mm Ø x 19 mm

other 33X: chill cast ~40 mm Ø x ~15 mm

Number	Zn	Sn	Pb	Ni	Fe	Cu	Ag	Al	As	Bi	Co	Cr	Mn	P	S	Sb	Si
CRM																	
33X GM9A	13.81	2.93	6.91	0.710	0.090	75.1	0.0321	0.0052	0.0251	0.076	0.079	Cd:0.0072	.	0.0547	0.0153	0.184	(0.003)
33X GM4AD	5.90	3.02	5.27	1.482	0.0932	84.02	0.0206	0.0015	0.0228	0.0442	0.0077	.	0.00060	0.0034	0.034	0.0568	0.0010
33X GM8H	5.80	3.89	5.76	0.493	0.142	83.63	0.0095	0.0052	0.0110	0.016	0.0151	0.0150	.	0.035	0.028	0.061	(0.003)
33X GM5P	5.66	4.48	5.18	0.728	0.127	83.39	0.0497	0.055	0.0498	0.018	0.0298	Cd:0.0048	Te:0.0075	0.0507	0.0411	0.072	0.0310
33X GM20B	1.80	4.49	0.294	0.211	0.44	89.49	0.200	0.133	0.300	0.044	0.0211	Cd:0.020	0.040	0.060	0.060	2.41	.
33X GM7K	1.363	10.07	1.79	0.531	0.0178	85.69	0.0682	.	0.095	0.098	0.100	.	.	0.0050	0.0613	0.111	Te:0.0112
RM																	
CURM 71.31	4.27	4.38	6.44	2.07	0.098	82.30	0.052	0.045	0.11	0.027	last	<0.01	0.010	0.060	0.050	0.11	0.006
33X GM24A	3.67	3.85	3.35	0.0087	0.0083	88.88	0.0046	(0.0001)	0.0010	0.0009	.	(0.0013)	<0.0005	0.190	0.003	0.0012	0.0028
CURM 71.33	3.60	4.96	6.84	0.938	0.018	83.60	<0.002	<0.001	<0.001	<0.002	.	<0.0005	<0.0005	<0.001	<0.001	<0.002	<0.005
C71.34	1.55	8.20	2.47	<0.01	0.29	rem	0.025	0.007	0.18	0.029	last	0.03	0.05	0.020	0.16	0.071	0.04
CURM 71.34	1.54	8.19	2.48	<0.005	0.29	86.74	0.023	0.008	0.18	0.031	.	0.04	0.05	0.019	0.18	0.072	0.03
Number	Zn	Sn	Pb	Ni	Fe	Cu	Ag	Al	As	Bi	Co	Cr	Mn	P	S	Sb	Si

CRM MANGANESE ALLOY SET

available individually or as a set

40 mm Ø x 13 mm

Number	Ag	As	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN CK1	0.012	0.013	0.029	1.06	0.44	0.0011	0.0021	0.0049	0.049	0.13	0.24
IMN CK2	0.0094	0.010	0.11	1.51	0.38	0.0022	0.0062	0.0015	0.091	.	0.14
IMN CK3	0.0066	0.0095	0.17	1.78	0.27	0.0043	0.0098	0.0026	0.033	0.075	0.095
IMN CK4	0.0041	0.0055	0.26	1.91	0.13	0.0056	0.017	0.0041	0.0025	0.042	0.065
IMN CK5	.	0.0015	0.29	2.30	0.011	.	.	0.0051	0.011	0.0048	0.033
IMN CK6	0.0012	0.0039	0.40	2.64	0.073	0.013	.	0.0052	0.21	0.025	0.034

CRM MAGNESIUM ALLOY SET

available in set only 40 mm Ø x 25 mm

Number	Mg
IMN CCB-1	0.00405
IMN CCB-2	0.0339
IMN CCB-3	0.241
IMN CCB-4	0.509
IMN CCB-5	0.748

NICKEL ALLOY, chart 1 of 2

#	Number	Ni	Ag	Al	Bi	Co	Cr	Cu	Fe	Mn	Nb	P	Pb	S	Si	Sn	Zn
1	36X 71500A	31.24	.	(0.001)	.	0.0163	.	66.74	0.888	0.850	.	0.0074	0.0114	0.0454	0.0096	0.0112	0.150
1	BS 715B	31.2	.	(0.0060)	.	(0.012)	(0.003)	67.3	0.59	0.745	.	0.0034	(0.003)	0.0034	0.0103	0.0036	0.053
1	BS 715C	31.2	.	(0.004)	.	(0.012)	(0.003)	67.4	0.59	0.706	.	0.0035	(0.003)	0.0036	0.011	0.0040	0.052
1	36X CN5P	31.03	.	.	.	0.0238	0.141	66.67	0.347	0.217	0.430	0.034	0.0120	0.088	0.689	0.0090	0.209
1	IARM Cu715-20	31.0	.	(0.004)	.	(0.004)	.	67.4	0.51	0.80	.	(0.009)	(0.001)	(0.002)	(0.09)	(0.004)	(0.007)
1	SRM 1276a	30.8	(0.004)	.	(<0.0001)	0.045	(0.0002)	67.5	0.56	1.01	.	0.006	0.004	(0.008)	(0.001)	0.023	0.038
2	BS 715A	30.22	.	(0.01)	.	0.03	.	68.0	0.61	0.82	.	0.006	(0.007)	0.001	0.10	0.008	0.10
2	C62.11	29.8	.	.	.	<0.005	.	rem	0.60	0.52	.	.	<0.005	<0.005	0.36	0.04	0.097
2	CTIF CN33	29.75	.	(0.0105)	0.0212	.	.	66.95	1.66	0.490	0.062	0.021	0.053	0.013	0.500	(0.003)	0.385
2	C62.15	25.9	.	.	.	0.042	.	rem	2.36	0.23	.	.	0.016	0.023	0.014	0.03	0.04
1	BAM 389	24.7	.	.	0.0044	0.0770	0.0153	74.3	0.107	0.415	.	0.0093	0.0098	.	.	0.0262	0.112
2	C62.14	20.2	.	.	0.03	0.03	.	rem	1.49	0.24	.	.	0.01	0.083	0.022	0.12	0.12
1	IARM 298A	19.6	(0.009)	(0.003)	0.014	(0.016)	(0.005)	65.3	0.73	0.34	<0.01	(0.004)	4.0	(0.011)	0.019	4.0	5.8
2	C65.29	16.8	.	.	.	.	.	58.9	0.39	0.17	.	0.07	0.11	0.07	0.02	0.08	23.4
1	36X CN24A	15.41	0.0466	(0.0010)	.	0.0096	0.0065	52.56	0.127	23.60	.	0.0037	0.0056	.	.	(0.0023)	8.00
2	C65.28	15.3	.	.	.	.	.	56.9	0.13	0.57	.	0.07	0.06	0.03	0.01	0.15	26.7
1	36X CN11A	14.96	.	1.457	.	0.0049	0.380	77.56	0.992	4.34	0.124	(0.002)	(0.003)	0.0012	0.083	(0.002)	(0.006)
1	IARM CuH130-18	14.6	(0.0010)	2.76	(0.0020)	0.0037	(0.002)	80.9	0.84	0.449	.	(0.004)	(0.0020)	(0.0010)	0.024	(0.0010)	0.001
1	36X CN13A	14.52	.	2.65	.	(0.001)	.	81.46	0.870	0.442	.	0.0011	(0.001)	(0.002)	0.012	(0.001)	0.001
1	IARM CuH191-18	14.5	(0.0020)	1.60	(0.0020)	(0.002)	(0.0013)	(79.6)	0.96	3.79	.	(0.003)	(0.0030)	(0.002)	(0.017)	(0.0020)	0.001
1	36X CN23A	14.38	0.042	0.007	.	0.0509	0.0029	70.22	0.140	0.0095	.	0.0299	0.115	.	.	0.102	14.88
2	C65.27	13.9	.	.	.	.	.	57.0	0.26	0.13	.	0.02	0.04	0.03	<0.002	0.01	28.7
1	36X CN12A	13.05	.	2.41	.	0.0056	.	83.79	0.105	0.402	0.0010	0.0011	0.0037	.	0.040	(0.0011)	0.157
1	CTIF CN1	12.3	.	(0.003)	.	.	.	85.0	1.1	0.8	(0.1)	.	0.085	0.046	(0.05)	(0.005)	0.2
1	36X CN2K	11.45	0.0274	0.0009	.	0.197	0.0043	86.25	0.0404	(0.69)	0.0176	0.0408	0.0449	0.0100	0.049	0.0258	1.03
2	CTIF CN4	11.2	.	(0.02)	.	.	.	84.0	1.8	1.5	0.7	.	0.006	(0.001)	(0.01)	0.058	0.07
2	BS 706B	10.9	.	<0.003	.	0.005	.	87.00	1.56	0.61	.	0.009	0.006	0.009	<0.002	0.006	0.054
1	36X 70600A	10.65	0.0055	(0.0008)	.	0.0087	.	86.70	1.619	0.759	.	0.0062	0.0086	0.0136	.	0.0090	0.115
2	HRT CU2014	10.49	.	.	.	.	.	86.96	1.60	0.82	.	.	(0.005)	.	.	(0.005)	(0.01)
2	BS 706A	10.18	.	(0.002)	.	0.007	.	87.80	1.30	0.66	.	0.006	0.008	0.012	<0.005	0.011	0.13
2	CTIF CuNi 10	10.08	.	.	.	.	.	87.4	1.69	0.70	.	.	0.0027	(0.002)	.	(<0.01)	0.033
#	Number	Ni	Ag	Al	Bi	Co	Cr	Cu	Fe	Mn	Nb	P	Pb	S	Si	Sn	Zn
Number		As	B	Be	C	Cd	Mg	Sb	Te	Ti	Zr	Units					
36X 71500A		.	0.0049	.	0.0240	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm				
BS 715B		(0.001)	.	(0.0002)	0.0089	.	.	(0.001)	0:0.0020	.	(0.0002)	.	38 mm Ø x ~7 or 19+ mm	17025, 17034			
BS 715C		(0.001)	.	(0.0002)	0.0081	.	(0.005)	(0.0014)	0:0.0020	.	(0.001)	.	38 mm Ø x ~7 or 19+ mm	17025, 17034			
36X CN5P		.	0.0053	0.0035	(0.008)	.	0.0106	.	.	0.0203	.	.	~40 mm Ø x ~15 mm				
IARM Cu715-20		.	.	.	(0.005)	.	(0.005)	.	.	0.073	.	.	31 mm Ø x 2 or 18 mm				
SRM 1276a		(<0.001)	(0.0001)	.	.	0.0002	0.12	0.0004	0.005	(0.0002)	.	.	32 mm Ø x 19 mm	Se: 0.0005			
BS 715A		(0.0014)	.	.	0.03	.	.	(0.003)	.	.	.	.	38 mm Ø x ~7 or 19+ mm				
C62.11		.	.	.	.	.	0.03	.	.	.	.	.	50 mm Ø x 10 - 12 mm				
CTIF CN33		.	.	.	0.025	0.0060	0.043	.	0.0224	.	.	.	60 mm Ø x 5 mm				
C62.15		.	.	.	.	.	0.004	.	.	.	.	.	50 mm Ø x 10 - 12 mm				
BAM 389		.	.	.	.	0.0016	0.067	0.0046	.	0.0660	0.098	.	40 mm Ø x 30 mm				
C62.14		.	.	.	.	0.002	.	.	.	.	.	.	50 mm Ø x 10 - 12 mm				
IARM 298A		(0.004)	<0.005	<0.001	(0.013)	<0.001	0.0004	(0.04)	<0.005	.	<0.01	.	31 mm Ø x 2 or 18 mm				
C65.29		.	.	.	.	0.01	.	.	.	.	.	.	50 mm Ø x 10 - 12 mm				
36X CN24A		(0.0011)	.	.	0.0436	.	.	.	.	.	.	.	~40 mm Ø x ~17 mm				
C65.28		.	.	.	.	.	0.01	.	.	.	.	.	50 mm Ø x 10 - 12 mm				
36X CN11A		.	.	.	(0.001)	.	0.0241	.	.	.	.	.	40 mm Ø x ~17 mm				
IARM CuH130-18		(0.0060)	(0.0009)	.	(0.006)	(0.0030)	0.0013	(0.0030)	.	(0.0010)	(0.0008)	.	31 mm Ø x 2 or 18 mm CRM				
36X CN13A		.	(0.002)	.	(0.003)	.	0.0039	.	.	.	.	.	~38 mm Ø x ~15 mm				
IARM CuH191-18		.	(0.0030)	.	(0.004)	(0.0010)	0.0059	.	.	.	.	.	31 mm Ø x 2 or 18 mm CRM				
36X CN23A		0.047	.	.	.	0.0021	.	.	.	.	.	.	40 mm Ø x ~17 mm				
C65.27		.	.	.	.	.	<0.01	.	.	.	.	.	50 mm Ø x 10 - 12 mm				
36X CN12A		.	0.0055	.	0.0101	.	0.072	.	.	.	.	.	~40 mm Ø x ~15 mm				
CTIF CN1N		.	.	.	(0.002)	.	.	.	.	.	.	.	60 mm Ø x 5 mm				
36X CN2K		.	.	.	0.0013	0.0054	0.030	.	.	0.0350	.	.	~40 mm Ø x ~15 mm				
CTIF CN4		.	.	.	(0.001)	.	.	.	.	.	.	.	60 mm Ø x 5 mm				
BS 706B		<0.0005	.	.	(0.004)	.	.	<0.002	.	.	.	.	38 mm Ø x ~7 or 19+ mm				
36X 70600A		.	0.0011	.	(0.0017)	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm				
HRT CU2014		.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 15 mm				
BS 706A		<0.0005	.	.	0.004	.	.	0.0006	.	.	.	.	38 mm Ø x 12 mm	last of stock			
CTIF CuNi 10		.	.	.	(0.009)	.	.	.	.	.	.	.	40 mm Ø x 18 mm				
Number		As	B	Be	C	Cd	Mg	Sb	Te	Ti	Zr	Units					

NICKEL ALLOY, chart 2 of 2

#	Number	Ni	Ag	Al	Bi	Co	Cr	Cu	Fe	Mn	Nb	P	Pb	S	Si	Sn	Zn
1	IARM 84C	9.8	(0.002)	.	.	(0.006)	.	89.4	0.28	(0.04)	.	(0.06)	0.047	(0.006)	(0.004)	0.13	0.13
1	34X 79830A	9.76	0.0028	0.0012	.	(0.0012)	.	45.88	0.079	0.311	.	0.0047	2.033	(0.0005)	.	0.1158	41.80
1	BS 706C	9.7	.	(0.001)	.	(0.003)	(0.0006)	87.9	1.68	0.60	.	(0.007)	0.0033	0.0014	0.0018	(0.0070)	0.084
1	36X SP1A	8.33	0.005	0.0020	0.0039	0.057	.	84.90	0.45	0.084	(0.031)	(0.003)	0.0115	0.005	0.004	5.75	0.344
2	CURM 62.12	7.94	.	.	.	0.081	.	89.42	0.45	1.59	.	.	0.053	0.034	0.109	0.111	0.180
2	CTIF CN2	7.80	.	(0.012)	.	.	.	88.40	1.68	1.19	(0.007)	.	0.055	0.028	0.26	(0.0065)	0.515
1	IMN MN5-4	5.90	.	.	0.0018	.	.	Rem	0.083	.	.	0.026	0.024	.	.	.	.
1	IMN MN5-3	5.29	.	.	0.0012	.	.	Rem	0.062	.	.	0.016	0.016	.	.	.	.
1	36X CN21A	5.50	0.0064	1.95	.	0.0079	0.0050	92.17	0.0316	0.0391	.	0.053	0.051	.	.	0.038	0.0203
1	IMN MN5-2	4.50	.	.	0.00071	.	.	Rem	0.033	.	.	0.010	0.012	.	.	.	.
1	IMN MN5-1	3.21	.	.	0.00011	.	.	Rem	0.0041	.	.	(0.00027)	0.0062	.	.	.	.
2	HRT CU2012	2.30	.	.	.	.	.	97.0	0.013	0.002	.	.	.	.	0.63	0.035	.
1	37X 218B	1.892	.	0.0018	.	.	0.176	97.29	0.0209	0.0022	.	.	0.0014	.	0.564	0.0032	0.0054

Number	As	B	Be	C	Cd	Mg	Sb	Ti	Zr	Units
IARM 84C	.	.	.	(0.003)	.	.	(0.0012)	.	.	31 mm Ø x 2 or 18 mm
34X 79830A	0.0070	.	.	(0.0052)	.	.	0.0041	.	.	~38 mm Ø x ~15 mm
BS 706C	(0.001)	0:0.0016	N: (0.005)	(0.004)	.	(0.000003)	(0.0006)	.	(0.0000002)	38 mm Ø x ~7 or 19+ mm
36X SP1A	0.0007	.	.	.	.	.	0.0177	(0.0004)	.	40 mm Ø x 15 mm
CURM 62.12	.	.	.	.	.	0.002	.	.	.	60 mm Ø x 10 mm
CTIF CN2	.	.	.	(0.008)	.	.	.	.	.	60 mm Ø x 5 mm
IMN MN5-4	0.0038	.	.	.	.	.	0.0019	.	.	35 mm Ø x 30 mm
IMN MN5-3	0.0017	.	.	.	.	.	0.0013	.	.	35 mm Ø x 30 mm
36X CN21A	0.0067	.	.	.	0.0021	.	.	.	.	40 mm Ø x ~17 mm
IMN MN5-2	0.0011	.	.	.	.	.	0.00078	.	.	35 mm Ø x 30 mm
IMN MN5-1	0.0007	.	.	.	.	.	0.00019	.	.	35 mm Ø x 30 mm
HRT CU2012	.	.	.	.	.	.	.	.	.	40 mm Ø x 20 mm
37X 218B	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~15 mm

CRM NICKEL ALLOY SETS

analysis listed in mass %

NA: 28 mm Ø x 25 mm MN5: 35 mm Ø x 30 mm N: 35 mm Ø x 30 mm
NB: 40 mm Ø x 25 mm NC: 40 mm Ø x 12 mm

Number	Ni	Al	As	Bi	C	Cd	Co	Fe	Mg	Mn	P	Pb	S	Sb	Si	Sn	Zn	singles?
IMN NC1	23.17	.	0.0056	0.0011	0.0320	0.0142	0.0062	0.0501	0.0016	0.552	0.0147	0.0025	0.0709	0.0024	0.0854	0.0374	0.776	no
IMN NC2	24.21	0.0219	0.0104	0.0046	(0.0026)	0.0189	0.0115	0.290	0.0024	0.413	.	0.0021	0.0837	0.0049	0.196	0.0457	0.508	yes
IMN NC3	24.68	0.229	0.0167	0.0077	(0.0036)	0.0120	0.0282	0.106	0.0561	0.148	0.0312	0.0027	(0.0202)	0.0084	0.0609	0.0171	0.244	yes
IMN NC4	25.39	0.332	0.0251	0.0117	0.0500	0.0049	0.101	0.426	0.0170	0.0172	0.0113	0.0120	0.0022	0.0113	0.0197	0.0087	0.0099	yes
IMN NC5	25.82	0.0749	0.0427	0.0213	0.0050	0.0018	0.151	0.369	0.0861	0.0623	0.0222	0.0409	.	0.0161	0.0198	0.0044	0.0152	yes
IMN N1	25.38	.	.	.	.	.	0.0050	0.0056	.	0.0018	.	0.0019	.	.	0.0070	0.0089	0.019	yes
IMN N2	24.28	.	.	.	.	.	0.023	0.35	.	0.21	.	0.011	.	.	0.025	0.012	0.16	yes
IMN N3	22.57	.	.	.	.	.	0.055	0.77	.	0.50	.	0.020	.	.	0.062	0.023	0.33	yes
IMN N4	21.39	.	.	.	.	.	0.080	1.07	.	0.71	.	0.039	.	.	0.13	0.038	0.47	yes
IMN NA1	7.19	.	.	.	(0.020)	.	.	2.52	.	1.51	.	0.081	(0.081)	.	.	.	0.80	yes
IMN NA2	9.05	.	.	.	(0.023)	.	.	2.03	.	1.03	.	0.056	(0.065)	.	.	.	0.55	yes
IMN NA3	10.35	.	.	.	(0.019)	.	.	1.15	.	0.60	.	0.035	(0.036)	.	.	.	0.30	yes
IMN NA4	12.15	.	.	.	(0.012)	.	.	0.50	.	0.21	.	0.0066	(0.0069)	.	.	.	0.019	yes

CRM SEBILOY / ENVIROBRASS / FEDERALLOY

Number	Sn	Zn	Bi	Se	As	Co	Fe	Ni	P	Pb	Sb	Cu
IARM 266A	6.9	3.48	2.37	0.001	0.004	(0.001)	0.035	0.46	0.032	0.010	0.010	(87)
32X SEB5C	5.18	5.30	1.056	0.471	.	0.0156	0.0430	0.317	0.072	0.268	0.0334	87.21
IARM 226A	5.1	4.8	1.7	0.93	0.003	0.001	0.054	0.54	0.005	0.040	0.004	86.7
IARM 227A	5.1	4.70	2.3	1.21	0.003	0.001	0.060	0.53	0.003	0.042	<0.01	85.9
IARM 265A	4.4	2.45	2.4	(0.002)	(0.005)	(0.001)	0.013	0.69	0.024	0.011	0.015	(90)
IARM 228A	4.1	4.1	1.53	0.67	0.003	0.001	0.052	0.45	0.032	0.026	0.010	89.0
IARM 263A	3.5	15.8	2.55	(0.002)	0.003	0.001	0.047	0.66	0.040	0.022	0.06	(78)
IARM 264A	3.03	5.33	3.6	(0.001)	(0.004)	(0.001)	0.048	0.54	0.027	0.057	0.074	(87.3)
Number	Ag	Al	B	C	Cd	Cr	Mn	N	O	S	Si	Units
IARM 266A	(0.001)	0.002	.	(0.002)	.	(0.002)	(0.002)	.	.	(0.002)	0.002	31 mm Ø x 2 mm
32X SEB5C	.	(0.001)	.	.	0.0051	.	.	.	.	0.050	.	~40 mm Ø x ~15 mm
IARM 226A	0.004	0.002	.	0.003	.	(0.001)	0.002	<0.0005	(0.001)	0.005	0.002	31 mm Ø x 2 mm
IARM 227A	0.004	0.002	.	0.003	.	(0.001)	0.001	(0.0002)	0.0013	0.005	0.002	31 mm Ø x 2 mm
IARM 265A	(0.002)	0.003	.	.	.	(0.001)	(0.002)	.	.	(0.002)	0.003	31 mm Ø x 2 mm
IARM 228A	0.003	0.002	.	0.003	.	0.001	0.001	<0.0005	(0.002)	0.004	0.002	31 mm Ø x 2 or 18 mm
IARM 263A	(0.006)	(0.002)	.	<0.005	.	(0.002)	(0.002)	.	.	(0.002)	0.003	31 mm Ø x 2 or 18 mm
IARM 264A	(0.005)	0.003	.	(0.004)	.	(0.002)	(0.002)	.	.	0.0013	0.003	31 mm Ø x 2 or 18 mm

CRM		PHOSPHORUS ALLOY										40 mm Ø x 25 mm	
Number	P	As	Bi	Cu	Fe	Ni	Pb	Sb	Se	Sn	Te	Zn	
IMN CO2	11.60	0.0050	0.0049	Rem	0.096	0.013	0.070	0.065	(0.0045)	0.35	(0.0055)	0.15	
IMN CO5	9.45	0.0023	0.00095	Rem	0.11	0.0082	0.0044	0.034	(0.0015)	0.55	(0.0023)	0.061	
IMN CO3	8.56	0.011	0.015	Rem	0.11	0.10	0.10	0.14	(0.0073)	0.037	(0.0080)	0.24	
IMN CO4	5.54	0.016	0.0086	Rem	0.29	0.25	0.29	0.092	(0.010)	0.13	(0.012)	0.029	

RM SILVER ALLOY		31 mm Ø x 2 or 18 mm				
Number	Ag	C	P	S	Zr	
IARM 159A	3.48	(0.002)	(<0.01)	(<0.01)	.	
IARM 160A	3.03	0.003	(0.004)	(<0.003)	0.40	
Al, Co, Cr, Fe, Mn, Ni, Pb, Si, Sn, and Zn: (<0.01)						

CRM SILVER ALLOY SET

available in set only 40 mm Ø x 25 mm

Number	Ag
IMN CCA-1	0.00720
IMN CCA-2	0.0539
IMN CCA-3	0.757
IMN CCA-4	1.524
IMN CCA-5	1.964

RM		TIN COPPER										32X: 40 mm Ø x 15 mm		C: 50 mm Ø x 10-12 mm	
cast	typical analysis														
Number	Sn	Al	As	Bi	Cu	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Zn
C11.04	9.6	<0.005	<0.005	<0.0005	rem	<0.005	<0.001	<0.005	<0.005	0.05	0.01	<0.001	<0.005	<0.005	<0.005
C11.03	7.4	<0.005	<0.005	<0.0005	rem	<0.005	<0.001	<0.005	<0.005	0.04	0.01	<0.001	<0.005	<0.005	<0.005
C11.02	5.5	<0.005	<0.005	<0.0005	rem	<0.005	<0.001	<0.005	0.006	0.02	0.02	<0.001	<0.005	<0.005	<0.005
C11.01	3.4	<0.005	<0.005	<0.0005	rem	<0.005	<0.001	<0.005	0.006	0.009	0.01	<0.001	<0.005	<0.005	<0.005

CRM		TIN COPPER SET											
		available in SET/5 or individually										40 mm Ø x 30 mm	
Number		Ag	As	Bi	Cu	Fe	Ni	P	Pb	Sb	Sn	Zn	
IMN CM1		0.010	0.0098	0.010	Rem	0.019	0.0086	0.0088	0.012	0.012	0.61	0.021	
IMN CM2		0.0061	0.0068	0.0072	Rem	0.0064	0.0055	0.0058	0.0067	0.0068	0.84	0.0061	
IMN CM3		0.0029	0.0036	0.0033	Rem	0.012	0.0031	0.0041	0.0038	0.0040	1.06	0.0060	
IMN CM4		0.0011	0.0011	0.00093	Rem	0.0042	0.0011	0.0009	0.0023	0.0019	1.30	0.0020	
IMN CM5		.	(0.015)	0.014	Rem	0.0094	0.014	0.015	0.019	0.018	1.14	0.013	

CRM

BRASS SETS

wrought	IMN MG2 in SET only, all others OK individually						MB: 40 mm Ø x 18 mm			ME, MG, WR: 35-40 mm Ø x 25-30 mm				WC: 40 mm Ø x 12 mm		
Number	Cu	Zn	Al	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	P	Pb	Sb	Si	Sn
IMN MG1	91.14	Rem	0.040	.	0.00058	.	.	.	0.0081	0.0013	0.048	(0.0019)	0.049	0.00077	.	0.0062
IMN MG2	90.08	Rem	(0.0026)	.	0.00039	.	.	.	0.0067	0.0007	0.0022	0.0012	0.0048	(0.00084)	.	0.018
IMN MG3	93.19	Rem	0.020	.	0.0014	.	.	.	0.062	0.0096	0.013	0.018	0.015	0.0026	.	0.033
IMN MG4	94.00	Rem	.	.	0.0017	.	.	.	0.091	0.024	0.0042	0.012	0.008	0.0045	.	0.023
IMN MG5	95.09	Rem	0.0011	.	0.0026	.	.	.	0.149	0.0036	0.0021	0.0069	0.0054	0.0061	.	0.013
IMN MG6	92.27	Rem	0.0067	.	0.00088	.	.	.	0.028	0.045	0.030	0.0026	0.031	0.0015	.	0.053
IMN WC1	75.10	Rem	0.0034	0.0043	0.0028	.	.	.	0.031	.	.	0.015	0.046	0.0034	0.26	0.0032
IMN WC2	75.05	Rem	0.0016	0.0024	0.0020	.	.	.	0.015	.	.	0.011	0.031	0.0023	0.41	0.0025
IMN WC3	75.28	Rem	0.0018	0.0011	0.00093	.	.	.	0.021	.	.	0.0058	0.0085	0.0010	0.89	0.0011
IMN WC4	75.32	Rem	0.00096	.	0.00047	.	.	.	0.0067	.	.	0.0048	0.0051	0.00080	0.76	0.0010
IMN WC5	75.03	Rem	0.00084	0.0022	0.0019	.	.	.	0.18	.	.	.	0.0055	0.0011	0.48	0.0044
IMN WC6	75.32	Rem	0.0019	0.00097	0.0012	.	.	.	0.051	.	.	0.0037	0.0036	0.00057	0.58	0.0028
IMN ME2	71.29	Rem	.	.	.	.	.	.	.	.	.	.	.	.	.	0.87
IMN ME3	70.70	Rem	.	.	.	.	.	.	.	.	.	.	.	.	.	1.11
IMN ME4	69.40	Rem	.	.	.	.	.	.	.	.	.	.	.	.	.	1.21
IMN ME5	68.53	Rem	.	.	.	.	.	.	.	.	.	.	.	.	.	1.42
IMN MB2	67.17	32.80	.	.	.	.	.	.	.	.	.	.	.	.	.	.
IMN MB3	73.26	26.67	.	.	.	.	.	.	.	.	.	.	.	.	.	.
IMN MB6	90.07	9.95	.	.	.	.	.	.	.	.	.	.	.	.	.	.
IMN MB7	95.00	4.99	.	.	.	.	.	.	.	.	.	.	.	.	.	.
IMN WR1	55.72	Rem	0.496	0.203	0.00109	0.00045	0.00196	0.00049	0.0577	1.051	3.534	0.00122	0.0496	0.00046	1.097	0.605
IMN WR2	56.99	Rem	1.092	0.0129	0.00642	0.00548	0.00210	0.00705	0.802	1.631	2.683	0.0311	0.291	0.00566	0.817	0.453
IMN WR3	58.95	Rem	1.683	0.0492	0.0118	0.00807	0.0106	0.0149	0.184	1.674	1.799	0.0126	0.514	0.0150	0.566	0.254
IMN WR4	60.07	Rem	2.297	0.00528	0.0211	0.0154	0.0154	0.0190	0.600	2.254	0.989	0.0213	0.683	0.0247	0.279	0.100
IMN WR5	61.20	Rem	3.024	0.00129	0.0278	0.0200	0.0196	0.0253	0.141	3.070	0.251	0.0282	0.885	0.0334	0.0485	0.0116
Number	Cu	Zn	Al	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	P	Pb	Sb	Si	Sn

RM

TRACE ELEMENTS IN BRASS

cast 50 mm Ø x 10 - 12 mm

Number	Cu	Zn	Al	As	Bi	Fe	Mn	Ni	Pb	Sb	Si	Sn	
C30.10	93.8	6.1	<0.002	<0.005	<0.002	<0.005	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01	
C30.07	82.0	rem	<0.002	<0.005	<0.002	<0.005	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01	
C30.06	74.8	rem	<0.005	<0.005	<0.002	<0.005	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01	
CURM 30.05	69.48	30.53	<0.001	<0.001	<0.003	<0.003	<0.0005	<0.0005	<0.002	<0.005	<0.001	<0.001	
C38.06	(62)	rem	<0.001	<0.005	<0.001	<0.002	<0.002	<0.005	<0.005	<0.002	<0.002	<0.002	last of stock
C38.06-1	(62)	rem	<0.001	<0.001	<0.0005	<0.005	<0.001	<0.005	0.002	<0.002	<0.002	<0.002	current batch
C30.17	61.6	rem	<0.005	<0.005	<0.005	1.4	<0.005	0.01	0.01	<0.005	<0.005	<0.01	
C30.16	61.2	rem	<0.002	<0.005	<0.002	0.90	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01	
C38.01	(61)	rem	0.003	0.03	<0.0005	0.01	0.009	0.01	0.20	0.02	<0.0005	0.20	
C38.02	(61)	rem	0.004	0.06	0.005	0.09	0.14	0.03	0.10	0.06	0.01	0.09	
C38.03	(61)	rem	0.06	0.08	0.008	0.05	0.07	0.13	0.06	0.08	0.07	0.05	
C38.04	(61)	rem	0.02	0.04	0.008	0.04	0.22	0.06	0.03	0.12	0.12	0.02	
C38.05	(61)	rem	0.12	0.01	0.01	0.008	0.02	0.19	0.02	0.01	0.14	0.01	
C30.12	60.85	rem	<0.005	<0.005	<0.002	<0.005	0.90	0.52	<0.01	<0.005	<0.005	<0.01	
C30.03	60.6	39.3	<0.002	<0.005	<0.005	<0.005	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01	
C30.13	60.6	rem	<0.002	<0.005	<0.002	<0.005	1.9	<0.01	<0.01	<0.005	<0.005	<0.01	
C30.15	60.6	rem	<0.002	<0.005	<0.002	0.55	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01	
C30.14	60.5	rem	<0.005	<0.005	<0.005	<0.01	2.4	1.0	<0.01	<0.005	<0.005	<0.005	
C30.22	58.28	rem	<0.003	0.011	<0.005	0.006	<0.005	<0.01	1.05	<0.012	<0.005	0.009	
C30.02	55.6	rem	<0.002	<0.005	<0.005	<0.005	<0.005	<0.005	<0.01	<0.005	<0.005	<0.01	
C30.01	51.48	rem	<0.002	<0.005	0.005	<0.005	<0.005	<0.005	<0.01	<0.005	<0.005	<0.01	

RM

BRASS MUSHROOMS

chill cast	typical analysis										60 mm Ø x 5 mm					
Number	Zn	Cu	Al	As	Be	Fe	Ni	Mg	Mn	P	Pb	Sb	Si	Sn		
CTIF L 7	42.45	55.6	0.308	.	.	0.031	0.020	.	0.62	.	0.71	.	0.13	0.038		
CTIF L 1-1	39.7	59.60	0.015	.	.	0.017	0.106	.	.	0.080	0.062	.	0.36	0.046		
CTIF L 2	35.55	61.55	0.485	.	.	0.216	0.71	.	0.350	.	0.408	.	0.202	0.48		
CTIF L 3-1	35.50	(58.60)	1.22	0.073	.	0.357	0.993	.	0.214	0.030	1.32	(0.032)	0.025	1.62		
CTIF L 4-1	34.55	61.75	0.100	.	.	0.466	0.227	.	0.109	.	2.017	.	0.12	0.693		
CTIF L 6	30.26	66.55	0.139	.	.	0.085	1.21	.	0.055	.	0.205	.	1.25	0.250		
CTIF L 23	17.90	81.20	.	0.051	.	0.246	0.033	.	.	0.05	0.058	.	0.280	0.20		
CTIF UZ 52	16.90	81.18	.	.	0.014	0.32	0.084	0.04	0.002	0.068	0.11	0.08	0.12	1.06		
CTIF UZ 53	16.67	82.60	.	0.01	.	0.255	0.025	.	<0.001	0.055	0.025	.	0.145	0.205		
CTIF L 21	15.40	82.50	.	0.103	.	0.086	0.156	.	0.004	0.05	0.209	0.10	0.036	1.5		
CTIF L 22	15.0	84.3	<0.02	<0.006	.	0.20	0.10	.	<0.01	.	0.10	.	<0.05	1.0		
CTIF L 20	13.10	85.55	0.008	0.122	.	0.115	0.205	.	0.043	.	0.27	.	0.035	0.56		

BRASS

= class, where 1 = CRM and 2 = RM

CURM: cast 50 mm Ø x 10-12 mm
SRM: wrought 31 mm Ø x 19 mm

PB: 45 mm Ø x 25 mm
others: chill cast ~38-43 mm Ø x ~15-18 mm

#	Number	Zn	Cu	Al	As	Bi	Fe	Mn	Ni	Pb	Sb	Si	Sn
1	31X B25C	42.2	55.6	0.48	0.027	0.061	0.014	0.128	0.255	0.272	0.075	0.235	0.62
1	31X B2N	39.1	60.2	0.161	0.0154	0.0150	0.122	0.0361	0.102	0.053	0.0121	.	0.0129
2	CURM 30.15	38.88	60.66	<0.001	.	.	0.50	<0.001	<0.001	<0.005	.	<0.005	<0.002
2	CURM 30.16	38.33	60.53	<0.001	.	.	1.14	<0.001	<0.001	<0.005	.	<0.005	<0.002
2	CURM 30.11	38.17	59.86	<0.001	.	.	0.002	0.23	1.70	0.005	.	<0.001	<0.002
1	IARM 75C	38.1	60.7	(0.003)	(0.005)	(0.0012)	(0.06)	(0.0024)	(0.013)	0.42	(0.007)	(0.005)	0.69
2	SRM 1107	37.3	61.2	.	.	.	0.037	.	0.098	0.18	.	.	1.04
1	31X TB3L	37.0	62.42	0.044	0.047	0.0085	0.040	0.034	0.031	0.118	0.053	0.020	0.133
1	31X TB1L	36.8	61.5	0.174	0.052	0.049	0.072	0.287	0.199	0.325	0.101	0.097	0.214
1	31X B10N	36.6	60.9	0.149	0.0099	0.021	0.135	0.160	1.56	0.022	0.0207	0.012	0.047
1	31X TB4G	33.64	66.07	0.0041	0.0106	0.0058	0.0340	0.0013	0.0133	0.0246	0.0095	0.0203	0.0197
1	31X B5L	23.98	75.38	0.0138	0.0357	0.0088	0.038	(0.002)	0.0275	0.084	0.016	(0.005)	0.266
1	31X B22G	17.8	80.5	0.100	0.150	0.148	0.107	0.00076	0.142	0.197	0.147	0.152	0.225
1	SRM 1110	15.2	84.5	.	.	.	0.033	.	0.053	0.033	.	.	0.051
1	SRM 1111	12.8	87.1	.	.	.	0.010	.	0.022	0.013	.	.	0.019
1	31X B9M	4.92	94.81	(0.0006)	0.0103	0.0059	0.0361	0.0006	0.0379	0.090	0.0089	.	0.062
2	PB MS10	.	84.26	.	0.014	0.37	0.28	0.016	0.025	0.020	(0.009)	0.12	0.052
1	BAM M396	.	65.49	0.223	0.0590	0.00032	0.0235	0.00445	0.0143	.	0.00061	.	.
1	IMN MF6	.	63.36	0.014	.	0.00025	0.010	0.051	0.038	0.0023	0.00084	0.30	0.010
#	Number	Zn	Cu	Al	As	Bi	Fe	Mn	Ni	Pb	Sb	Si	Sn

Number	Ag	B	C	Cd	Co	Cr	P	S	Se	Te
31X B25C	0.0025	.	.	0.00019	.	(0.0002)	0.116	.	.	.
31X B2N	0.0118	0.0029	.	0.0032	0.042	.	0.0191	.	.	0.0015
CURM 30.15	.	.	.	.	.	.	.	.	.	.
CURM 30.16	.	.	.	.	.	.	.	.	.	.
CURM 30.11	.	.	.	.	.	.	.	.	.	.
IARM 75C	.	<0.1	(0.002)	(0.0015)	(0.0007)	0.0009	(0.004)	(0.0015)	(0.005)	.
SRM 1107	.	.	.	.	.	.	.	.	.	.
31X TB3L	0.011	0.0014	.	0.0078	0.0043	.	.	.	.	0.0025
31X TB1L	0.061	0.0005	.	0.0122	0.0017	0.0024	0.0080	(0.002)	(0.0008)	(0.004)
31X B10N	0.0030	.	.	0.0005	0.0062	0.0006	0.033	.	(0.0009)	.
31X TB4G	.	(0.0004)	.	0.0032	0.0067	.	.	.	.	0.0035
31X B5L	.	(0.0009)	.	0.0040	0.0250	.	.	.	.	.
31X B22G	0.0015	0.0029	.	0.0130	0.059	(0.0006)	0.214	.	(0.0007)	.
SRM 1110	.	.	.	.	.	.	.	.	.	.
SRM 1111	.	.	.	.	.	.	.	.	.	.
31X B9M	0.0065	(0.0005)	.	.	.	.	0.0047	.	0.0019	0.0181
PB MS10	.	.	.	.	.	.	.	.	last	.
BAM M396	.	.	.	0.00022	0.00012	0.00079	0.00089	.	<0.001	.
IMN MF6	.	.	.	.	.	.	0.0012	.	.	.
38 mm Ø x 30 mm										
40 mm Ø x ~30 mm										
Number	Ag	B	C	Cd	Co	Cr	P	S	Se	Te

ALUMINUM BRASS

= class, where 1 = CRM and 2 = RM

#	Number	Al	Zn	Cu	As	Bi	Fe	Mn	Ni	Pb	Sb	Si	Sn	Other	Units
2	CTIF LH1-1	7.99	16.90	64.90	.	.	4.48	5.18	0.0944	0.022	0.081	0.205	(0.007)	P: 0.079	60 mm Ø x 5 mm
2	CTIF LH 2	6.20	21.95	61.98	.	.	2.98	3.65	3.00	0.080	.	0.086	0.055		60 mm Ø x 5 mm
2	CTIF LH 6-1	6.09	18.98	63.18	.	.	(3.1)	4.54	3.19	0.25	.	0.20	0.257		60 mm Ø x 5 mm
1	BAM 388	4.972	4.81	89.27	.	.	0.0303	0.0512	0.00736	0.000969	.	.	0.857		40 mm Ø x 30 mm
2	C30.19	4.65	rem	69.9	<0.005	<0.002	<0.005	<0.005	<0.01	<0.01	<0.01	<0.005	1.07		50 mm Ø x 10-12 mm
1	31X B14G	4.02	36.52	58.85	0.0091	0.0103	0.0183	0.0117	0.0190	0.0104	0.0139	0.051	0.486	Ag:0.0130 Co:0.0109	~40mmØ x ~15mm
2	CTIF LH 5-1	3.65	25.72	66.0	.	.	1.26	1.37	1.57	0.110	.	0.114	0.141		60 mm Ø x 5 mm
2	CURM 30.18	3.28	32.33	63.66	.	.	0.006	<0.001	<0.001	<0.005	.	0.131	0.58		50 mm Ø x 10-12 mm
2	CTIF LH 7	3.16	(26.85)	63.40	.	.	(2.35)	2.96	0.70	0.327	.	0.055	0.227		60 mm Ø x 5 mm
1	31X B15H	2.98	36.80	59.07	0.0048	0.0074	0.0176	0.0122	0.0102	0.0073	0.0111	0.109	0.944	Ag:0.0071 Co:0.0046	~40mmØ x ~15mm
2	C30.18	2.91	rem	64.36	<0.005	<0.003	<0.005	<0.005	<0.005	<0.01	<0.005	0.10	0.65		50 mm Ø x 10-12 mm
2	CURM 43.01	2.75	22.44	74.36	0.118	<0.002	0.008	0.064	0.121	<0.002	<0.001	0.063	0.116		50 mm Ø x 10-12 mm
2	CTIF LH 10	2.66	28.90	59.05	.	.	(1.0)	3.57	1.49	1.76	.	1.30	0.203		60 mm Ø x 5 mm
2	CURM 43.02	2.40	20.82	76.21	0.083	<0.001	0.128	0.035	0.068	0.064	<0.001	0.038	0.060		50 mm Ø x 10-12 mm
2	CURM 30.20	2.32	35.71	61.46	.	.	<0.005	<0.001	<0.001	<0.002	.	0.17	0.40		50 mm Ø x 10-12 mm
2	CTIF LH 13	2.00	31.8	55.75	.	.	(2.00)	3.14	3.22	0.67	.	0.21	1.19		60 mm Ø x 5 mm
1	31X B16H	1.98	37.18	58.37	0.0056	0.0042	0.0162	0.0029	0.0076	0.0295	0.0126	0.197	2.13	Ag:0.0052 Co:0.0023	~40mmØ x ~15mm
2	C43.03	1.6	rem	79.7	<0.005	<0.005	0.07	<0.002	<0.005	0.10	<0.01	<0.005	<0.005		50 mm Ø x 10-12 mm
1	BAM 368 *	1.972	rem	77.049	0.0246	.	0.0193	0.0203	0.0258	0.01313	(0.002)	.	0.0147	P: 0.00899	50 mm Ø x 5 mm
2	C30.21	1.44	rem	56.0	<0.005	.	<0.005	<0.005	<0.005	<0.005	<0.01	0.18	1.96		50 mm Ø x 10-12 mm
2	CURM 30.21	1.44	40.08	56.23	.	.	0.003	<0.001	<0.001	0.004	.	0.213	2.01		50 mm Ø x 10-12 mm
2	CTIF LH 12	1.13	33.15	62.75	.	.	(1.2)	0.125	0.505	0.21	.	(0.06)	0.83		60 mm Ø x 5 mm
2	CTIF LH 11	0.46	26.20	66.80	.	.	0.36	0.71	2.91	1.26	.	0.88	0.44		60 mm Ø x 5 mm

* BAM 368 also contains 62.1 ppm Mg

CRM ALUMINUM BRASS SET

IMN W02 available in SET/4 only, others individually

40 mm Ø x 35 mm

Number	Al	As	Bi	Cd	Cr	Cu	Fe	Mg	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN W01	1.33	0.056	0.0003	0.013	0.013	78.85	0.13	0.00060	0.014	0.0043	0.0023	0.15	0.0083	0.044	0.011	Rem
IMN W02	1.76	0.041	0.0014	0.032	0.0098	77.80	0.050	0.0066	0.16	0.031	0.0090	0.098	0.00098	0.013	0.056	Rem
IMN W03	2.15	0.015	0.0047	0.039	0.0027	77.58	0.029	0.0055	0.051	0.11	0.0062	0.054	0.0035	0.007	0.0071	Rem
IMN W04	2.50	0.030	0.0098	0.0063	0.00034	76.20	0.022	0.013	0.074	0.077	0.015	0.020	0.0058	0.001	0.13	Rem

CRM BISMUTH BRASS

analysis listed in mass % except * which is mg/kg

~38-40 mm Ø x ~15 mm

Number	Bi	Zn	Cu	Ag*	Al	As	B*	Cd*	Co	Cr*	Fe	Mn	Ni	P	Pb	S*	Sb	Se*	Si	Sn
31X B1B1E	1.96	34.0	62.7	14	0.213	0.0290	.	91	0.0057	.	0.074	0.0266	0.301	0.062	0.090	(30)	0.012	(10)	0.065	0.376
31X B1B2-21	1.11	37.1	58.7	.	0.81	0.025	.	62	0.026	.	0.122	0.0258	0.58	0.035	0.131	.	0.083	.	0.18	1.31
31X B1B4D	0.80	34.8	62.9	14	0.435	0.0095	19	22	0.0108	6	0.094	0.00082	0.211	0.039	0.096	(50)	0.022	11	0.060	0.58

RM CARTRIDGE BRASS

cast typical analysis listed in mass %

31X: ~40 mm Ø x ~15 mm

others: 50 mm Ø x 10 - 12 mm

Number	Zn	Cu	Al	As	Bi	Cd	Cr	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Sn
CURM 48.01	32.6	66.98	<0.001	0.067	0.038	<0.0003	*	0.049	0.0008	<0.001	0.134	0.016	0.106	<0.001	0.047	0.041	<0.002
CURM 48.02	32.58	67.16	0.013	0.025	0.004	*	0.004	0.053	*	0.067	<0.001	0.012	0.084	0.007	0.037	0.010	0.035
CURM 48.05	31.0	68.69	<0.002	<0.001	*	<0.0003	*	0.066	*	0.016	0.117	0.007	<0.003	0.013	*	0.026	0.083
31X B4N	30.22	69.3	Cr:0.0013	0.059	0.0139	0.032	0.0083	0.043	.	0.032	0.019	0.0083	0.080	(0.002)	0.006	0.030	0.046
C48.03	rem	70.45	0.007	0.079	0.029	0.013	0.0005	<0.001	0.001	0.040	0.030	<0.001	0.054	0.004	0.097	<0.002	0.047
C48.06	rem	71.6	0.002	0.008	0.004	0.008	0.0006	0.02	0.001	0.006	0.11	0.002	0.02	0.006	0.006	0.006	0.03
CURM 48.04	26.99	72.68	<0.001	0.034	0.014	<0.0003	<0.002	0.008	0.0005	0.012	0.096	0.006	0.043	0.011	0.026	0.004	0.018

* For the above chart, * indicates a value of <0.0005

CRM CARTRIDGE BRASS

available in SET/5 or individually remainder is Zinc

wrought 40 mm Ø x 25 mm

Number	Ag	Al	As	Be	Bi	Cd	Cu	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Te
IMN MH1	0.0029	0.0010	0.0670	0.0088	0.0037	0.0260	65.93	0.0170	0.0350	0.2600	0.0160	0.0065	0.0034	0.0004	0.0740	0.1400	0.0004
IMN MH2	0.0110	0.0190	0.0410	0.0015	0.0022	0.0180	68.25	0.0270	0.0110	0.2200	0.0055	0.0210	0.0055	0.0240	0.0540	0.0970	0.0015
IMN MH3	0.0065	0.0081	0.0160	0.0003	0.0011	0.0089	71.28	0.0810	0.0850	0.1000	0.0035	0.0780	0.0090	0.0130	0.0310	0.0240	0.0046
IMN MH4	.	0.0027	0.0011	0.0045	0.0006	0.0029	69.94	0.1300	0.0017	0.0520	0.0022	0.3300	0.0043	0.0170	0.0160	0.0110	0.0035
IMN MH5	0.0250	0.0140	0.0038	0.00004	.	0.0012	72.87	0.1900	0.0720	0.0072	0.0011	0.2000	0.0180	0.0035	0.0039	0.0021	0.0047

CRM CARTRIDGE BRASS SETS

Number	Cd	Cr	Cu	Se	Zn	Zr	Units						
IMN MJ1	0.00355	0.0120	67.77	0.00062	Rem	.	available	individually	40 mm	Ø x ~28 mm			
IMN MJ2	0.00377	0.00440	66.40	0.00037	Rem	.	available	individually	40 mm	Ø x ~28 mm			
IMN MJ3	0.00165	0.00158	67.39	0.00035	Rem	.	available	individually	40 mm	Ø x ~28 mm			
IMN MJ4	0.00130	0.00374	68.06	0.0124	Rem	.	available	individually	40 mm	Ø x ~28 mm			
IMN MJ5	0.000360	0.00065	(67.82)	0.00288	Rem	.	available	individually	40 mm	Ø x ~28 mm			
IMN MJJ1	.	.	67.82	.	Rem	0.0454	available	individually	40 mm	Ø x ~28 mm			
IMN MJJ2	.	.	(68.03)	.	Rem	0.00017	available	individually	40 mm	Ø x ~28 mm			
IMN MJJ3	.	.	67.87	.	Rem	0.00070	available	individually	40 mm	Ø x ~28 mm			
IMN MJJ4	.	.	67.75	.	Rem	0.0074	available	individually	40 mm	Ø x ~28 mm			

CRM FREE CUTTING BRASS SET

40 mm Ø x 25 mm

Number	Al	As	Bi	Cu	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn		
IMN WN1	0.33	0.035	0.023	58.44	0.23	0.57	0.29	0.031	0.51	0.099	0.16	1.00	Rem	available	individually
IMN WN2	0.24	0.011	0.035	60.38	0.29	0.73	0.19	0.051	1.58	0.10	0.22	0.68	Rem	available	in SET/5 only
IMN WN3	0.14	0.032	0.020	62.32	0.062	0.39	0.098	0.034	2.62	0.020	0.12	0.39	Rem	available	in SET/5 only
IMN WN4	0.047	0.021	0.0094	57.97	0.11	0.13	0.050	0.014	0.86	0.061	0.036	0.13	Rem	available	individually
IMN WN5	(0.0004)	0.030	0.0028	64.36	0.0085	0.0020	0.0049	0.0051	3.78	0.0035	(0.0013)	0.019	Rem	available	individually

LEADED BRASS

= class, where 1 = CRM and 2 = RM

#	Number	Pb	Sn	Zn	Cu	Al	As	Bi	Co	Fe	Mn	Ni	P	Sb	Si		
1	IARM Cu844-18	6.7	3.08	9.5	80.5	0.0010	0.0041	0.030	0.0015	0.030	.	0.209	0.0018	0.037	(0.001)		
1	IMN BR1	5.03	4.9	5.07	Rem	0.0074	0.0102	.	.	0.085	0.080	0.48	0.009	0.090	(0.0077)		
1	IARM Cu836-18	4.9	5.02	5.09	84.5	.	0.0098	0.035	0.0026	0.049	.	0.423	0.028	0.103	(0.003)		
1	IMN WD-1	3.74	0.026	Rem	58.45	0.0043	0.0033	0.054	.	0.011	0.17	0.010	0.0022	0.0042	0.0048		
1	SRM 1124	3.363	0.3112	35.19	(62.5)	.	.	(0.0202)	(0.0014)	0.2068	(0.0009)	0.0801	(0.0224)	0.02325	.		
1	IMN WD-2	3.18	0.077	Rem	58.58	0.0081	0.041	0.036	.	0.047	0.22	0.049	0.0070	0.038	0.011		
2	CURM H30.24	3.02	<0.001	37.92	58.87	<0.001	<0.001	<0.001	.	0.005	<0.001	<0.001	.	<0.001	<0.001		
1	33X RB2B	2.99	4.65	9.01	82.02	0.0078	0.0395	0.091	0.0326	0.503	0.0076	0.330	0.0435	0.0494	(0.0017)		
1	BS 360C	2.86	0.104	35.3	61.5	(0.026)	(0.016)	.	(0.0003)	0.096	0.0025	0.020	(0.007)	0.0043	0.0026		
1	BS 360B	2.77	0.15	35.7	(61.2)	(<0.001)	0.002	.	(<0.002)	0.117	0.0094	0.040	(<0.002)	0.017	0.002		
1	IARM Cu360-18	2.73	0.29	35.1	61.6	(0.010)	0.026	(0.0023)	0.0010	0.27	0.0131	0.0120	(0.003)	0.012	(0.010)		
1	IMN WD-3	2.69	0.29	Rem	60.16	0.048	0.022	0.020	.	0.12	0.18	0.10	0.012	0.023	0.033		
1	BS 360D	2.68	0.153	35.0	61.8	(0.0003)	(0.040)	.	(0.0004)	0.155	0.0011	0.029	(0.002)	(0.007)	(0.001)		
1	31X B19S	2.36	0.0556	37.3	59.7	0.015	0.0214	0.019	0.0007	0.357	0.0194	0.0249	0.016	0.036	0.015		
1	31X 7835-2L	2.07	0.206	33.4	63.7	0.136	0.069	0.013	0.0036	0.25	.	0.051	(0.08)	0.073	0.023		
1	31X CZ132A	2.05	0.160	39.90	57.63	0.0007	0.0119	.	0.0009	0.165	.	0.0510	.	0.0054	(0.004)		
1	IMN WD-7	2.03	0.31	Rem	60.53	0.16	0.019	0.014	.	0.10	0.30	0.17	0.019	0.020	0.17		
2	HRT CU2015	2.00	0.19	.	57.57	.	.	.	.	0.14	.	0.04	0.004	.	.		
1	31X CZ122A	1.97	0.0866	36.21	61.51	.	0.150	.	.	0.066	0.00097	0.0261	.	0.0088	(0.001)		
1	BAM M394	1.93	0.232	.	57.70	(0.00010)	0.01001	0.00081	.	0.1191	0.00141	0.0399	0.00157	0.00238	(0.00053)		
1	BAM M394a	1.92	0.174	.	57.64	(0.00079)	0.00959	0.00083	.	0.1323	0.00125	0.0386	0.00172	0.00241	(0.00058)		
1	IMN WD-4	1.88	0.53	Rem	60.62	0.10	0.011	0.013	.	0.22	0.027	0.21	0.012	0.025	0.022		
1	31X 7835-3K	1.70	0.355	36.64	59.9	0.488	0.059	0.0298	0.0069	0.484	0.048	0.146	0.033	0.060	(0.077)		
1	IMN WD-5	1.31	0.77	Rem	61.84	0.18	0.0066	0.0085	.	0.34	0.0054	0.31	0.039	0.0071	0.099		
1	31X 7835-6D	1.31	0.70	37.2	59.9	0.527	0.0069	0.0047	0.0059	0.118	.	0.061	0.038	.	0.004		
2	BS 857B-1	1.22	1.14	34.91	61.3	0.35	(0.001)	.	.	0.30	0.003	0.61	0.004	(0.002)	0.004		
2	BS 857B-2	1.21	1.13	34.91	[62.4]	0.364	0.0004	.	.	0.30	0.003	0.61	0.003	.	0.003		
2	BS 857B-3	1.21	1.13	34.91	[62.4]	0.351	0.0003	.	.	0.30	0.003	0.61	0.003	.	0.004		
2	BS 857B-4	1.20	1.13	34.91	[62.4]	0.339	0.0004	.	.	0.30	0.003	0.61	0.003	.	0.005		
1	31X CZ115A	1.169	0.729	39.20	57.19	0.0007	0.0008	.	.	0.601	1.095	0.0143	0.0091	0.0020	(<0.005)		
1	31X 7835-4K	0.98	0.200	38.0	59.9	0.153	0.058	0.018	0.0058	0.239	0.0262	0.099	0.156	0.0284	.		
1	IMN WD-6	0.82	1.00	Rem	62.42	0.30	0.056	0.0019	.	0.58	0.47	0.0087	0.052	0.050	0.060		
1	31X CZ112A	0.458	1.130	37.07	61.24	(0.0006)	0.0052	.	.	0.0488	0.0010	0.0150	0.0136	0.0043	(0.0033)		

Number	Ag	B	Be	C	Cd	Cr	Mg	O	S	Se	Te	Units	
IARM Cu844-18	0.0133	.	.	.	(0.0008)	.	.	.	0.023	0.0040	.	~38 mm	Ø x ~3 or ~19 mm
IMN BR1	.	.	.	.	.	.	.	.	0.014	.	.	40 mm	Ø x ~25 mm
IARM Cu836-18	0.0292	.	.	.	0.0014	.	.	.	0.041	0.0016	.	~38 mm	Ø x ~3 or ~19 mm
IMN WD-1	.	.	.	.	.	.	.	.	.	.	.	40 mm	Ø x 30 mm
SRM 1124	0.0131	.	.	.	0.00651	0.0155	.	.	(0.0031)	.	.	cont. cast	39 mm Ø x 19 mm
IMN WD-2	.	.	.	.	.	.	.	.	.	.	.	40 mm	Ø x 30 mm
CURM H30.24	.	.	.	.	.	.	.	(0.2)	.	.	.	50 mm	Ø x 10 - 12 mm
33X RB2B	0.105	.	.	.	.	(0.0013)	.	.	0.069	.	0.0078	chill cast	~42 mm Ø x ~17 mm
BS 360C	0.0040	.	(0.0002)	0.0014	.	(0.0008)	.	(0.0007)	(0.0008)	.	N:(0.0002)	38 mm	Ø x ~7 or 19+ mm 17025, 17034
BS 360B	0.006	.	(<0.001)	(<0.002)	.	(0.0001)	.	0.0007	(<0.0005)	last	(<0.002)	38 mm	Ø x 19 mm 17025
IARM Cu360-18	0.011	.	.	(0.003)	0.0034	(0.003)	.	.	.	.	.	31 mm	Ø x 2 or 18 mm
IMN WD-3	.	.	.	.	.	.	.	.	.	.	.	40 mm	Ø x 30 mm
BS 360D	0.0059	.	(0.0003)	0.0013	.	(0.0005)	.	(0.0009)	(0.0008)	.	.	38 mm	Ø x ~7 or 19+ mm 17025, 17034
31X B19S	0.0041	.	.	.	0.0110	0.0012	.	.	(0.003)	0.0010	0.0012	~38 mm	Ø x ~15 mm
31X 7835-2L	0.015	0.0012	.	.	0.0040	.	.	.	.	.	.	chill cast	~40 mm Ø x ~15 mm
31X CZ132A	0.0050	.	.	.	0.0012	.	.	.	0.0008	.	.	wrought	~40 mm Ø x ~15 mm
IMN WD-7	.	.	.	.	.	.	.	.	.	.	.	40 mm	Ø x 30 mm
HRT CU2015	.	.	.	.	.	.	.	.	.	.	.	40 mm	Ø x 20 mm
31X CZ122A	0.0030	(0.0004)	.	.	0.0011	.	.	.	0.0009	.	.	wrought	~40 mm Ø x ~15 mm
BAM M394	.	.	.	.	0.00070	.	.	.	.	.	.	40 mm	Ø x 30 mm
BAM M394a	.	.	.	.	0.00073	0.00013	.	.	.	.	.	40 mm	Ø x 30 mm
IMN WD-4	.	.	.	.	.	.	.	.	.	.	.	40 mm	Ø x 30 mm
31X 7835-3K	0.0205	.	.	.	0.0060	0.0107	.	.	.	.	0.0011	chill cast	~40 mm Ø x ~15 mm
IMN WD-5	.	.	.	.	.	.	.	.	.	.	.	40 mm	Ø x 30 mm
31X 7835-6D	0.0048	0.0032	.	.	0.0017	.	.	.	(0.001)	(0.001)	0.0007	chill cast	~40 mm Ø x ~15 mm
BS 857B-1	(0.002)	.	.	.	.	.	.	.	.	.	last	cont. cast	38 mm Ø x 10 or 19 mm
BS 857B-2	(0.002)	.	.	(0.003)	.	.	.	.	(0.001)	.	(0.004)	cont. cast	38 mm Ø x 12 mm
BS 857B-3	(0.002)	.	.	(0.003)	.	.	.	.	(0.001)	.	(0.004)	cont. cast	38 mm Ø x 12 mm
BS 857B-4	(0.002)	.	.	(0.003)	.	.	.	.	(0.001)	.	(0.004)	cont. cast	38 mm Ø x 12 mm
31X CZ115A	0.0041	.	.	.	.	0.0005	.	.	.	.	.	wrought	~41 mm Ø x ~15 mm
31X 7835-4K	.	0.0020	.	.	0.0092	0.0051	.	.	.	.	.	chill cast	~40 mm Ø x ~15 mm
IMN WD-6	.	.	.	.	.	.	.	.	.	.	.	40 mm	Ø x 30 mm
31X CZ112A	0.0043	.	.	.	.	.	.	.	.	.	.	wrought	~41 mm Ø x ~15 mm

CRM LEADED BRASS SET

40 mm Ø x 30 mm

Number	Al	Bi	Cu	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn	
IMN WG1	0.096	0.0013	60.99	0.0084	0.16	0.20	0.029	0.71	(0.062)	(0.0046)	0.29	Rem	available individually
IMN WG2	(0.00095)	0.016	56.99	0.42	(0.0024)	0.0051	.	2.66	(0.0024)	(0.021)	(0.0025)	Rem	available individually
IMN WG3	0.041	0.0057	58.20	0.31	0.037	0.029	0.013	2.29	0.018	(0.014)	0.091	Rem	available in set only
IMN WG4	0.073	0.014	60.05	0.10	0.12	0.16	0.020	1.41	(0.042)	(0.016)	0.21	Rem	# 4 sold out
IMN WG5	0.058	0.0094	59.32	0.18	0.074	0.078	0.016	1.66	0.034	(0.022)	0.14	Rem	available in set only
IMN WG6	0.020	0.023	60.67	0.18	0.21	0.29	0.044	3.70	(0.0078)	(0.019)	0.40	Rem	available individually

CRM MANGANESE BRASS

chill cast

analysis listed in mass % except * which is mg/kg

31X: ~40 mm Ø x ~15-18 mm

CTIF: 2 Discs 60 mm Ø x 5 mm

Number	Mn	Zn	Cu	Al	Fe	Ni	Pb	Si	Sn	As	Co	P	Sb	Ag*	Bi*	Cd*	Cr*
31X MNB12C *	16.1	21.2	58.3	0.70	0.29	0.696	1.97	0.046	0.171	0.0100	0.012	0.078	0.0101	21	101	22	26
31X B13G	2.84	36.67	60.03	0.0148	0.182	0.212	0.0188	0.032	0.0127	0.0120	.	.	0.0056	.	116	.	.
31X MNB3F	2.11	25.57	66.41	1.41	1.25	0.377	0.509	1.642	0.423	0.044	0.036	0.056	0.044	99	.	97	360
31X B12G	1.720	36.66	60.51	0.081	0.430	0.491	0.0244	0.0207	0.0229	0.0181	.	.	0.0194	.	198	.	.
31X MNB6C	0.871	28.51	70.01	0.0148	0.0697	0.261	0.016	0.0196	0.0308	0.0107	0.0107	0.0226	0.0128	509	.	.	.

* 31X MNB12Ca lso contains C:0.009

CRM MANGANESE BRASS DISC AND ROD SETS

Number	Al	As	Bi	Cu	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn	availability	Units
IMN MA1	1.51	0.085	0.0020	55.50	0.073	3.37	0.39	0.10	0.16	0.0061	0.071	1.04	Rem	set only	10 mm Ø x 100 mm
IMN MA2	3.35	0.0081	0.0029	60.88	1.27	1.30	0.011	0.015	0.020	0.0019	0.042	0.41	Rem	set only	10 mm Ø x 100 mm
IMN MA3	.	0.029	0.028	57.04	0.55	0.78	0.13	0.040	0.049	0.14	0.50	0.74	Rem	set only	10 mm Ø x 100 mm
IMN MA4	0.33	.	.	57.40	0.20	2.75	0.69	0.15	.	0.20	0.27	0.015	Rem	set only	10 mm Ø x 100 mm
IMN MA5	1.04	0.11	0.020	58.51	0.70	1.97	1.01	0.062	1.20	0.072	0.65	0.046	Rem	set only	10 mm Ø x 100 mm
IMN MA6	2.15	0.013	0.0072	60.45	1.72	0.50	0.056	0.019	0.60	0.016	0.013	0.13	Rem	set only	10 mm Ø x 100 mm
IMN WF1	.	.	0.00059	56.47	0.097	2.16	0.010	(0.0012)	0.010	0.00058	.	0.012	Rem	OK individually	44 mm Ø x 30 mm
IMN WF2	.	.	0.00091	57.66	0.21	1.79	0.040	(0.0032)	0.040	0.0018	.	0.045	Rem	OK individually	44 mm Ø x 30 mm
IMN WF3	.	.	0.0015	58.66	0.29	1.36	0.10	0.0075	0.070	0.0036	.	0.072	Rem	OK individually	44 mm Ø x 30 mm
IMN WF4	.	.	0.0021	60.50	0.42	0.57	0.15	0.0095	0.10	0.0045	.	0.11	Rem	OK individually	44 mm Ø x 30 mm
IMN WF5	.	.	0.0030	58.77	0.68	0.52	0.18	0.014	0.14	0.0061	.	0.16	Rem	set only	44 mm Ø x 30 mm
IMN WF6	.	.	0.00095	59.78	0.05	0.98	0.074	0.0020	0.026	.	.	0.028	Rem	OK individually	44 mm Ø x 30 mm

NAVAL BRASS

= class, where 1 = CRM and 2 = RM

31X NB: 42 mm Ø x ~15 mm

BS: 38 mm Ø x see below

CURM: 50 mm Ø x 10-12 mm

IARM: 38 mm Ø x 3 or 19 mm

#	Number	Sn	Pb	Zn	Cu	Al	As	Bi	Fe	Mn	Ni	P	S	Sb	Si	Ag	B	Co
2	CURM 42.25	2.72	0.0023	39.20	57.78	0.021	0.118	<0.001	0.003	0.169	<0.001	0.050	0.005	<0.001	<0.001	.	.	.
2	C42.25	2.2	<0.01	rem	58.5	0.02	0.10	<0.002	<0.005	0.13	<0.005	0.06	0.001	<0.005	<0.002	.	.	.
2	CURM 42.23	1.63	0.575	22.13	74.36	0.008	0.168	0.034	0.354	0.019	0.168	0.128	0.045	0.356	0.015	.	.	.
1	31X NB3J	1.38	0.127	24.46	72.86	0.130	0.0559	0.0786	0.071	0.124	0.0599	0.203	(0.004)	0.197	0.127	0.0464	.	.
1	IARM Cu485-18	0.759	1.76	36.5	60.8	(0.002)	(0.055)	.	0.062	0.0013	0.013	.	.	(0.0018)	(0.003)	C: (0.002)	Cd: 0.0005	
1	IARM Cu464-21	0.751	0.066	38.5	60.7	0.0006	0.0011	0.0010	0.096	0.0115	0.0084	0.0012	.	0.0016	.	0.0040	.	.
1	IARM 76D	0.73	1.69	36.8	60.7	(0.002)	(0.004)	0.0011	0.013	0.0006	(0.003)	0.0018	0.0012	0.0040	0.0037	0.0014	.	0.0010
1	BS 485A	0.725	1.39	36.2	61.5	0.0022	(0.0003)	.	0.010	(0.001)	0.0017	(0.002)	(0.0005)	(0.006)	(0.005)	C: (0.002)	O: (0.0009)	
1	IARM Cu486-18	0.692	1.31	36.5	61.2	(0.0030)	(0.025)	(0.0004)	0.036	(0.0003)	0.032	(0.004)	(0.0030)	(0.0050)	(0.002)	(0.004)	.	(0.0006)
1	BS 464B	0.69	0.054	38.7	60.5	(0.004)	0.0005	.	0.050	(0.09)	0.0092	(0.002)	0.0005	(0.001)	0.011	O: 0.0013	~7 or 19mm	
2	BS 482A	0.65	0.50	38.8	60.0	(0.003)	<0.002	0.020	<0.002	(0.007)	<0.003	<0.002	0.0012	(0.002)	.	.	.	~7 or 19mm
2	BS 464A	0.62	0.056	38.73	60.6	(0.001)	<0.002	0.013	0.0002	0.004	0.012	0.001	(0.001)	<0.01	.	.	.	~7 or 19mm
2	CURM 42.21	0.60	0.259	31.61	66.78	0.003	<0.003	0.013	0.119	<0.001	0.120	0.087	0.034	0.25	0.15	.	.	
1	IARM 75B	0.59	0.63	38.0	60.63	(0.005)	(0.004)	(0.001)	0.06	(0.003)	0.02	0.003	(0.001)	(0.004)	(0.003)	.	.	.
2	C42.21	0.54	0.23	rem	66.1	0.005	<0.005	0.012	0.06	<0.005	0.096	0.081	0.007	0.19	0.081	.	.	.
1	31X NB 1H	0.535	0.504	29.73	68.35	(0.0004)	0.161	0.0065	0.037	0.051	0.520	0.0223	0.0024	0.0057	0.004	.	.	(0.0006)

BS 464B and **BS 485A** are **17025, 17034****CRM NAVAL BRASS SET**

40 mm Ø x 25 mm

Number	Al	Bi	Cu	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn	availability
IMN WK1	0.11	0.014	59.97	0.28	0.13	0.28	0.030	0.17	0.024	0.30	0.11	Rem	ok individually
IMN WK2	0.080	0.011	60.54	0.16	0.088	0.21	0.017	0.33	0.018	0.29	1.34	Rem	ok individually
IMN WK3	0.045	0.0088	62.09	0.066	0.046	0.13	0.017	0.11	0.012	0.16	0.49	Rem	set only
IMN WK4	0.013	0.0052	63.28	0.085	0.020	0.070	0.010	0.050	0.0056	0.082	1.04	Rem	set only
IMN WK5	0.0042	0.0011	64.92	0.0092	0.0056	0.0055	0.0056	0.0062	0.0027	0.0064	0.47	Rem	ok individually

CRM NICKEL AND PHOSPHOR BRASS

analysis listed in mass %

Number	Ni	P	Cu	Zn	Al	Cd	Cr	Fe	Mn	Pb	Sn	Units
31X B29A	4.11	3.33	67.08	24.75	0.219	0.0144	0.062	0.144	0.0625	0.146	0.0328	40 mm Ø x ~15 mm
BAM 387	5.020	.	75.18	19.57	.	.	.	0.0617	0.0796	0.00108	0.00301	40 mm Ø x 30 mm

CRM NICKEL BRASS SETS

nalysis listed in mass % except * which is mg/kg

IMN WH, WM: 40 mm Ø x 25 mm IMN WP: 40 mm Ø x 30 mm

Number	Ni	Zn	Cu	Al	As	Bi	C*	Cd	Co	Fe	Mg	Mn	P	Pb	S	Sb	Si	Sn
available individually																		
IMN WP1	5.45	Rem	67.15	0.020	0.0012	0.00080	.	0.0019	.	0.020	.	0.0069	0.020	0.52	.	0.0010	(0.01)	0.0042
IMN WP2	7.79	Rem	65.08	0.0090	0.0049	0.0052	.	0.0052	.	0.12	.	0.040	0.0067	0.82	.	0.0052	(0.009)	0.11
IMN WP3	10.24	Rem	63.05	0.0020	0.011	0.012	.	0.011	.	0.20	.	0.15	0.0079	1.52	.	0.012	(0.03)	0.18
IMN WP4	12.38	Rem	60.91	0.039	0.015	0.016	.	0.016	.	0.31	.	0.35	0.011	(2)	.	0.015	(0.04)	0.26
IMN WP5	15.63	Rem	58.70	0.049	0.021	0.021	.	0.026	.	0.026	.	0.49	0.0027	(1.8)	.	0.028	(0.03)	0.33
IMN WP6	4.27	Rem	69.37	.	.	.	.	.	.	.	.	.	.	2.41	.	.	.	.
IMN WM1	5.03	25.35	69.06	0.083	0.00026	0.011	44	0.0046	0.021	0.011	0.0054	0.38	0.0018	0.018	0.017	0.00098	0.0026	0.0036
IMN WM2	6.66	24.18	68.41	0.050	0.0030	0.014	52	0.022	0.017	0.022	0.019	0.53	0.023	0.011	0.0058	0.013	0.0067	0.011
IMN WM3	6.09	23.57	69.85	0.033	0.0053	0.0055	58	0.0024	0.011	0.077	0.0042	0.19	0.0052	0.0073	0.0073	0.0043	0.037	0.098
IMN WM4	5.36	23.19	71.10	0.0080	0.0072	0.0029	72	0.0021	0.0099	0.13	0.0027	0.011	0.0057	0.0044	0.0058	0.0059	0.071	0.075
IMN WM5	4.68	25.90	68.99	0.0012	0.0089	0.0007	90	0.00077	0.0021	0.22	0.00056	0.0024	0.016	0.0020	0.0030	0.0068	0.094	0.035
available in SET ONLY																		
IMN WH1	5.70	Rem	68.16	.	.	.	(46)	.	0.0061	0.0052	.	0.56	0.0029	.	(0.0055)	.	0.010	.
IMN WH2	6.34	Rem	69.14	.	.	.	(58)	.	0.017	0.038	.	0.36	0.0072	.	(0.0071)	.	0.038	.
IMN WH3	3.44	Rem	70.18	.	.	.	(70)	.	0.031	0.11	.	0.25	0.013	.	(0.011)	.	0.072	.
IMN WH4	4.14	Rem	71.15	.	.	.	(75)	.	0.048	0.13	.	0.11	0.015	.	(0.017)	.	0.12	.
IMN WH5	4.89	Rem	72.28	.	.	.	(87)	.	0.028	0.22	.	0.011	0.017	.	(0.021)	.	0.17	.

SILICON BRASS

= class, where 1 = CRM and 2 = RM

Number	Si	Zn	Cu	Al	Fe	Mn	Ni	P	Pb	Sb	Sn
2 CTIF LS2	4.91	11.60	79.60	0.156	1.022	0.220	1.110	0.064	0.886	0.0103	0.338
1 ERM-EB393a	3.35	(20.8)	75.8	0.00021	0.0143	0.00185	0.00297	0.0454	0.0104	(0.000093)	0.00390
2 CTIF LS3	3.3	19	76	0.43	0.10	0.15	0.11	0.011	0.58	0.107	0.15
1 31X WSB6F	3.13	0.0506	95.40	(0.0013)	0.158	0.924	0.0509	0.0179	0.0310	0.0406	0.0142
1 IARM Cu693-21	3.1	21.9	74.8	0.00043	0.028	0.041	0.0019	0.099	0.030	.	0.022
1 IARM 313A	3.09	21.3	75.4	(0.001)	0.011	(0.001)	(0.002)	0.09	0.042	0.014	0.006
2 HRT CU2021	2.9	10.0	86.6	0.0008	0.019	0.044	0.002	0.081	0.006	0.001	0.006

Number	Ag	As	B	C	Cd	Co	Cr	S	Zr	Units
CTIF LS2	.	.	.	.	.	.	.	.	.	60 mm Ø x 5 mm
ERM-EB393a	.	0.000134	Bi: (0.000019)	.	0.000061	.	0.000156	Se: (0.00047)	.	40 mm Ø x 30 mm
CTIF LS3	.	.	.	.	.	.	.	.	.	60 mm Ø x 5 mm
31X WSB6F	0.0131	0.0110	0.0054	.	0.0039	0.0095	.	.	.	~40 mm Ø x ~15 mm
IARM Cu693-21	.	.	.	.	.	.	0.0006	.	.	38 mm Ø x 3 or 19 mm
IARM 313A	0.0017	0.0010	0.0008	(0.002)	(0.0003)	(0.004)	(0.001)	0.0016	(0.0004)	31 mm Ø x 2 mm
HRT CU2021	.	(0.0006)	Bi:0.0006	.	0.0005	.	0.0006	0.001	.	42 mm Ø x 20 mm

CRM HIGH TENSILE BRASS

Number	Cu	Zn	Al	Fe	Mn	Si	As	C	Ni	P	Pb	S	Sb	Sn	Units
31X HT31B	67.00	17.06	6.82	3.01	5.69	0.0443	0.0005	0.0057	0.226	0.0030	0.0139	0.0007	B:0.0014	0.079	~40 mm Ø x ~15 mm

RM BRONZE MUSHROOMS

chill cast typical analysis 60 mm Ø x 5 mm

Number	Sn	Zn	Cu	Al	As	Fe	Mn	Ni	P	Pb	S	Sb	Si
CTIF B 1	15.15	0.92	82.90	0.072	.	0.088	.	0.063	0.037	0.202	0.030	0.444	0.055
CTIF B 2	13.55	0.11	85.90	(0.002)	.	0.041	.	(0.003)	0.17	0.0206	0.048	(<0.002)	0.17
CTIF B 3	12.8	2.2	80.2	0.1	.	0.2	0.20	1.5	0.45	1.6	0.04	0.2	0.07
CTIF B 4	11.10	1.34	83.75	.	.	0.021	.	0.57	0.52	2.53	0.019	0.10	0.015
CTIF B 14	10.75	0.15	87.00	<0.01	0.04	0.11	0.02	0.30	0.64	0.50	0.02	0.08	0.075
CTIF B 13	10.05	1.09	86.35	0.016	0.065	0.250	0.046	0.50	0.210	0.99	0.070	0.243	0.085
CTIF B 5	9.90	0.42	85.95	0.039	.	0.18	0.082	2.28	0.041	0.48	0.067	0.47	0.049
CTIF B 30	9.80	1.05	77.45	0.063	.	0.115	0.150	0.97	0.063	10.0	0.048	0.22	0.066
CTIF B 12	9.57	0.61	85.65	0.120	0.111	0.162	0.235	2.63	0.525	0.201	0.013	0.117	0.050
CTIF B 11	8.04	2.10	84.75	.	.	0.170	.	2.0	0.057	1.93	0.09	0.70	0.14
CTIF B 31	7.65	0.79	78.65	(0.031)	.	(0.015)	.	0.489	.	11.79	0.028	0.475	(0.047)
CTIF B 23	7.18	1.46	83.45	0.020	.	(0.040)	.	0.086	0.070	7.20	0.019	0.384	0.025
CTIF B 10	6.95	2.75	83.65	0.205	0.0075	0.165	(0.0045)	1.01	0.014	4.07	0.050	1.14	.
CTIF B 20	6.35	3.77	83.35	0.040	.	0.165	.	0.51	0.072	5.10	0.115	0.520	0.055
CTIF B 32	5.92	1.17	74.80	0.075	0.0056	0.11	.	1.49	0.039	16.10	0.027	0.13	0.070
CTIF B 21	5.13	6.17	83.05	0.13	.	0.285	.	1.21	(0.004)	3.79	0.047	0.18	.
CTIF B 22	3.5	4.0	83.0	.	.	<0.10	.	2.5	.	6.0	0.03	0.05	<0.1
CTIF UN 3S	0.215	1.62	92.65	0.11	.	0.30	0.073	3.45	.	0.20	.	.	1.24
Number	Sn	Zn	Cu	Al	As	Fe	Mn	Ni	P	Pb	S	Sb	Si

BRONZE

Number	Cu	Fe	Ni	P	Pb	Sn	Zn	method	Units
32X CSN1A	.	0.0020	(0.0001)	0.0007	.	0.306	0.0039	wrought	~20 mm Ø x ~22 mm
SRM 1115	87.9	0.13	0.074	0.005	0.013	0.10	11.7	wrought	31 mm Ø x 19 mm
SRM C1115	87.9	0.13	0.074	0.005	0.013	0.10	11.7	cast	31 mm x 31 mm x 19 mm
SRM 1116	90.3	0.046	0.048	0.008	0.042	0.04	9.4	wrought	31 mm Ø x 19 mm
SRM 1117	93.0	0.014	0.020	0.002	0.069	0.02	6.8	wrought	31 mm Ø x 19 mm
SRM C1117	93.0	0.014	0.020	0.002	0.069	0.02	6.8	cast	31 mm x 31 mm x 19 mm

40 mm Ø x ~25-30 mm

Number	Al	As	Bi	Cd	Co	Cr*	Fe	Mg*	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	Singly?
IMN BF1	10.90	0.061	0.00042	.	.	.	(6.2)	.	0.0059	2.49	(0.012)	0.23	.	(0.002)	0.26	0.011	0.57	no
IMN BF2	9.96	0.050	0.0025	.	.	.	(5.4)	.	0.12	3.54	0.053	0.15	.	(0.013)	0.25	0.081	0.40	yes
IMN BF3	9.58	0.038	0.0039	.	.	.	4.50	.	0.28	4.43	0.098	0.111	.	0.028	0.20	0.17	0.27	no
IMN BF4	9.12	0.022	0.0057	.	.	.	3.25	.	0.39	5.24	0.13	0.059	.	0.037	0.097	0.25	0.10	yes
IMN BF5	8.35	0.0039	0.010	.	.	.	2.44	.	0.50	6.03	0.16	0.014	.	0.048	0.028	0.35	0.018	yes
IMN BP1	8.935	0.00094	0.00053	0.00054	.	3.7	0.00305	.	0.00535	0.243	0.00055	0.00055	.	0.00052	(0.00544)	0.00043	0.0100	yes
IMN BP2	6.136	0.00215	0.00222	0.00214	.	26.7	0.0184	.	0.0189	1.032	0.00208	0.00238	.	0.00468	0.0220	0.00199	0.024	no
IMN BP3	7.120	0.00980	0.0102	0.00928	.	104	0.0743	.	0.152	1.850	0.00661	0.0103	.	0.0108	0.0804	0.0106	0.176	no
IMN BP4	4.632	0.0238	0.0207	0.0226	.	217	0.0131	.	0.304	2.522	0.0238	0.0229	.	0.0215	0.183	0.0229	0.343	no
IMN BP5	3.769	0.0361	0.0349	0.0356	.	374	0.200	.	0.411	3.528	0.0189	0.0347	.	0.0356	0.266	0.0336	0.459	yes
IMN BO1	3.16	0.00033	0.00030	0.00035	.	32.7	0.0158	.	0.0167	0.00517	(0.0004)	0.00384	.	0.00035	(0.00471)	2.54	7.10	yes
IMN BO2	4.03	0.00199	0.00197	0.00182	.	3.7	0.00569	.	0.00102	0.00204	0.00227	(0.00214)	.	0.00226	0.00979	1.83	6.26	yes
IMN BO3	4.67	0.00662	0.00660	0.00570	.	54.8	0.0752	.	0.00884	0.0683	0.00550	0.0537	.	0.00568	0.0552	1.17	5.07	yes
IMN BO4	6.15	0.0115	0.0107	0.00881	.	91	0.137	.	0.00612	0.111	0.0100	0.102	.	0.0104	0.0951	0.704	4.28	yes
IMN BO5	7.02	0.0161	0.0152	0.0134	.	145	0.218	.	0.0772	0.0355	0.0155	0.0299	.	0.0152	0.0135	0.117	3.08	yes
IMN BJ1	2.88	0.011	0.013	0.016	0.027	.	0.011	58	0.60	6.97	0.0022	0.0025	0.021	0.0012	(0.11)	(0.11)	0.020	yes
IMN BJ2	2.46	0.0089	0.0095	0.011	0.020	.	0.038	98	0.42	6.47	0.011	0.0043	0.014	0.0030	(0.091)	(0.080)	0.038	yes
IMN BJ3	1.97	0.0072	0.0071	0.0076	0.014	.	0.12	65	0.21	5.87	0.014	0.0081	0.0082	0.0056	(0.047)	(0.049)	0.22	no
IMN BJ4	1.50	0.0031	0.0042	0.0048	0.0076	.	0.20	35	0.013	5.49	0.013	0.010	0.0049	0.0088	(0.015)	(0.014)	0.36	no
IMN BJ5	1.09	0.0018	0.0013	0.00075	0.0024	.	0.28	17	0.0030	5.00	0.019	0.017	0.0023	0.010	(0.0071)	(0.0034)	0.51	yes

= class, where 1 = CRM and 2 = RM

#	Number	Al	Cu	As	Cr	Fe	Mg	Mn	Ni	P	Pb	Si	Sn	Zn
1	IARM Cu954-20	10.48	84.7	0.0007	0.028	3.84	.	0.54	0.30	0.009	0.018	0.029	0.010	0.068
1	IARM Cu955-18	10.37	80.8	(0.0020)	0.008	3.50	.	0.77	4.5	(0.013)	0.006	(0.022)	0.0056	0.038
1	IARM Cu954-18	10.36	84.7	(0.0030)	(0.003)	4.23	(0.0013)	0.29	0.134	(0.016)	0.016	0.025	0.047	0.141
1	BS 624	10.2	86.5	<0.01	.	3.02	.	0.16	0.052	<0.005	<0.005	0.019	(0.016)	(0.007)
2	HRT CU2018	10.00	84.06	.	.	3.06	.	2.49	0.04	0.014	(0.021)	0.020	0.014	0.10
1	VS BR1	9.6	.	.	.	3.32	.	1.41	0.015	0.007	0.016	0.041	0.011	0.075
1	VS BR4	9.4	.	.	.	3.38	.	1.51	0.043	.	0.015	0.077	0.008	0.034
1	32X CA 7A	9.37	88.06	.	0.0028	2.09	0.0004	0.151	0.234	.	(0.004)	0.017	0.0172	0.006
2	BS 623	9.24	(88.1)	<0.01	.	2.25	.	0.16	0.10	0.013	<0.01	0.046	0.01	0.05
1	IARM 79C	9.20	87.6	0.003	(0.002)	2.28	.	0.20	0.55	0.006	<0.005	0.033	0.010	0.014
1	IARM 79B	9.19	88.4	.	(0.003)	2.13	.	0.16	0.075	0.005	(0.003)	0.019	0.017	0.013
2	BS 623A	9.12	88.13	(0.006)	.	2.19	.	0.273	0.146	<0.002	0.001	0.014	0.002	0.008
1	VS BR2	8.53	.	.	.	0.101	.	1.77	0.023	0.0083	0.0085	0.038	0.019	0.011
2	CURM 51.14	8.42	88.57	0.44	.	0.72	.	0.55	0.219	0.012	0.003	0.286	0.113	0.656
2	CURM 51.13	7.30	88.79	0.215	.	1.81	.	0.898	0.057	0.022	0.104	0.174	0.270	0.335
1	BS 642B	7.17	89.9	0.0015	0.0014	0.285	0.0032	0.069	0.222	0.004	0.0152	2.15	0.0056	0.128
1	BS 642C	7.13	90.4	0.0008	0.0009	0.11	0.0014	0.0148	0.0363	0.0040	0.0109	2.20	0.0061	0.039
2	C51.13	6.93	Rem	0.21	.	2.05	.	0.77	0.053	0.021	0.12	0.16	0.19	0.30
1	32X 61400A	6.81	89.99	.	.	2.74	0.0050	0.082	0.0242	0.0008	(0.0007)	0.0124	0.301	0.060
1	BS 642D	6.73	91.2	(0.002)	0.0004	0.152	(0.0003)	0.018	0.047	0.0007	0.0038	1.77	0.019	0.093
1	IARMCu642-18	6.5	90.0	.	.	0.039	.	0.0024	(0.014)	(0.009)	0.019	1.96	0.019	1.19
2	CURM 51.12	6.36	88.29	0.111	.	2.87	.	1.33	0.112	<0.001	0.219	0.005	0.196	0.45
1	32X CA12A	6.14	90.48	.	0.0008	0.657	0.0005	0.0290	0.088	.	(0.0017)	2.57	0.0157	0.040
2	C51.12	6.06	Rem	0.11	.	2.90	.	1.25	0.11	<0.005	0.25	<0.01	0.18	0.42
2	CURM 51.11	5.27	93.95	<0.001	.	0.060	.	<0.001	0.012	0.035	0.33	0.159	0.027	0.111

**Need a larger size?
Most BS items are
available in any height.**

[illegible]

ALUMINUM BRONZE - HIGH NICKEL

= class, where 1 = CRM and 2 = RM

#	Number	Al	Cu	As	Cr	Fe	Mg	Mn	Ni	P	Pb	Si	Sn	Zn
2	BS 955C	10.68	80.6	(<0.002)	.	4.04	.	0.06	4.31	0.012	0.003	0.025	0.003	0.15
1	IARM Cu954-21	10.55	85.1	.	0.022	3.66	0.0013	0.393	0.105	0.0031	0.012	0.029	0.0053	0.029
2	BS 954C	10.21	83.9	(0.006)	.	3.9	.	0.29	1.38	0.011	0.050	0.07	0.08	0.09
2	BS 954B	10.20	83.9	(0.005)	.	3.90	.	0.27	1.38	0.012	0.047	0.07	0.07	0.10
2	HRT CU2001	10.05	79.09	.	.	4.79	.	0.36	4.94	0.011	0.015	0.08	0.018	0.17
2	C52.51	10.0	Rem	.	<0.01	4.3	<0.01	<0.01	5.1	.	<0.01	<0.01	<0.01	0.02
2	HRT CU2009	9.93	78.88	.	.	3.73	.	0.29	6.22	0.010	0.037	0.19	0.020	0.54
1	IARM 334B	9.91	80.8	(0.003)	(0.004)	3.7	(0.001)	0.60	4.70	0.005	0.006	0.075	0.019	0.122
1	BS 630C	9.90	80.7	0.0007	0.0030	3.82	0.0011	0.325	4.82	0.0043	0.0093	0.064	0.0152	0.234
1	BS 630B	9.78	80.8	0.0007	0.0017	3.90	0.0009	0.281	4.88	0.0028	0.0056	0.0166	0.0289	0.254
1	IARM 334A	9.76	80.7	(0.004)	(0.01)	3.82	(0.001)	0.69	4.77	(0.005)	0.010	0.073	0.025	0.110
2	IARM 80D	9.67	(81.7)	(0.009)	(0.005)	2.99	(0.003)	0.346	5.01	(0.005)	(0.005)	0.025	0.093	(0.007)
1	VS BR3	9.6	.	.	.	4.00	.	0.227	3.85	(0.003)	0.007	0.071	0.005	0.009
2	BS CC954	9.28	84.0	0.003	.	3.61	.	0.353	1.12	0.013	0.13	0.092	0.061	1.30
2	C52.56	8.9	Rem	.	0.14	4.6	0.09	0.74	5.6	.	0.17	0.15	0.11	0.28
1	32X ALB 12A	8.29	82.90	.	.	1.094	0.0013	0.958	6.33	0.0101	0.0018	0.0202	0.310	0.0625
2	CURM 52.54	7.85	81.59	.	<0.005	3.31	<0.005	1.20	5.40	.	0.086	0.022	0.135	0.39
1	32X ALB 13A	7.09	84.96	.	.	1.171	.	5.39	1.381	0.009	(0.0009)	0.086	0.0072	0.0194

#	Number	Al	Cu	As	Cr	Fe	Mg	Mn	Ni	P	Pb	Si	Sn	Zn
Number	Ag	Be	Bi	C	Co	S	Sb	Se	Units					
BS 955C	0.014	.	.	.	.	.	(<0.002)	.	38 mm Ø x ~7 or 19+ mm					
IARM Cu954-21	0.0012	.	(0.0009)	.	(0.002)	(0.0019)	(0.0019)	.	38 mm Ø x 3 or 19 mm					
BS 954C	.	.	.	(0.004)	.	(<0.0005)	<0.003	.	38 mm Ø x ~7 or 19+ mm					
BS 954B	.	.	.	(0.005)	.	(<0.0005)	(0.001)	.	38 mm Ø x ~7 or 19+ mm					
HRT CU2001	.	.	.	.	.	0.003	.	.	40 mm Ø x 20 mm					
C52.51	.	.	.	.	.	.	.	.	50 mm Ø x 10 - 12 mm					
HRT CU2009	.	.	.	.	.	.	.	.	40 mm Ø x 20 mm					
IARM 334B	0.0013	(0.001)	(0.001)	0.005	(0.003)	0.0008	(0.004)	(0.004)	31 mm Ø x 2 or 18 mm					
BS 630C	.	(<0.0005)	.	0.0060	0.0019	(<0.0005)	0.0003	last	38 mm Ø x 19 mm 17025					
BS 630B	.	(<0.0005)	.	0.0067	0.0017	0.0013	(<0.0005)	.	38 mm Ø x ~7 or 19 mm+ 17025					
IARM 334A	(0.001)	(0.001)	(0.001)	0.0058	(0.003)	0.0007	0.004	.	31 mm Ø x 2 or 18 mm					
IARM 80D	(0.04)	<0.002	(0.004)	(0.004)	0.022	(0.003)	<0.02	<0.03	31 mm Ø x 2 or 18 mm					
VS BR3	.	.	.	.	.	.	.	.	38 mm Ø x 18 mm					
BS CC954	.	.	.	(0.007)	.	(0.002)	0.004	.	32 mm Ø x 17 mm					
C52.56	.	.	.	.	.	.	.	.	50 mm Ø x 10 - 12 mm					
32X ALB 12A	0.044	.	.	.	0.0056	.	.	(0.0007)	~41 mm Ø x ~15 mm					
CURM 52.54	.	.	.	.	.	.	.	.	50 mm Ø x 10 - 12 mm					
32X ALB 13A	.	.	.	.	0.0011	.	.	(0.0007)	~35 mm Ø x ~15 mm					
Number	Ag	Be	Bi	C	Co	S	Sb	Se	Units					

Need a larger size?
Most BS items are
available in any height.

RM ALUMINUM BRONZE MUSHROOMS

chill cast	typical analysis												60 mm Ø x 5 mm	
Number	Al	Cu	Fe	Mn	Ni	Pb	Si	Sn	Zn	Bi	Cd	Cr	Mg	
CTIF CA 36	12.60	77.25	2.93	0.131	6.33	0.0154	0.113	0.201	0.244	0.058	.	0.041	0.130	last
CTIF 2158-W	11.95	85.00	2.53	0.26	0.10	<0.005	0.015	<0.01	<0.01	.	.	.	.	
CTIF 4065-P	11.85	81.20	3.40	0.075	3.18	0.03	0.034	0.18	0.03	.	.	.	.	
CTIF CA 35	11.4	75.6	6.1	1.6	3.80	0.10	0.25	0.30	0.55	.	.	.	.	
CTIF CA 13	11.20	82.45	3.82	1.22	0.50	0.0230	0.11	(0.01)	0.65	.	.	.	.	
CTIF CA 3	10.9	86.5	0.80	0.06	0.80	0.15	0.08	0.20	0.30	.	.	.	.	0.125
CTIF CA 21	10.82	81.9	3.45	0.30	3.09	0.05	0.07	0.07	0.100	.	0.0095	.	.	
CTIF CA11	10.54	84.45	1.27	0.779	1.95	0.109	0.254	0.258	0.211	.	.	.	.	
CTIF CA 22	10.45	80.50	2.51	0.745	4.54	0.0243	0.32	0.30	0.605	.	.	.	.	
CTIF 3011-G	10.35	84.80	1.98	0.165	2.00	0.10	0.16	0.125	0.25	.	.	.	.	
CTIF CA 27	10.25	81.1	2.81	1.195	3.88	0.11	0.127	0.054	0.428	.	0.012	.	.	0.077
CTIF CA 10	10.15	80.65	4.55	0.333	3.39	0.16	0.46	0.16	0.067	.	.	.	.	
CTIF 3299-J	10.10	87.60	0.38	1.12	0.21	0.110	0.136	0.106	0.19	.	.	.	.	
CTIF 3297-Y	10.00	87.45	1.88	0.03	.	0.11	0.15	0.10	0.27	.	.	.	.	
CTIF CA37	9.84	76.79	6.85	0.752	4.98	0.0503	0.040	0.147	0.364	0.0118	.	0.085	.	
CTIF 4149-G	9.84	84.95	2.00	0.21	1.96	0.15	0.18	0.34	0.37	.	.	.	.	0.02
CTIF 2152-S	9.78	85.05	3.99	0.42	0.68	<0.005	0.015	.	<0.01	.	.	.	.	
CTIF 2151-R	9.43	84.75	4.48	0.73	0.56	<0.005	0.015	<0.01	<0.01	.	.	.	.	
CTIF 3296-L	9.40	88.55	0.07	0.37	0.41	0.30	0.20	0.06	0.62	.	.	.	.	
CTIF CA 31	9.15	76.5	3.18	3.27	7.51	0.020	0.064	0.063	0.145	.	.	.	.	
CTIF CA 26	9.10	81.25	4.36	0.188	4.87	0.058	0.035	0.005	0.038	.	0.034	.	.	0.05
CTIF 3300-M	8.73	89.5	0.45	0.165	0.205	0.205	0.415	0.205	0.085	.	.	.	.	
CTIF 3301-Z	8.10	87.30	4.00	0.26	0.125	0.032	0.057	0.028	0.06	.	.	.	.	
CTIF 2794-H	8.0	90.3	0.82	<0.01	0.69	<0.01	0.048	0.105	<0.01	.	.	.	.	
CTIF CA 20	8.00	87.15	0.79	1.85	1.18	0.18	0.17	0.19	0.41	.	.	.	.	
CTIF CA 12	8.0	84.1	2.77	3.09	1.385	0.047	0.058	0.036	0.45	.	.	.	.	0.090
CTIF CA 25	7.97	79.12	6.10	0.51	5.74	0.03	0.084	0.177	0.252	.	.	.	.	
CTIF CA 30	7.55	81.6	5.2	2.05	3.10	0.142	0.15	0.099	0.066	.	.	.	.	
CTIF 3018-F	7.25	81.90	4.45	1.57	4.50	0.02	0.085	0.06	0.06	.	.	.	.	
CTIF 3610-Q	7.10	82.32	3.98	0.045	5.40	0.23	0.065	0.25	0.51	.	.	.	.	
Number	Al	Cu	Fe	Mn	Ni	Pb	Si	Sn	Zn	Bi	Cd	Cr	Mg	

CRM BISMUTH BRONZE

Number	Bi	Cu	Ni	P	Pb	Sn	Zn	Al	Fe	O	S	Sb	Se	Units
IARM CuB1-18	4.51	88.98	0.58	0.049	0.015	5.58	0.47	(0.0012)	(0.0016)	(0.003)	(0.0020)	(0.003)	(0.0025)	31 mm Ø x 2 mm or 18 mm

MANGANESE BRONZE

# = class, 1=CRM and 2=RM		BS 675B, 863B, 675A: 38 Ø x ~7 to 19+ mm										BS 675: 38 Ø x 12 mm			IARM: 31 Ø x 2 or 18 mm		
#	Number	Mn	Al	Fe	Sn	Zn	Cu	As	C	Co	Cr	Ni	P	Pb	S	Sb	Si
1	BS 863B	2.97	5.25	2.84	0.033	26.1	[62.4]	0.0004	0.0028	0.0009	0.0042	0.081	0.0010	0.0205	0.0007	0.0012	0.0103
1	IARM 88C	2.99	5.79	2.98	0.147	22.86	64.5	(0.007)	0.005	0.0010	0.008	0.276	0.020	0.133	0.0010	(0.003)	0.091
2	BS 675A	0.32	<0.002	1.12	0.8	39.1	58.5	0.003	(0.0007)	.	.	0.019	0.010	0.074	(0.0005)	0.0011	(0.005)
1	BS 675B	0.175	(<0.005)	1.10	0.92	39.3	58.7	0.0009	(<0.001)	(0.0002)	(0.0002)	0.0071	0.0020	0.071	0.0002	0.0011	(<0.005)
1	IARM 83B	0.13	0.002	0.97	0.85	39.3	58.7	.	0.003	.	.	0.010	0.004	0.017	(0.001)	(0.004)	(0.003)
2	BS 675	0.11	<0.01	0.73	0.92	39.7	Rem.	<0.005	(0.0004)	.	last	<0.01	<0.01	<0.01	(0.0013)	<0.01	<0.02
BS 675B and 863B are 17025																	

CRM NICKEL BRONZE SET

available in SET/5 or individually					analysis listed in mass %							40 mm Ø x ~30 mm	
Number	Al	Bi	Cu	Fe	Ni	P	Pb	S	Sb	Se	Si	Sn	Zn
IMN BN5	0.0245	0.0298	rem	0.00731	2.69	0.0634	0.00612	0.0018	0.0314	0.00636	(0.00211)	11.82	0.0560
IMN BN1	0.00286	0.118	rem	0.495	0.226	0.123	0.0239	0.113	0.117	0.00335	(0.00839)	6.47	0.135
IMN BN2	0.00371	0.0707	rem	0.589	1.64	0.0769	0.00514	0.213	0.0656	0.0104	.	6.21	0.369
IMN BN3	0.00126	0.00098	rem	0.153	1.04	0.00038	0.0054	(0.0017)	0.0088	.	.	9.29	0.0625
IMN BN4	0.00055	0.00595	rem	0.0216	0.635	0.0066	0.0145	0.112	0.0055	0.0134	(0.00064)	9.81	0.00771

Need a larger size?
Most BS items are
available in any height.

PHOSPHOR BRONZE

= class, where 1 = CRM and 2 = RM

#	Number	P	Sn	Zn	Cu	Mn	Ni	Pb	Al	As	Fe	Mg	S	Sb	Si
1	32X PB11H	0.89	3.07	1.53	91.3	0.0404	0.70	1.07	0.070	0.187	0.377	0.015	0.011	0.446	0.084
1	BS 510C	0.335	5.43	0.13	94.1	<0.001	0.015	0.0051	(0.0009)	<0.005	0.0042	.	0.0019	<0.01	0.0028
1	32X 51000A	0.300	4.85	0.0105	94.87	.	0.0084	0.0032	0.0007	.	0.0024	.	0.0021	.	.
1	33X 54400A	0.243	3.97	3.87	86.79	.	0.244	4.69	0.0009	0.0156	0.072	.	0.0251	0.0362	.
1	IARM 78B	0.19	4.73	3.55	87.7	(0.002)	0.077	3.87	(0.002)	<0.003	0.02	.	0.010	0.01	<0.002
1	IARM Cu510-18	(0.16)	4.54	0.0034	95.2	(0.0010)	(0.017)	(0.0027)	(0.0004)	(0.0007)	(0.0008)	.	(0.0020)	(0.0008)	(0.0050)
1	IARM 77B	0.148	4.66	0.007	95.2	(0.002)	0.002	0.016	(0.001)	(0.001)	0.002	.	0.002	0.005	(0.003)
1	32X 52100A	0.146	7.73	0.0026	92.10	.	0.0111	0.0031	0.0009	0.0009	0.0008	.	0.0008	.	.
1	32X PB14E	0.128	9.65	0.103	89.70	0.0141	0.103	0.0354	0.0201	0.0235	0.0211	.	0.070	0.0433	(0.003)
2	BS 510A	0.11	4.6	0.21	95.10	<0.002	0.020	0.016	<0.002	0.0008	0.005	.	0.008	(0.003)	<0.003
2	CURM 54.02	0.107	5.53	0.410	92.87	0.101	0.109	0.663	0.020	0.023	0.102	0.0020	0.030	0.026	0.012
1	32X PB15B	0.104	2.04	0.75	.	0.0006	0.145	0.046	0.064	0.102	0.044	0.023	0.0016	0.020	.
1	32X PB13E	0.089	6.55	0.301	92.48	0.0440	0.0953	0.109	0.0251	0.0391	0.0549	.	.	0.092	0.053
1	BS 510B	0.074	4.6	0.251	[95.0]	0.0004	0.0211	0.0112	(0.006)	0.0010	0.009	.	0.007	(0.002)	(0.003)
1	IARM Cu544-18	0.069	4.14	3.80	88.0	.	0.019	3.92	.	.	(0.010)	.	.	.	.
2	CURM 54.01	0.053	3.17	0.346	95.42	0.158	0.348	0.307	0.040	0.044	0.028	0.008	0.023	0.070	0.039
2	HRT CU2016	0.050	7.23	0.006	92.67	0.007	0.007	0.006	.	.	0.004	.	0.003	0.006	.
2	C54.01	0.05	3.2	0.31	Rem	0.13	0.26	0.29	0.009	0.04	0.01	<0.001	0.03	0.08	0.006
1	BS 544B	0.0258	4.06	3.51	88.2	(0.0009)	0.068	3.9	(0.0009)	0.0043	0.087	.	0.0249	0.0244	0.0042
1	32X PB17A	0.017	21.8	0.0188	77.3	.	0.044	0.213	.	0.175	0.0009	.	0.0220	0.051	.
1	BS 544C	0.0092	4.10	3.78	88.4	<0.005	0.153	3.31	<0.05	(0.008)	0.055	.	0.058	0.0045	0.0029
1	32X PB16A	0.0073	17.60	0.0082	82.02	.	0.127	0.088	(0.0006)	0.0035	(0.001)	.	0.0049	0.013	0.005

Number	Ag	Bi	C	Co	Cr	N	O	Se	Units
32X PB11H	B:0.0021	0.023	.	0.034	.	.	.	.	~40 mm Ø x ~15 mm
BS 510C	(0.004)	.	(0.0010)	0.0008	<0.005	.	0.0006	.	38 mm Ø x ~7 or 19+ mm 17025, 17034
32X 51000A	0.0022	.	.	.	.	.	.	.	38 mm Ø x ~15 mm
33X 54400A	0.0124	.	.	0.0013	.	.	.	.	~38 mm Ø x ~15 mm
IARM 78B	.	.	.	.	.	.	.	.	31 mm Ø x 2 mm
IARM Cu510-18	0.0019	.	(0.0018)	.	.	.	0.0011	.	31 mm Ø x 2 or 18 mm
IARM 77B	.	0.003	.	.	.	.	.	.	31 mm Ø x 2 or 18 mm
32X 52100A	0.0011	0.0019	.	.	.	.	.	.	38 mm Ø x ~15 mm
32X PB14E	0.0152	0.146	.	0.0047	.	.	.	.	~40 mm Ø x ~15 mm
BS 510A	.	.	(0.0006)	.	.	.	.	.	38 mm Ø x ~5-7 or 12 mm last
CURM 54.02	.	.	.	.	.	.	.	.	50 mm Ø x 10-12 mm
32X PB15B	.	(0.0002)	.	0.037	0.0004	.	.	(0.0008)	~40 mm Ø x ~15 mm
32X PB13E	0.0205	0.0224	.	0.0088	.	.	.	.	~40 mm Ø x ~15 mm
BS 510B	Zr: (0.0004)	.	0.0010	(0.0006)	(0.0008)	(0.0001)	0.0009	.	38 mm Ø x ~7 or 19+ mm 17025
IARM Cu544-18	.	.	.	.	.	.	.	.	38 mm Ø x ~3 or 19 mm
CURM 54.01	.	.	.	.	.	.	.	.	50 mm Ø x 10-12 mm
HRT CU2016	.	.	.	.	.	.	.	.	40 mm Ø x 20 mm
C54.01	.	.	.	.	.	.	.	.	50 mm Ø x 10-12 mm
BS 544B	0.0173	.	0.0031	(0.0012)	(0.0007)	(0.0007)	0.0005	.	38 mm Ø x ~7 or 19+ mm 17025
32X PB17A	0.017	0.026	.	0.0018	(0.0004)	.	.	0.0022	~40 mm Ø x ~15 mm
BS 544C	<0.005	.	0.0018	(0.0020)	<0.005	.	0.0006	.	38 mm Ø x ~7 or 19+ mm 17025, 17034
32X PB16A	0.0166	0.0530	.	(0.0004)	.	.	Te: (0.002)	.	~40 mm Ø x ~15 mm

SILICON BRONZE

= class, where 1 = CRM and 2 = RM

#	Number	Si	Cu	Mn	Al	As	C	Cr	Fe	Ni	P	Pb	Sn	Zn
1	BS 655B	3.25	95.7	0.928	(0.005)	0.0004	0.0012	0.0006	0.042	0.0043	0.0047	0.0205	0.0053	0.0248
1	BS 655C	3.22	95.6	0.958	(0.005)	0.0006	(0.005)	0.0021	0.052	0.0030	0.0035	0.0047	0.0049	0.0152
1	IARM 82B	3.22	95.3	1.04	0.002	<0.002	(0.003)	0.004	0.080	0.011	0.004	0.011	0.017	0.38
1	37X 65500A	3.13	95.75	0.960	0.0028	.	(0.0044)	0.0029	0.035	0.0059	0.0046	0.0034	0.0426	0.0353
1	IARM Cu655-18	3.15	95.5	0.98	(0.0020)	(0.0004)	(0.0100)	.	0.055	0.0034	(0.0020)	(0.018)	0.009	0.149
2	BS 655A	3.14	95.74	0.91	(0.002)	<0.002	(0.0006)	.	0.075	0.008	(0.004)	0.008	0.07	0.02
1	IARM Cu647-18	0.70	(96.5)	(0.099)	0.0027	.	.	.	(0.0056)	2.69	(0.02)	(0.007)	(0.01)	(0.005)
	Number	Be	Co	Mg	N	O	S	Sb	Zr	Units				
	BS 655B	(0.0005)	(0.005)	(0.0005)	(0.0005)	(0.0005)	0.0010	0.0002	(0.0005)	38 mm Ø x ~7 or 19+ mm	17025			
	BS 655C	(0.0005)	(0.005)	(0.005)	(0.0005)	(0.001)	0.0007	(0.0005)	.	38 mm Ø x ~7, ~12 or 19+ mm	17025			
	IARM 82B	.	.	.	<0.0005	(0.001)	0.003	<0.01	.	31 mm Ø x 2 mm last				
	37X 65500A	0.0014	.	.	.	.	0.0010	.	.	~38 mm Ø x ~15 mm				
	IARM Cu655-18	.	Ag: (0.0015)	.	.	.	(0.0010)	(0.0008)	.	31 mm Ø x 2 or 18 mm				
	BS 655A	.	.	.	.	.	(0.0006)	<0.002	.	38 mm Ø x ~7, 12 or 19+ mm				
	IARM Cu647-18	.	.	(0.0086)	.	.	.	.	0.044	31 mm Ø x 2 or 18 mm				

CRM

SILICON BRONZE SET

BH1 BH3 and BH6 set only, others ok individually

40 mm Ø x 25 mm

Number	Al	As	Bi	Cu	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn
IMN BH1	0.027	0.0047	0.018	Rem	1.67	0.0065	0.25	0.96	0.0047	0.74	0.012	0.066	4.77	0.044	2.03
IMN BH2	0.079	0.015	0.014	Rem	1.28	0.0066	0.54	0.74	0.023	0.57	0.0092	0.042	4.14	0.21	2.99
IMN BH3	0.14	0.022	0.0091	Rem	0.96	0.0075	1.00	0.53	0.039	0.40	0.0062	0.026	3.07	0.37	3.84
IMN BH4	0.22	0.054	0.006	Rem	0.55	0.0057	1.46	0.28	0.059	0.24	0.0064	0.016	2.29	0.55	4.91
IMN BH5	0.29	0.071	0.0019	Rem	0.093	0.0024	1.80	0.047	0.073	0.015	0.0055	0.0054	1.45	0.69	5.58
IMN BH6	0.32	0.078	0.018	Rem	0.35	0.01	0.80	0.39	0.078	0.017	0.016	0.056	1.51	0.32	6.27

LEADED, TIN, AND LEADED TIN BRONZE CHART 1 of 2

= class, where 1 = CRM and 2 = RM

#	Number	Sn	Pb	Zn	Cu	Al	Fe	Mn	Ni	P	S	Sb	Si
1	32X SN5C	16.7	0.27	0.815	77.2	0.89	0.95	1.19	0.382	0.017	0.0015	0.69	0.016
2	CTIF B1	15.15	0.202	0.92	82.90	0.072	0.088	.	0.063	0.037	0.030	0.444	0.055
1	IARM 310A	10.56	0.064	0.10	89.2	0.0009	0.006	(0.001)	0.043	0.094	0.0021	(0.002)	(0.001)
2	CURM 50.02	10.34	10.67	0.006	78.84	.	.	.	.	0.046	.	.	.
1	32X 52480A	10.33	0.329	0.397	88.54	.	0.020	.	0.369	0.0103	0.0071	0.0182	(0.002)
2	BS 905A-2	10.3	0.032	2.3	[87.3]	(<0.005)	0.014	(<0.005)	0.018	0.056	(0.004)	0.004	(<0.005)
2	BS 905A-3	10.3	0.033	2.3	[87.3]	(<0.005)	0.013	(<0.005)	0.018	0.052	(0.004)	0.004	(<0.005)
2	BS 905A-4	10.3	0.033	2.2	[87.3]	(<0.005)	0.012	(<0.005)	0.018	0.049	(0.004)	0.004	(<0.005)
2	BS 905A-1	10.25	0.030	2.27	87.3	(<0.003)	0.015	(<0.003)	0.018	0.055	.	0.004	(<0.004)
1	32X Sn7-22	10.0	1.28	0.025	87.4	.	.	.	1.22	0.030	0.003	0.0045	.
1	BS 937C	9.99	9.15	0.196	80.0	(0.0008)	0.0033	(0.0007)	0.26	0.0009	0.025	0.55	(0.002)
1	32X 93700A	9.95	8.38	0.78	80.43	.	0.0011	.	0.307	(0.0015)	0.0017	0.0051	.
1	NCS HS45742	9.79	1.43	2.88	Rem	0.037	0.191	.	0.153	0.56	.	0.288	0.010
1	IARM 92C	9.65	9.42	0.146	80.35	0.0013	(0.008)	(0.0016)	0.170	0.073	0.026	0.078	(0.0019)
1	32X LB12E	9.63	8.64	0.459	79.76	0.0337	0.029	.	0.354	0.240	0.053	0.484	0.0099
2	HRT CU2017	9.24	8.91	0.37	80.11	.	0.011	.	1.25	0.007	0.026	0.14	.
1	BS 929	9.07	1.98	0.0055	85.3	(<0.00005)	0.0030	(<0.00005)	3.37	0.119	0.0026	0.0146	(<0.001)
1	NCS HS45743	9.06	4.20	1.39	Rem	0.028	0.100	.	0.056	0.38	.	0.206	0.020
2	CURM 50.01	9.01	11.13	0.91	75.38	<0.0005	0.074	<0.001	1.93	0.069	0.188	0.50	<0.001

#	Number	Sn	Pb	Zn	Cu	Al	Fe	Mn	Ni	P	S	Sb	Si
---	--------	----	----	----	----	----	----	----	----	---	---	----	----

Number	Ag	As	Bi	C	Cd	Co	Cr	Mg	Se	Te	Units
32X SN5C	0.082	0.053	0.097	Au:0.011	0.121	0.110	0.011	.	(0.0009)	(0.0013)	~40 mm Ø x ~15 mm
CTIF B1	.	.	.	.	.	.	.	.	.	.	60 mm Ø x 5 mm
IARM 310A	0.0020	(0.002)	(0.001)	(0.005)	(0.001)	0.0011	(0.001)	.	(0.001)	.	31 mm Ø x 2 or 18 mm
CURM 50.02	.	.	.	.	.	.	.	.	.	.	50 mm Ø x 10-12 mm
32X 52480A	0.0131	.	0.0013	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm
BS 905A-2	0.002	0.002	.	(0.002)	.	.	.	.	.	.	38 mm Ø x 12 mm
BS 905A-3	(0.002)	0.002	.	(0.001)	.	.	.	.	.	.	38 mm Ø x 12 mm
BS 905A-4	(0.002)	0.002	.	(0.002)	.	.	.	.	.	.	38 mm Ø x 12 mm
BS 905A-1	(0.002)	(0.001)	.	.	.	.	.	.	.	.	38 mm Ø x 12 mm
32X Sn7-22	0.008	.	0.0028	.	.	.	.	.	.	.	38 mm Ø x 19 mm
BS 937C	(0.015)	0.0112	(0.018)	(0.0015)	(0.0002)	0.0006	(0.00004)	O:0.0060	(0.0008)	(0.0005)	38 mm Ø x 19+ mm 17025
32X 93700A	.	.	.	.	.	0.0004	.	.	.	.	~42 mm Ø x ~15 mm
NCS HS45742	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 30 mm
IARM 92C	(0.05)	(0.005)	(0.011)	(0.002)	.	(0.0007)	(0.0007)	.	(0.001)	.	31 mm Ø x 2 or 18 mm
32X LB12E	0.0450	0.112	0.0338	.	.	0.061	.	.	.	0.0215	~40 mm Ø x ~15 mm
HRT CU2017	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 20 mm
BS 929	(<0.005)	0.0017	(<0.005)	(<0.005)	.	0.0031	(<0.005)	.	O:0.0031	.	51 mm Ø x ~7 or 19+ mm 17025
NCS HS45743	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 30 mm
CURM 50.01	0.19	.	0.024	.	.	.	.	.	.	.	50 mm Ø x 10 - 12 mm

Number	Ag	As	Bi	C	Cd	Co	Cr	Mg	Se	Te	Units
--------	----	----	----	---	----	----	----	----	----	----	-------

available individually except IMN WL4 and WL5 are SET ONLY IMN BB: 10 mm Ø x 100 mm IMN BL: 40 mm Ø x 27 mm IMN BI, WL: 40 mm Ø x 25 mm

Number	Al	As	Bi	C	Cd	Co	Cu	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn
IMN BL1	0.11	0.058	0.024	.	0.060	.	Rem	0.38	0.051	0.062	0.25	0.49	0.25	(0.0081)	0.053	0.059	2.58	0.68
IMN BL2	0.15	0.039	0.014	.	0.040	.	Rem	0.21	0.11	0.055	0.37	0.29	0.14	(0.0063)	0.039	0.031	4.04	0.40
IMN BL3	0.019	0.025	0.0099	.	0.022	.	Rem	0.10	.	0.026	0.13	0.084	0.065	.	0.021	0.015	6.12	0.15
IMN BL4	.	0.0089	0.0058	.	0.0092	.	Rem	0.014	.	0.0092	0.015	0.010	0.013	(0.0022)	0.0095	0.011	8.38	0.017
IMN BL5	0.00052	0.00057	0.0015	.	0.0015	.	Rem	0.0061	0.0030	0.0011	0.0074	0.0042	0.0069	0.031	0.0039	(0.0038)	11.05	0.0078
IMN BB1	0.019	0.086	0.032	.	.	.	84.82	0.33	.	0.081	0.061	0.055	1.55	.	0.60	0.037	8.10	3.90
IMN BB2	0.032	0.12	0.024	.	.	.	84.09	0.28	.	0.12	0.097	0.085	2.64	.	0.49	0.055	7.11	4.70
IMN BB3	0.0021	0.0079	0.0021	.	.	.	80.88	0.037	.	0.0012	2.42	(0.014)	6.73	.	0.052	0.0044	3.36	6.23
IMN BB4	0.0062	0.029	0.011	.	.	.	81.32	0.086	.	0.020	1.20	0.030	6.14	.	0.21	0.018	2.58	8.11
IMN BB5	0.015	0.051	0.018	.	.	.	82.25	0.14	.	0.054	0.49	0.037	5.18	.	0.31	0.028	4.11	7.21
IMN BB6	0.040	0.16	0.041	.	.	.	83.54	0.31	.	0.15	0.23	0.12	3.52	.	0.62	0.083	5.47	5.40
IMN BI1	0.15	0.14	0.12	.	.	.	Rem	0.42	.	0.26	2.41	0.70	6.97	(0.011)	0.58	0.23	3.19	3.55
IMN BI2	0.077	0.11	0.070	.	.	.	Rem	0.31	.	0.15	1.46	0.59	5.39	(0.0055)	0.43	0.13	4.18	5.73
IMN BI3	0.034	0.052	0.028	.	.	.	Rem	0.17	.	0.082	0.29	0.32	4.52	(0.003)	0.24	0.075	5.01	7.16
IMN BI4	0.0020	0.010	0.0030	.	.	.	Rem	0.083	.	0.025	0.088	0.029	3.82	(0.002)	0.075	0.014	7.69	10.22
IMN WL1	0.082	0.0010	0.0093	0.0050	0.0017	0.0010	95.54	0.072	0.00036	0.0041	0.44	0.012	0.013	0.020	.	0.057	0.22	3.52
IMN WL2	0.057	0.0078	0.0073	0.0082	0.0023	0.0065	97.49	0.13	0.00097	0.0038	0.32	0.016	0.011	0.0070	0.0050	0.046	0.32	1.56
IMN WL3	0.0034	0.020	0.0050	0.010	0.010	0.0096	96.51	0.20	0.0016	0.38	0.22	0.021	0.0083	0.0088	0.0085	0.0037	0.37	2.21
IMN WL4	.	0.0034	0.0026	0.0032	0.0068	0.013	96.41	0.012	.	0.019	.	.	0.0066	0.0050	.	0.0019	0.55	2.97
IMN WL5	0.0014	0.0011	0.0011	.	0.0038	0.019	97.62	0.0025	.	0.00073	0.0014	.	0.0030	0.0019	0.0006	0.0009	0.73	1.61
IMN WL6	0.10	0.024	0.012	0.016	0.025	0.019	95.76	0.31	0.015	0.14	0.091	0.032	0.016	0.017	0.0011	0.13	0.80	2.48

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
101		IARM Cu101-18	630		IARM 80D	922		BS 922B-4
110	17034	BS 110C	632		CTIF CA26	922		BS 922B-5
110		IARM Cu110-18	642	17025	BS 642B	927.1		32X SN1
110		IARM 70C	642	17025	BS 642C	929	17025	BS 929
122.2		CURM 09.03	642	17034	BS 642D	929 MOD	17034	BS 929MOD
125		CURM 09.02	642		IARM 81B	931 MOD		C71.34
145	17025	BS 14500	642		IARM Cu648-18	932	17034	BS 932G
145	17034	BS 14500A	647		IARM Cu647-18	932	17034	BS 932H
172		BS 172Be-1	655		37X 65500	932		IARM 91E
172	17034	BS 172Be-2	655		BS 655A	932		IARM Cu932-18
172		CTIF 4872	655	17025	BS 655B	932 MOD		CTIF B23
172		IARM Cu172-18	655	17025	BS 655C	936	17025	BS 936
172		IARM Cu172-19	655		IARM 82B	936		CTIF B31
173		36X CBC4	655		IARM Cu655-18	937		32X 93700
175.1		36x CBC5	656.8		HRT Cu2021	937	17025	BS 937C
175.1	17034	BS 17510	675		BS 675	937		CURM 50.02
180		36X 274	675		BS 675A	937		IARM 92C
181.50	17025	BS 18150	675	17025	BS 675B	938		BS 938-1
181.50	17025	BS 18150A	675		IARM 83B	941		IARM 184A
181.55		36X CCR1	687		BAM 368	945 MOD		CTIF B32
182		IARM 279A	693		ERM-EB393A	947		IARM 267A
182		IARM Cu182-18	693		IARM 313A	952.2		CTIF 2152-5
240		C30.07	702.6		37X 218	953		CTIF CA3
260		C48.06	706		36X 70600A	954		BS 954B
260		CURM 48.04	706		BS 706	954		BS 954C
261.3		C48.03	706		BS 706A	954		BS CC954
274		C38.06	706		BS 706B	954		IARM Cu954-18
274		C38.06-1	706	17034	BS 706C	954		IARM Cu954-19
280		C30.03	706		CTIF CuNi 10	954		IARM Cu954-21
280		C30.12	706		IARM 84C	955		BS 955C
314		IARM 72B	706		HRT CU2014	955		IARM Cu955-18
360	17025	BS 360B	713		BAM 389	955 MOD		CTIF CA10
360	17034	BS 360C	715		36X 71500	955.1		IARM 334A
360	17034	BS 360D	715		BS 715A	955.1		IARM 334B
360		IARM Cu360-18	715	17034	BS 715B	955.1 MOD		CTIF CA22
360		SRM 1124	715	17034	BS 715C	956		32X CA12
370		31X B18	715		IARM Cu715-18	976		IARM 298A
371		C30.22	715		IARM Cu715-20			36X CN21
464		BS 464A	715		SRM 1276a			36X CN23
464	17034	BS 464B	767		C65.28			SRM C1252a
464		IARM Cu464-21	798.3		34X 79830			SRM C1251a
482		BS 482A	815		IARM 158C			SRM C1253a
482		IARM 75B	836	17034	BS 836B			HRT CU2022
482		IARM 75C	836	17034	BS 836C			IARM 226A
485	17034	BS 485A	836	17034	BS 836D			IARM 227A
485		IARM 76D	836		IARM Cu836-18			IARM 228A
485		IARM Cu485-18	836 + Al		IMN BR1			IARM 265A
486		IARM Cu486-18	838		33X GM8			IARM 264A
510		32X 51000	844		IARM Cu844-18			IARM 263A
510		BS 510A	855		31X B2N			IARM 266A
510	17025	BS 510B	855		31X TB3			IARM CuH130-18
510	17034	BS 510C	855		C38.01			IARM CuH191-18
510		IARM 77B	855		C38.02			IARM 159A
510		IARM Cu510-18	855		C38.03			IARM 160A
512		32X 92100	855		C38.04			36X SP1
521		32X 52100	855		C38.05			36X SP2
521		HRT CU2016	857		BS 857B-1			
524		C11.04	857		BS 857B-2			
544		33X 54400	857		BS 857B-3			
544	17025	BS 544B	857		BS 857B-4			
544	17034	BS 544C	862		CTIF LH7			
544		IARM 78B	863	17025	BS 863B			
544		IARM Cu544-18	863		IARM 88C			
544 MOD	17025	BS 544c	873		31X WSB6			
610 MOD		31X B17	893.2, Magnolia B		IARM CuMB1-18			
614		32X 61400	902		BAM 377			
623		32X CA7	903		BS 903B			
623		BS 623	903	17034	BS 903E			
623		BS 623A	903		IARM Cu903-18			
623		IARM 79B	905		BS 905A-1			
623		IARM 79C	905		BS 905A-2			
624		32X ALB3	905		BS 905A-3			
624	17034	BS 624	905		BS 905A-4			
624		C52.51	907		IARM 310A			
624		CTIF 3011-G	908		32X PB10			
624		CTIF CA21	910 MOD		CTIF B1			
630	17025	BS 630B	922		BS 922B-1			
630	17025	BS 630C	922		BS 922B-2			

Please use the Adobe Acrobat "search" function to find the complete chemistry of these samples listed within this catalog

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
101	Impurity limits	>99.99	<0.0025	.	<0.0010	<0.0005	<0.0010	<0.0003	<0.0005	<0.0018	<0.0004	.	<0.0002	<0.0001	<0.0005	.	<0.0001	.	.	.	.	.
102	Cu = Ag-Cu, O<0.0010	>99.95	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
103	Cu = Ag-Cu, O<0.0010	>99.95	.	.	.	.	.	0.001-0.005	.	.	.	.	.	.	.	.	.	.	.	.	.	.
104	Cu = Ag-Cu, O<0.0010	>99.95	>0.027	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
105	Cu = Ag-Cu, O<0.0010	>99.95	>0.034	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
107	Cu = Ag-Cu, O<0.0010	>99.95	>0.085	.	.	.	.	0.005-0.012	.	.	.	.	.	.	.	.	.	.	.	.	.	.
108	Cu = Ag-Cu+P	>99.95	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
109.1	Cu = Ag-Cu, O<0.005	>99.95	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
109.2	Cu = Ag-Cu, O<0.02	>99.90	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
109.3	Cu = Ag-Cu, O<0.02	>99.90	>0.044	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
109.4	Cu = Ag-Cu, O<0.02	>99.90	>0.085	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
110	Cu = Ag-Cu	>99.90	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
110.1	Cu = Ag-Cu	>99.90	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
110.2	Cu = Ag-Cu	>99.90	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
110.3	Cu = Ag-Cu	>99.90	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
110.4	Impurity limits, O 0.010-0.065	>99.90	<0.0025	.	<0.0010	.	<0.0010	.	<0.0005	<0.0015	<0.0004	.	<0.0005	.	<0.0005	.	<0.00010	.	.	.	.	.
111	Cu = Ag-Cu	>99.90	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
113	Cu = Ag-Cu	>99.90	>0.027	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
114	Cu = Ag-Cu	>99.90	>0.034	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
115	Cu = Ag-Cu	>99.90	>0.054	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
116	Cu = Ag-Cu	>99.90	>0.085	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
117	Cu = Cu+Bi, B 0.004-0.020	>99.90	.	.	.	.	.	<0.04	.	.	.	.	.	.	.	.	.	.	.	.	.	.
119.04	Cu = Ag-Cu	>99.90	>0.027	.	.	.	.	0.004-0.012	.	.	.	.	.	.	.	.	.	.	.	.	.	.
119.05	Cu = Ag-Cu	>99.90	>0.034	.	.	.	.	0.005-0.012	.	.	.	.	.	.	.	.	.	.	.	.	.	.
119.06	Cu = Ag-Cu	>99.90	>0.054	.	.	.	.	0.015-0.040	.	.	.	.	.	.	.	.	.	.	.	.	.	.
122.1	Cu = Ag-Cu	>99.90	.	.	.	.	.	0.015-0.025	.	.	.	.	.	.	.	.	.	.	.	.	.	.
122.2	Cu = Ag-Cu	>99.90	.	.	.	.	.	0.040-0.065	.	.	.	.	.	.	.	.	.	.	.	.	.	.
123	Cu = Ag-Cu	>99.90	.	.	.	.	.	0.015-0.040	.	.	.	.	.	.	.	.	.	.	.	.	.	.
125	Cu=Ag-Cu, Te+Se <0.025	>99.88	.	.	<0.05	.	<0.050	>0.03	<0.004	.	<0.003	.	<0.05	<0.080	<0.012	.	<0.003	.	.	.	.	.
125.1	Cu=Ag-Cu, Te+Se <0.025	>99.90	.	.	.	.	<0.050	.	<0.020	.	<0.003	.	.	.	<0.012	.	<0.005	.	.	.	.	.
127	Cu=Ag-Cu, Te+Se <0.025	>99.98	>0.027	.	.	.	<0.050	.	<0.004	.	<0.003	.	.	.	<0.012	.	<0.003	.	.	.	.	.
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
128	Cu=Ag-Cu, Te+Se <0.025	>99.88	>0.034	.	.	.	<0.050	.	<0.004	.	<0.003	.	.	.	<0.012	.	<0.003	.	.	.	.	.
129	Cu=Ag-Cu, Te+Se <0.025	>99.88	>0.054	.	.	.	<0.050	.	<0.004	.	<0.003	.	.	.	<0.012	.	<0.003	.	.	.	.	.
130	Cu=Ag-Cu, Te+Se <0.025	>99.88	>0.085	.	.	.	<0.050	.	<0.004	.	<0.003	.	.	.	<0.012	.	<0.003	.	.	.	.	.
131	Cu = Ag-Cu	>99.80	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
141	Cu = Ag-Cu	>99.40	.	.	.	.	.	.	.	.	.	.	.	.	0.15-0.50	.	.	.	.	.	.	.
141.8	Cu = Ag-Cu	>99.90	.	<0.01	.	.	.	<0.075	<0.02	.	.	.	.	.	.	.	.	.	.	.	.	.
141.81	Cu=Ag-Cu, C<0.005, Cd<0.002	>99.90	.	.	.	.	.	<0.002	<0.002	.	.	.	.	<0.002	.	.	.	.	.	.	.	.
142	Cu = Ag-Cu	>99.40	.	.	.	.	.	0.015-0.040	.	.	.	.	.	.	0.15-0.50	.	.	.	.	.	.	.
142.1	Cu = Ag-Cu	>99.20	.	.	.	.	.	0.013-0.050	.	.	.	.	.	.	0.30-0.50	.	.	.	.	.	.	.
143	Cu = Ag-Cu+Cd, Cd 0.05-0.15	>99.90	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
143.1	Cu = Ag-Cu+Cd, Cd 0.10-0.30	>99.90	.	.	<0.03	.	<0.05	0.013-0.025	.	.	<0.003	.	0.10-0.20	<0.05	.	.	.	.	.	.	.	.
144	Cu=Ag-Cu+Sn+P, Te+Se <0.02	>99.90	.	.	<0.05	.	.	0.005-0.020	<0.05	.	.	.	0.10-0.20	.	.	.	.	.	.	.	.	.
144.1	Cu = Ag-Cu+Sn	>99.90	.	.	.	.	.	.	.	.	.	.	0.10-0.15	.	.	.	.	.	.	.	.	.
144.15	Cu = Ag-Cu+Sn	>99.96	.	.	.	.	.	.	.	.	.	.	0.05-0.15	.	.	.	.	.	.	.	.	.
144.2	Cu=Ag-Cu+Sn+Te Te+Se 0.02-0.05	>99.90	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
144.3	Cu = Ag-Cu	>99.90	.	.	.	.	.	.	.	.	.	.	0.25-0.35	.	.	.	.	.	.	.	.	.
144.4	Cu = Ag-Cu+Sn	>99.96	.	.	.	.	.	.	.	.	.	.	0.005-0.010	.	.	.	.	.	.	.	.	.
145	Cu = Ag-Cu+Te, Te 0.40-0.70	>99.90	.	.	.	.	.	0.004-0.012	.	.	.	.	.	.	.	.	.	.	.	.	.	.
145.1	Cu = Ag-Cu+Te, Te 0.30-0.70	>99.85	.	.	.	.	.	0.010-0.030	<0.05	.	.	.	.	.	.	.	.	.	.	.	.	.
145.2	Cu = Ag-Cu+Te, Te 0.40-0.70	>99.40	.	.	.	.	.	0.004-0.020	.	.	.	.	.	.	.	.	.	.	.	.	.	.
145.3	Cu = Ag-Cu, Te 0.003-0.022	>99.95	.	.	.	.	.	0.001-0.005	.	.	.	.	0.003-0.22	.	.	.	.	.	.	.	.	.
147	Cu = Ag-Cu+P+S	>99.90	.	.	.	.	.	0.002-0.005	.	0.20-0.50	.	.	.	.	.	.	.	.	.	.	.	.
147.1	Cu = Ag-Cu+P+P+S	>99.90	.	.	.	.	.	0.010-0.030	<0.05	0.05-0.15	.	.	.	.	.	.	.	.	.	.	.	.
147.2	Cu = Ag-Cu+P+P+S	>99.50	.	.	.	.	.	0.10-0.03	<0.10	0.20-0.50	.	.	.	.	.	.	.	.	.	.	.	.
147.3		>99.80	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
150	Cu = Ag-Cu	>99.80	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
151	Cu = Ag-Cu	>99.80	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
151.5	Cu = Ag-Cu+Zn	>99.96	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
155	Cu = Ag-Cu	>99.75	0.027-0.10	.	.	.	.	0.040-0.080	.	.	.	.	.	.	.	.	.	.	.	.	.	.
156	Cu = Ag-Cu	>99.60	.	.	.	.	.	0.06-0.09	.	.	.	.	.	.	.	.	.	0.20-0.30	.	<0.02	.	.
157.1	Cu = Ag-Cu, O 0.07-0.15	>99.71	.	0.08-0.12	<0.01	.	.	.	<0.01	.	.	.	.	.	.	.	.	.	.	.	.	.
157.15	Cu = Ag-Cu, O 0.12-0.19	>99.62	.	0.13-0.17	<0.01	.	.	.	<0.01	.	.	.	.	.	.	.	.	.	.	.	.	.
157.15	Cu=Ag-Cu, B 1.2-1.8, O <0.19	>97.82	.	0.13-0.17	<0.01	.	.	.	<0.01	.	.	.	.	.	.	.	.	.	.	.	.	.
157.2	Cu = Ag-Cu, O 0.16-0.24	>95.52	.	0.18-0.22	<0.01	.	.	.	<0.01	.	.	.	.	.	.	.	.	.	.	.	.	.
157.25	Cu = Ag-Cu, O 0.20-0.28	>93.43	.	0.23-0.27	<0.01	.	.	.	<0.01	.	.	.	.	.	.	.	.	.	.	.	.	.
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
157.35	Cu = Ag-Cu, 0 0.29-0.37	>99.24		0.33-0.37	<0.01				<0.01													
157.6	Cu = Ag-Cu, 0 0.52-0.59	>98.77		0.58-0.62	<0.01				<0.01													
162	Cu = Ag-Cu, Cd 0.70-1.20	ren			<0.02																	
162.1	Cu = Ag-Cu, Cd 0.50-1.20	ren											0.20-0.40									
164	Cu = Tot. All, Cd 0.60-0.90	>99.80			<0.02																	
165	Cu = Ag-Cu, Cd 0.60-1.00	ren			<0.02								0.50-0.70									
170	Cu = Ag-Cu Ni+Co >0.20	ren		<0.20								<0.20				1.60-1.79						
172	Cu = Ag-Cu Ni+Co >0.20	ren		<0.20								<0.20				1.80-2.00						
173	Cu = Ag-Cu Ni+Co >0.20	ren		<0.20					0.20-0.60			<0.20				1.80-2.00						
174	Cu = Ag-Cu	ren		<0.20								<0.20				0.15-0.50						
174.1	Cu = Ag-Cu	ren		<0.20								<0.20				0.05-0.50						
174.2	Cu = Ag-Cu	ren		<0.20								<0.20				0.05-0.50						
174.5	Cu = Ag-Cu	ren		<0.20								<0.20				0.15-0.50						
174.55	Cu = Ag-Cu	ren		<0.20					0.20-0.60				<0.25			0.15-0.50						
174.6	Cu = Ag-Cu	ren		<0.20									<0.25			0.15-0.50						
174.65	Cu = Ag-Cu	ren		<0.20								<0.20				0.15-0.50						
175	Cu = Ag-Cu	ren		<0.20								<0.20				0.40-0.70						
175.1	Cu = Ag-Cu	ren		<0.20												0.20-0.60						
175.2	Cu = Ag-Cu	ren		<0.20												0.10-0.30						
175.3	Cu = Ag-Cu Ni = Ni+Co	ren		<0.6								<0.20				0.20-0.40						
176	Cu = Ag-Cu Te 0.40-0.60	ren	0.90-1.10	<0.20	<0.10							<0.20				0.25-0.50		1.4-1.7				
177	Cu = Ag-Cu Ni = Ni+Co	ren		<0.20	<0.10							<0.20				0.40-0.70		2.4-2.7				
180	Cu = Ag-Cu Ni = Ni+Co	ren			<0.15		2.0-3.0					0.40-0.80										
180.3	Cu = Ag-Cu	>99.90						0.005-0.150					0.08-0.12									
180.4	Cu = Ag-Cu	>99.90											0.20-0.30	0.05-0.15								
180.45	Cu = Ag-Cu	>99.10										<0.05	0.20-0.30	0.15-0.30								
180.5	Cu = Ag-Cu Te 0.005-0.015	>99.80																				
180.7	Cu = Ag-Cu	>99.00										0.02-0.07										
180.8	Cu = Ag-Cu	ren	0.01-0.30		0.02-0.20							0.01-0.10										
180.9	Cu = Ag-Cu	>96.00					0.30-1.20						0.50-1.20									
181	Cu = Ag-Cu	>98.70																				
181.35	Cu = Ag-Cu, Cd 0.20-0.60	ren																				
181.4	Cu = Ag-Cu	ren																				
181.45	Cu = Ag-Cu	ren																				
181.5	Cu = Ag-Cu	ren																				
181.55	Cu = Ag-Cu	ren																				
182	Cu = Ag-Cu	ren			<0.10				<0.05			<0.10										
184	Cu=Ag-Cu Ca<0.005 Li<0.05	ren			<0.15							<0.10										
185	Cu = Ag-Cu	ren	0.08-0.12						<0.015													
185.5	Cu = Ag-Cu	ren											0.10-0.14									
186	Cu = Ag-Cu	ren			0.25-0.80																	
186.1	Cu = Ag-Cu	ren			<0.10																	
186.65	Cu = Ag-Cu	>99.00																				
187	Cu = Ag-Cu	ren																				
188.35	Cu = Ag-Cu	>99.00			<0.10								0.15-0.55	<0.30								
189	Cu = Ag-Cu	ren		<0.01																		
189.8	Cu = Ag-Cu	>98.00										0.15-0.40	0.6-0.9	<0.10								
189.9	Cu = Ag-Cu	ren										<0.50	<1.00									
190	Cu = Ag-Cu	ren			<0.10								1.8-2.2									
190.1	Cu = Ag-Cu	ren										0.15-0.35										
190.15	Cu = Ag-Cu	ren																				
190.2	Cu = Ag-Cu Mn+Si <0.35	ren																				
190.25	Cu = Ag-Cu	ren			<0.10								0.30-0.90									
190.3	Cu = Ag-Cu	ren			<0.10								0.7-1.1	<0.20								
191	Cu = Ag-Cu Te 0.35-0.60	ren			<0.20								1.0-1.5	<0.50								
191.4	Cu = Ag-Cu	ren			<0.05								<0.05	<0.50								
191.6	Cu = Ag-Cu	ren			<0.05								<0.05	<0.50								
192	Cu = Ag-Cu	>98.70			0.8-1.2									<0.20								
192.1	Cu = Ag-Cu	ren			0.05-0.15																	
192.15	Cu = Ag-Cu	ren			0.05-0.20																	
192.2	B 0.005-0.015	ren			0.10-0.30																	
192.5	B 0.005-0.025	ren			0.05-0.40								0.05-0.10									
192.6		>98.50			0.40-0.80								0.05-0.20									
192.8		ren			0.50-1.50								0.30-0.70	0.30-0.70								
194		>97.00			2.1-2.6									0.05-0.20								
194.1		ren			1.8-2.3								0.6-0.9									
194.5		ren			1.5-3.0								0.8-2.5									
195		>96.00			1.0-2.0								0.10-1.00	<0.20								
195.2		>96.60			0.50-1.50								0.50-1.50									
196		ren			0.9-1.2									<0.35								
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
197.1	Ni+Co <0.10	rem	.	.	0.30-1.20	<0.05	<0.05	0.10-0.40	<0.05	.	.	.	<0.02	<0.20	.	.	.	<0.05	.	0.01-0.20	.	.
197.2	Ni+Co <0.10	rem	.	.	0.05-0.40	<0.05	<0.10	0.07-0.15	<0.05	.	.	.	<0.20	<0.20	.	.	.	.	.	0.03-0.06	.	.
197.5		rem	.	.	0.05-0.50	<0.05	<0.10	0.05-0.15	<0.05	.	.	.	<0.20	<0.20	.	.	.	.	.	0.06-0.20	.	.
198		rem	.	.	0.35-1.20	<0.05	<0.05	0.10-0.40	<0.05	.	.	.	0.05-0.40	<0.20	.	.	.	<0.05	.	0.01-0.20	.	.
		rem	.	.	0.02-0.50	.	.	0.01-0.10	.	.	.	.	0.10-1.00	0.30-1.50	.	.	.	.	.	0.10-1.00	.	.
198.1		rem	.	.	1.5-3.0	.	.	<0.10	.	.	.	.	.	1.0-5.0	.	.	.	.	<0.10	<0.10	<0.10	<0.10
199	>99.50		.	.		.	.		.	.	.	.	.	rem	.	.	.	.	.	.	2.9-3.4	.
205			.	.	<0.05	.	.	.	<0.02	.	.	.	.	rem	.	.	.	.	.	.	.	.
210			.	.	<0.05	.	.	.	<0.03	.	.	.	.	rem	.	.	.	.	.	.	.	.
220			.	.	<0.05	.	.	.	<0.05	.	.	.	.	rem	.	.	.	.	.	.	.	.
226			.	.	<0.05	.	.	.	<0.05	.	.	.	.	rem	.	.	.	.	.	.	.	.
230			.	.	<0.05	.	.	.	<0.05	.	.	.	.	rem	.	.	.	.	.	.	.	.
230.3			.	.	<0.05	.	.	.	<0.05	.	.	0.20-0.40	.	rem	.	.	.	.	.	.	.	.
234			.	.	<0.05	.	.	.	<0.05	.	.	.	.	rem	.	.	.	.	.	.	.	.
240			.	.	<0.05	.	.	.	<0.05	.	.	.	.	rem	.	.	.	.	.	.	.	.
240.8			.	<0.10	.	.	.	.	<0.20	.	.	.	.	rem	.	.	.	.	.	.	.	.
250			.	.	<0.05	.	.	.	<0.05	.	.	.	.	rem	.	.	.	.	.	.	.	.
256			.	.	<0.05	.	.	.	<0.05	.	.	.	.	rem	.	.	.	.	.	.	.	.
260			.	.	<0.05	.	.	.	<0.07	.	.	.	.	rem	.	.	.	.	.	.	.	.
261			.	.	<0.05	.	.	0.02-0.05	<0.05	.	.	.	.	rem	.	.	.	.	.	.	.	.
261.3			.	.	<0.05	.	.	.	<0.05	.	.	.	.	rem	0.02-0.08	.	.	.	.	.	.	.
262			.	.	<0.05	.	.	.	<0.07	.	.	.	.	rem	.	.	.	.	.	.	.	.
263.8			.	<0.10	.	.	.	.	<0.30	.	.	.	.	rem	.	.	.	.	.	.	.	.
268			.	.	<0.05	.	.	.	<0.03	.	.	.	.	rem	.	.	.	.	.	.	.	.
270			.	.	<0.05	.	.	.	<0.15	.	.	.	.	rem	.	.	.	.	.	.	.	.
			.	.	<0.07	.	.	.	<0.10	.	.	.	.	rem	.	.	.	.	.	.	.	.
272			.	.	<0.07	.	.	.	<0.07	.	.	.	.	rem	.	.	.	.	.	.	.	.
274			.	.	<0.05	.	.	.	<0.10	.	.	.	.	rem	.	.	.	.	.	.	.	.
280			.	.	<0.07	.	.	.	<0.30	.	.	.	.	rem	.	.	.	.	.	.	.	.
282			.	<0.005	<0.05	.	.	0.12-0.22	<0.03	.	.	.	<0.05	rem	.	.	.	.	.	.	.	.
285.8			.	<0.10	<0.10	.	.	.	<0.50	.	.	.	.	rem	.	.	.	.	.	.	.	.
298			.	<0.10	<0.10	.	.	.	<0.50	.	.	.	.	rem	.	.	.	.	.	.	.	.
310			.	.	<0.10	.	.	.	0.30-0.70	.	.	.	.	rem	.	.	.	.	.	.	.	.
312			.	.	<0.10	.	.	.	0.7-1.2	.	.	.	.	rem	.	.	.	.	.	.	.	.
314			.	.	<0.10	.	.	.	1.3-2.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
316			.	.	<0.10	.	.	0.04-0.10	1.3-2.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
			.	.	<0.10	.	.	.	.	.	.	.	.	rem	.	.	.	.	.	.	.	.
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
320		83.5-86.5	.	.	<0.10	.	<0.25	.	1.5-2.2	.	.	.	.	rem	.	.	.	.	.	.	.	.
325		72.0-74.5	.	.	<0.10	.	.	.	2.5-3.0	.	.	.	.	rem	.	.	.	.	.	.	.	.
325.1		69.0-72.0	.	.	.	.	.	.	0.30-0.70	.	.	.	.	rem	0.02-0.06	.	.	.	.	.	.	.
330		65.0-68.0	.	.	<0.07	.	.	.	0.25-0.70	.	.	.	.	rem	.	.	.	.	.	.	.	.
331		65.0-68.0	.	.	<0.06	.	.	.	0.8-1.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
332		65.0-68.0	.	.	<0.07	.	.	.	1.5-2.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
335		62.0-65.0	.	.	<0.15	.	.	.	0.25-0.70	.	.	.	.	rem	.	.	.	.	.	.	.	.
335.3		62.5-66.5	.	.	<0.10	.	.	.	0.30-0.80	.	.	.	.	rem	0.02-0.06	.	.	.	.	.	.	.
340		62.0-65.0	.	.	<0.15	.	.	.	0.8-1.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
342		62.0-65.0	.	.	<0.15	.	.	.	1.5-2.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
344		62.0-66.0	.	.	<0.10	.	.	.	0.50-1.00	.	.	.	.	rem	.	.	.	.	.	.	.	.
345		62.0-65.0	.	.	<0.15	.	.	.	1.5-2.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
347		62.5-64.5	.	.	<0.10	.	.	.	1.0-1.8	.	.	.	.	rem	.	.	.	.	.	.	.	.
348		61.5-63.5	.	.	<0.10	.	.	.	0.40-0.80	.	.	.	.	rem	.	.	.	.	.	.	.	.
349		61.0-64.0	.	.	<0.10	.	.	.	0.10-0.50	.	.	.	.	rem	.	.	.	.	.	.	.	.
350		60.0-63.0	.	.	<0.15	.	.	.	0.8-2.0	.	.	.	.	rem	.	.	.	.	.	.	.	.
353		60.0-63.0	.	.	<0.15	.	.	.	1.5-2.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
353.3		60.5-64.0	.	.	.	.	.	.	1.5-3.5	.	.	.	.	rem	0.02-0.25	.	.	.	.	.	.	.
353.4		60.0-63.0	.	.	0.10-0.30	.	.	.	1.5-2.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
356		60.0-63.0	.	.	<0.15	.	.	.	2.0-3.0	.	.	.	.	rem	.	.	.	.	.	.	.	.
360		60.0-63.0	.	.	<0.35	.	.	.	2.5-3.7	.	.	.	.	rem	.	.	.	.	.	.	.	.
362		60.0-63.0	.	.	<0.15	.	.	.	3.5-4.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
365		58.0-61.0	.	.	<0.15	.	.	.	0.25-0.70	.	.	.	<0.25	rem	.	.	.	.	.	.	.	.
366		58.0-61.0	.	.	<0.15	.	.	.	0.25-0.70	.	.	.	.	rem	0.02-0.06	.	.	.	.	.	.	.
367		58.0-61.0	.	.	<0.15	.	.	.	0.24-0.70	.	0.02-0.10	.	<0.25	rem	.	.	.	.	.	.	.	.
368		58.0-61.0	.	.	<0.15	.	.	0.02-0.10	0.25-0.70	.	.	.	<0.25	rem	.	.	.	.	.	.	.	.
370		59.0-62.0	.	.	<0.15	.	.	.	0.8-1.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
371		58.0-62.0	.	.	<0.15	.	.	.	0.6-1.2	.	.	.	.	rem	.	.	.	.	.	.	.	.
377		58.0-61.0	.	.	<0.30	.	.	.	1.5-2.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
377.1		56.5-60.0	.	.	<0.30	.	.	.	1.0-2.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
378		56.0-59.0	.	.	<0.30	.	.	.	1.5-2.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
380		55.0-60.0	.	<0.50	<0.35	.	.	.	1.5-2.5	.	.	.	<0.30	rem	.	.	.	.	.	.	.	.
380.1		55.0-60.0	.	0.10-0.60	<0.30	.	.	.	1.5-3.0	.	.	.	.	rem	.	.	.	.	.	.	.	.
385		55.0-59.0	.	.	<0.35	.	.	.	2.5-3.5	.	.	.	.	rem	.	.	.	.	.	.	.	.
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
385.1		56.0-60.0							2.5-4.5												
385.9		56.5-60.0			<0.35				2.0-3.5												
386		56.0-59.0			<0.35				2.5-3.5		<0.02										
404		rem											0.35-0.70								
405		94.0-96.0			<0.05				<0.05				0.7-1.3								
408		94.0-96.0			<0.05				<0.05				1.8-2.2								
408.1		94.5-96.5			0.08-0.12			0.11-0.20	0.028-0.040				1.8-2.2								
408.2		>94.00						0.10-0.50	<0.05				1.0-2.5								
408.5		94.5-96.5			0.05-0.20			0.05-0.20	0.02-0.04				2.6-4.0								
408.6		94.0-96.0			0.01-0.05			0.05-0.20	0.02-0.04				1.7-2.3								
409		92.0-94.0			<0.05				<0.05				0.50-0.80								
410		91.0-93.0			<0.05				<0.05				2.0-2.8								
411		89.0-92.0			<0.05				<0.10				0.30-0.70								
411.2		89.0-92.0			0.05-0.20			0.05-0.20	0.02-0.05				0.30-0.70								
413		89.0-93.0			<0.05				<0.10				0.7-1.3								
415		89.0-93.0			<0.05				<0.10				1.5-2.2								
419		89.0-92.0			<0.05				<0.10				4.8-5.5								
420		88.0-91.0			<0.05			<0.25	<0.05				1.5-2.0								
421		87.5-89.0			<0.05	0.15-0.35		<0.35	<0.05				2.2-3.0								
422		86.0-89.0			<0.05			<0.35	<0.05				0.8-1.4								
422.2		88.0-91.0			0.05-0.20			0.02-0.05	<0.05				0.7-1.4								
425		87.0-90.0			<0.05			<0.35	<0.05				1.5-3.0								
425.2		88.0-91.0			0.05-0.20			0.02-0.04	<0.05				1.5-3.0								
426	Ni = Ni+Co	87.0-90.0			0.05-0.20			0.05-0.20	0.02-0.05				2.5-4.0								
430		84.0-87.0			<0.05				<0.10				1.7-2.7								
432		85.0-88.0			<0.05			<0.35	<0.05				0.40-0.60								
434		84.0-87.0			<0.05				<0.05				0.40-1.00								
435		79.0-83.0			<0.05				<0.10				0.6-1.2								
436		80.0-83.0			<0.05				<0.05				0.20-0.50								
438		79.0-82.0			<0.05				<0.05				1.0-1.5								
442.5		73.0-76.0			<0.20		<0.20	<0.10	<0.07				0.50-1.50								
443		70.0-73.0			<0.06				<0.07		0.02-0.10		0.8-1.2								
444		70.0-73.0			<0.06			0.02-0.10	<0.07				0.8-1.2								
445		70.0-73.0			<0.06			0.10-0.30	<0.07				0.8-1.2								
454.5		65.0-66.0		0.20-0.40									0.10-0.30								
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
462		62.0-65.0			<0.10				<0.20				0.50-1.00								
462.1		61.0-64.0		<0.03					<0.05			<0.50	<1.00								
464		59.0-62.0			<0.10				<0.20				0.50-1.00								
464.2		61.0-63.5			<0.20				<0.20				1.0-1.4								
465		59.0-62.0			<0.10				<0.20				0.50-1.00								
466		59.0-62.0			<0.10				<0.20		0.02-0.10		0.50-1.00								
467		59.0-62.0			<0.10			0.02-0.10	<0.20				0.50-1.00								
470		57.0-61.0		<0.01	<0.10				<0.05				0.25-1.00								
472		49.0-52.0			<0.10				<0.50				3.0-4.0								
476		86.0-88.0			<0.05	0.05-0.15		0.03-0.07	1.8-2.2				1.8-2.2								
479.4	Ni = Ni+Co	63.0-66.0			0.10-1.00		0.10-0.50		1.0-2.0				1.2-2.0								
482		59.0-62.0			<0.10				0.40-1.00				0.50-1.00								
485		59.0-62.0			<0.10				1.3-2.2				0.50-1.00								
485.1		59.0-62.0							1.0-2.5				0.7-1.5								
486		59.0-62.0							1.0-2.5				0.8-1.5								
490.8		49.0-52.0		<0.10					<0.50				3.0-4.0								
501		rem			<0.05			0.01-0.05	<0.05				0.50-0.80								
502		rem			<0.10			<0.04	<0.05				1.0-1.5								
505		rem			<0.10			0.03-0.35	<0.05				1.0-1.7								
505.1		rem						0.15-0.40	0.02-0.07				1.0-1.5								
505.8		rem			0.05-0.20		0.05-0.20	0.02-0.10	<0.05				1.0-1.7								
505.9		>97.00			0.05-0.40			0.02-0.15	<0.02				0.5-1.5								
507		rem			<0.10			<0.30	<0.05				1.5-2.0								
507.05		>96.50			0.10-0.40			0.04-0.15	<0.02				1.5-2.0								
507.1		rem					0.10-0.40	<0.15					1.7-2.3								
507.15		rem			0.05-0.15			0.025-0.040	<0.02				1.7-2.3								
507.25		>94.00			0.05-0.20			0.02-0.06	<0.02				1.5-2.5								
507.8		rem			0.05-0.20		0.05-0.20	0.020-0.100	<0.05				1.7-2.3								
508		rem			<0.10			0.01-0.07	<0.05				2.6-3.4								
509		rem			<0.10			0.03-0.30	<0.05				2.5-3.8								
510		rem			<0.10			0.03-0.35	<0.05				4.2-5.8								
510.8		rem			0.05-0.20		0.05-0.20	0.02-0.10	<0.05				4.8-5.8								
511		rem			<0.10			0.03-0.35	<0.05				3.5-4.9								
511.8		rem			0.05-0.20		0.11-0.20	0.02-0.10	<0.05				3.5-4.9								
511.9		rem			0.05-0.15			0.025-0.045	<0.02				3.0-6.5				<0.15				
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	As	Be	Bi	Co	Cr	Mg	Ti	Zr

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
518		ren		<0.01	<0.10			0.10-0.35	<0.02				4.0-6.0									
519		ren			<0.10			0.03-0.35	<0.05				5.0-7.0	<0.30								
519.8		ren			0.05-0.20			0.02-0.10	<0.05				5.0-7.0	<0.30								
521		ren			<0.10			0.03-0.35	<0.05				7.0-9.0	<0.20								
521.8		ren			0.05-0.20			0.02-0.10	<0.05				7.0-9.0	<0.30								
524		ren			<0.10			0.03-0.35	<0.05				9.0-11.0	<0.20								
524.8	Cu-Mn-P-Sn >99.5	ren			0.05-0.20			0.02-0.10	<0.05				9.0-11.0	<0.30								
526		ren			<0.10	1.0-2.0		0.03-0.35	<0.05				2.2-3.3	<0.20								
529	Cu-Mn-P-Sn >99.5	ren			<0.10	1.0-2.0		0.03-0.35	<0.05				7.0-9.0	<0.20								
532		ren			<0.10			0.03-0.35	2.5-4.0				4.0-5.5	<0.20								
534		ren			<0.10			0.03-0.35	0.8-1.2				3.5-5.8	<0.30								
544		ren			<0.10			0.01-0.50	3.5-4.5				3.5-4.5	1.5-4.5								
546	Cu-P-Pb-Sn-Zn >99.5				<0.10			<0.50	3.5-4.5				3.5-4.5	1.5-4.5								
548	Cu-P-Pb-Sn-Zn >99.5				<0.10			0.03-0.35	4.0-6.0				4.0-6.0	<0.30								
551.8	Cu-P >99.85	ren						4.8-5.2														
551.81	Cu-P >99.85	ren						7.0-7.5														
552.8		ren	1.80-2.20					6.8-7.2														
552.81		ren	4.80-5.20					5.8-6.2														
552.82		ren	4.80-5.20					6.5-7.0														
552.83		ren	5.80-6.20					7.0-7.5														
552.84		ren	14.5-15.5					4.8-5.2														
552.85		ren	17.2-18.0					6.0-6.7						30-34								
560		ren	29-31																			
606		ren		4.0-7.0	<0.50																	
607		ren		2.3-2.9					<0.01				1.7-2.0									
608		ren		5.0-6.5	<0.10				<0.10						0.20-0.35							
610		ren		6.0-8.5	<0.50				<0.02					<0.20								
613		ren		6.0-7.5	2.0-3.0	<0.20	<0.15	<0.015	<0.01			<0.10	0.20-0.50	<0.10								
614		ren		6.0-8.0	1.5-3.5	<1.00		<0.015	<0.01					<0.20								
615	Cu = Ag-Cu	ren		7.7-8.3			1.8-2.2		<0.015													
615.5	Cu = Ag-Cu	ren		5.5-6.5	<0.20		1.5-2.5		<0.05				<0.50	<0.80								
618	Cu = Ag-Cu	ren		8.5-11.0	0.50-1.50				<0.02				<0.10	<0.02								
619	Cu = Ag-Cu	ren		8.5-10.0	3.0-4.5				<0.02				<0.60	<0.80								
622	Cu = Ag-Cu	ren		11.0-12.0	3.0-4.2				<0.02				<0.10	<0.02								
623	Cu = Ag-Cu	ren		8.5-10.0	2.0-4.0	<0.50	<1.0						<0.60									
624	Cu = Ag-Cu	ren		10.0-11.5	2.0-4.5	<0.30							<0.25									
625	Cu = Ag-Cu	ren		12.5-13.5	3.5-5.0	<2.00																
625.8	Cu = Ag-Cu	ren		12.0-13.0	3.0-5.0				<0.02													
625.81	Cu = Ag-Cu	ren		13.0-14.0	3.0-5.0				<0.02													
625.82	Cu = Ag-Cu	ren		14.0-15.0	3.0-5.0				<0.02													
627.3	Cu = Ag-Cu	ren		8.5-11.0	4.0-6.0	<0.50	4.0-6.0		<0.05				<0.10	<0.40						<0.05		
630	Cu = Ag-Cu	ren		9.0-11.0	2.0-4.0	<1.50	4.0-5.5						<0.20	<0.30								
630.1	Cu = Ag-Cu	ren		9.7-10.9	2.0-3.5	<1.50	4.5-5.5						<0.20	<0.30								
630.2	Cu = Ag-Cu	ren		10.5-11.5	4.0-5.5	<1.50	4.2-6.0		<0.03				<0.15	<0.25				<0.20	<0.05			
632	Cu = Ag-Cu	ren		8.7-9.5	3.5-4.3	1.2-2.0	4.0-4.8		<0.02				<0.10									
632.3	Cu = Ag-Cu	ren	75.9-84.5	8.5-9.5	3.0-5.0	<3.50	4.0-5.5		<0.02													
632.8	Cu = Ag-Cu	ren		8.5-9.5	3.0-5.0	0.6-3.5	4.0-5.5		<0.02													
633	Cu = Ag-Cu	ren		5.0-7.5	2.0-6.0	11.0-13.0	1.0-2.5		<0.02													
633.8	Cu = Ag-Cu	ren		7.0-8.5	2.0-4.0	11.0-14.0	1.5-3.0		<0.02													
634	Cu = Ag-Cu	ren		2.6-3.2	<0.15		<0.15		<0.05				0.25-0.45	<0.20	<0.15							
636	Cu = Ag-Cu	ren		3.0-4.0	<0.15	<0.10	<0.15		<0.05				0.7-1.3	<0.20	<0.15			0.25-0.55				
638	Cu = Ag-Cu	ren		2.5-3.1	<0.20	<0.10	<0.20		<0.05				1.5-2.1	<0.80								
641.1	Cu = Ag-Cu	ren		8.0-11.0	<0.50	<0.50	<0.25		1.0-2.0													
642	Cu = Ag-Cu	ren		6.3-7.6	<0.30	<0.10	<0.25		<0.05				1.5-2.2	<0.20	<0.15							
642.1	Cu = Ag-Cu	ren		6.3-7.0	<0.30	<0.10	<0.25		<0.05				1.5-2.0	<0.20	<0.15							
642.5	Cu = Ag-Cu	ren		5.5-7.5	<1.00	<0.50	<0.50						1.5-3.0									
644	Cu = Ag-Cu	ren		3.5-4.5	<0.05		4.2-5.0		<0.03				0.8-1.3	<0.10								
647	Cu = Ag-Cu	ren			<0.10		1.6-2.2		<0.10				0.40-0.80	<0.50								
647.1	Cu = Ag-Cu	ren				<0.10	2.9-3.5						0.50-0.90									
647.2	Cu = Ag-Cu	ren					1.6-2.2						0.35-0.60	0.10-0.40					0.01-0.03			
647.25	Cu = Ag-Cu	ren			<0.25		1.3-2.7		<0.01				0.20-0.80	0.50-1.50					<0.20			
647.3	Cu = Ag-Cu	ren			<0.10	<0.10	2.9-3.5		<0.01				0.50-0.90	1.0-1.5								
647.4	Cu = Ag-Cu	ren			<0.10	<0.10	1.0-2.0		<0.01				0.05-0.50	1.5-2.5						<0.05		
647.5	Cu = Ag-Cu	ren			<1.00		1.0-3.0		<0.10				0.10-0.70	0.05-0.80								<0.10
647.6	Cu = Ag-Cu	ren			0.10-0.40		0.40-2.50		<0.02				0.05-0.60	<0.30								
647.8	Cu = Ag-Cu	ren				0.01-1.00	1.0-3.5		<0.02				0.20-0.90	0.10-2.00					<0.01			<0.01
649	Cu = Ag-Cu	ren		<0.10	<0.10	<0.10	<0.10		<0.05				0.8-1.2	1.2-1.6								
651	Cu = Ag-Cu	ren		<0.80	<0.70				<0.05				0.8-2.0	<1.50								
653	Cu = Ag-Cu	ren			<0.80				<0.05				2.0-2.6									
654	Cu = Ag-Cu	ren							<0.05				1.2-1.9	<0.50					0.01-0.12			
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
655	Cu = Ag-Cu	rem			<0.80	0.50-1.30	<0.6		<0.05			2.8-3.8	<1.50	<1.50								
656	Cu = Ag-Cu	rem		<0.01	<0.50	<1.50			<0.02			2.8-4.0	<1.50	<1.50								
656.2	Cu = Ag-Cu	>90.00			1.0-2.0	<1.00		<0.10				2.4-4.0		1.5-4.0								
658	Cu = Ag-Cu	rem			<0.25	0.50-1.30	<0.6		<0.05			2.8-3.8										
661	Cu = Ag-Cu	rem			<0.25	<1.50			0.20-0.80			2.8-3.5		<1.50								
662	Cu = Ag-Cu	86.6-91.0			<0.05		0.30-1.00	0.05-0.20	<0.05				0.20-0.70	rem				<0.20				
663	Cu = Ag-Cu	84.5-87.5			1.3-1.7		<0.05	<0.02	<0.05			<0.05	<0.05	11.0-12.0				0.30-0.70				
664	Cu = Ag-Cu	rem			1.8-2.3		<0.05	<0.02	<0.015			<0.05	<0.05	11.0-12.0								
664.1	Cu = Ag-Cu	rem		<0.05	0.50-1.50				<0.015					12.7-17.0								
667	Cu = Ag-Cu	68.5-71.5		<0.25	<0.10	0.8-1.5	<0.25		<0.07				<0.30	rem								
668	Cu = Ag-Cu	60.0-63.0		<0.25	<0.35	2.0-3.5	<0.25		<0.05			0.50-1.50	<0.30	rem								
669	Cu = Ag-Cu	62.5-64.5			<0.25	11.5-12.5			<0.05					rem								
669.5	Cu = Ag-Cu	rem		1.0-1.5	<0.50	14.0-15.0			<0.01					14.0-15.0								
670	Cu = Ag-Cu	63.0-68.0			2.0-4.0	2.5-5.0			<0.20				<0.50	rem								
671.3	Cu = Ag-Cu	56.0-59.0		0.10-1.00		0.50-1.50	0.50-1.50		0.50-1.50			0.50-1.50	<0.50	rem								
673	Cu = Ag-Cu	58.0-63.0		<0.25	<0.50	2.0-3.5	<0.25		0.40-3.00			0.50-1.50	<0.30	rem								
674	Cu = Ag-Cu	57.0-60.0		0.50-2.00	<0.35	2.0-3.5	<0.25		<0.50			0.50-1.50	<0.30	rem								
674.1	Cu = Ag-Cu	55.5-59.0		1.3-2.3	<1.00	1.0-2.4	<2.0		<0.8			0.7-1.3	<0.50	rem								
674.2	Cu = Ag-Cu	57.0-58.5		1.0-2.0	0.15-0.55	1.5-2.5	<0.25		0.25-0.80			0.25-0.70	<0.35	rem								
675	Cu = Ag-Cu	57.0-60.0		<0.25	0.8-2.0	0.05-0.50			<0.20				0.50-1.50	rem								
676	Cu = Ag-Cu	57.0-60.0			0.40-1.30	0.05-0.50			0.50-1.00				0.05-1.50	rem								
676.2	Cu = Ag-Cu	55.0-57.0			0.50-1.20	1.0-2.0			0.50-1.50					rem								
677	Cu = Ag-Cu	55.5-58.0			0.7-1.5	0.05-0.30	1.5-2.3		0.50-1.00				<0.20	rem				0.04-0.80				
678	Cu = Ag-Cu	56.0-59.0		0.30-1.50	0.7-1.5	0.20-0.60			<0.30					rem								
678.1	Cu = Ag-Cu	56.5-59.5		0.40-1.60	<1.00	0.40-1.80	<1.5		<1.0			<0.60	<0.50	rem								
678.2	Cu = Ag-Cu	56.5-59.5		0.30-1.30	0.50-1.20	0.30-2.00			<0.50				0.30-1.00	rem								
680	Cu = Ag-Cu	56.0-60.0		<0.01	0.25-1.25	0.01-0.50	0.20-0.80		<0.05			0.04-0.15	0.75-1.10	rem								
681	Cu = Ag-Cu	56.0-60.0			0.25-1.25	0.01-0.50			<0.05			0.04-0.15	0.75-1.10	rem								
682	Cu = Ag-Cu	58.0-60.0		<0.01	0.6-1.0	0.6-1.0						0.07-0.15		rem								
686	Cu = Ag-Cu	56.0-60.0		0.30-1.50	0.50-1.20	0.30-2.00			0.50-1.50				0.20-1.00	rem								
687	Cu = Ag-Cu	76.0-79.0		1.8-2.5	<0.06				<0.07					rem								
688	Cu = Ag-Cu	3.0-3.8			<0.20				<0.05					21.3-24.1				0.25-0.55				
690	Cu = Ag-Cu	72.0-74.6		3.0-3.8	<0.05		0.50-0.80		<0.025			0.10-0.60		rem								
690.5	Cu = Ag-Cu	70.0-75.0		3.0-4.0			0.50-1.50							rem								0.01-0.20
691	Cu = Ag-Cu	81.0-84.0		0.7-1.2	<0.25	<0.10	0.8-1.4		<0.05			0.8-1.3	<0.10	rem								
694	Cu = Ag-Cu	80.0-83.0			<0.20				<0.30			3.5-4.5		rem								
694.3	Cu = Ag-Cu	80.0-83.0			<0.20				<0.30			3.5-4.5		rem								
694.4	Cu = Ag-Cu	80.0-83.0			<0.20				<0.30			3.5-4.5		rem								
694.5	Cu = Ag-Cu	80.0-83.0			<0.20	<0.40		0.03-0.06	<0.30			3.5-4.5		rem								
697	Cu = Ag-Cu	75.0-80.0			<0.20	<0.40			0.50-1.50			2.5-3.5		rem								
697.1	Cu = Ag-Cu	75.0-80.0			<0.20	<0.40			0.50-1.50			2.5-3.5		rem								
697.2	Cu = Ag-Cu	75.0-80.0			<0.20	<0.40			0.50-1.50			2.5-3.5		rem								
697.3	Cu = Ag-Cu	75.0-80.0			<0.20	<0.40		0.03-0.06	0.50-1.50			2.5-3.5		rem								
698	Cu = Ag-Cu	66.0-70.0			<0.4		<0.50		<0.8			0.7-1.3		rem								
699	Cu=Ag-Cu; C, Cd <0.05	<0.05		1.4-2.3	<0.10	40.0-48.0	<0.10		<0.02					<0.14	<0.01		<0.20					
699.1	Cu = Ag-Cu	rem		0.25-0.80	1.0-1.4	28.0-32.0			<0.01					3.0-5.0								
699.5	Cu = Ag-Cu	51.0-54.0			36.0-40.0	8.5-10.5								<0.25								
701	Cu = Ag-Cu	rem			<0.05	<0.50	3.0-4.0															
702	Cu = Ag-Cu	rem			<0.10	<0.40	2.0-3.0		<0.05													
702.3	Cu = Ag-Cu	rem			<0.10	<0.40	2.2-3.2					0.40-0.80	0.10-0.50	0.50-2.00					0.05-0.30			
702.5	Cu = Ag-Cu	rem			<0.20	<0.10	2.2-4.2		<0.05			0.25-1.20		<1.00								
702.6	Cu = Ag-Cu	rem				<0.10	1.0-3.0	<0.01				0.20-0.70		<1.00								
702.7	Cu = Ag-Cu	rem			0.28-1.00	<0.15	1.0-3.0		<0.05			0.20-1.00	0.10-1.00	<1.00								
702.8	Cu = Ag-Cu	rem			<0.015		1.3-1.7	0.020-0.040	<0.02			0.22-0.30	1.0-1.5	<0.30								
702.9	Cu = Ag-Cu	rem			<0.015		1.3-1.7	0.020-0.040	<0.02			0.22-0.30	2.1-2.7	<0.30								
703	Cu = Ag-Cu	>99.50			<0.05	<0.50	4.7-5.7					0.20-1.20		<1.00				0.18-0.50				
703.2	Cu = Ag-Cu	rem		0.20-1.20	1.3-1.7	0.30-0.80	2.5-5.0		<0.05			0.20-1.20		<1.00								
704	Cu = Ag-Cu	rem			1.0-1.8	0.30-1.00	4.5-6.0		<0.05			0.35-0.45	<0.10	<1.00								
704.4	Cu = Ag-Cu, C<0.05	rem			1.0-1.8	0.30-1.00	4.5-6.0		<0.05	<0.05				<1.00								
705	Cu = Ag-Cu	rem			<0.10	<0.15	5.8-7.8		<0.05					<0.20								
706	Cu = Ag-Cu	rem			1.0-1.8	<1.00	10.0-11.0		<0.05					<1.00								
706.1	Cu = Ag-Cu, C<0.05	rem			1.0-2.0	0.30-1.00	10.0-11.0		<0.01	<0.05				<1.00								
706.2	Cu = Ag-Cu, C<0.05	>86.50			1.0-1.8	<1.00	9.0-11.0	<0.02	<0.02	<0.02				<1.00								
706.9	Cu=Ag-Cu, C<0.03, Hg<0.0005	rem		<0.002	<0.005	<0.001	9.0-11.0	<0.001	<0.001	<0.003	<0.001	<0.02	<0.001	<0.001	<0.001		<0.001	<0.02			<0.001	
707	Cu = Ag-Cu	rem			<0.05	<0.50	9.5-10.5		<0.05					<0.20								
708	Cu = Ag-Cu	rem			<0.10	<0.15	10.5-12.5		<0.05					<0.20								
709	Cu = Ag-Cu	rem			<0.60	<0.60	13.5-16.5		<0.05					<1.00								
710	Cu = Ag-Cu	rem			<1.00	<1.00	19.0-23.0		<0.05					<1.00								
711	Cu = Ag-Cu	rem			<0.10	<0.15	22.0-24.0		<0.05	<0.008				<0.20								
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
711.1	Cu = Ag-Cu	rem			<0.20	<0.35	21.5-23.5		<0.05					<1.00								
713	Cu = Ag-Cu	rem			0.40-1.00	<1.00	23.5-26.5		<0.05					<1.00								
715	Cu = Ag-Cu	rem			0.40-1.00	<1.00	29.0-33.0		<0.05	<0.02				<1.00								
715.2	Cu = Ag-Cu	>65.00			0.40-1.00	<1.00	29.0-33.0	<0.02	<0.05	<0.02				<0.05								
715.8	Cu = Ag-Cu, C <0.70	rem		<0.05	<0.50	<0.30	29.0-33.0		<0.05	<0.024		<0.15										
715.81	Cu = Ag-Cu	rem			0.40-0.70	<1.00	29.0-32.0	<0.02	<0.02	<0.01	<0.001	<0.25	<0.001	<0.001	<0.001		<0.001	<0.05		<0.10	0.20-0.50	
715.9	Cu = Ag-Cu, C <0.02, Hg <0.0005	rem		<0.002	<0.15	<0.50	29.0-31.0	<0.001	<0.001	<0.003	<0.001	<0.015	<0.001	<0.001	<0.001		<0.001	<0.05		<0.10	<0.001	
716.3	Cu = Ag-Cu, C <0.06	rem			0.40-1.00	0.50-1.50	30.0-32.0		<0.01	<0.08												
716.4	Cu = Ag-Cu, C <0.06	rem			1.7-2.3	1.5-2.5	29.0-32.0		<0.01	<0.03												
717	Cu = Ag-Cu	rem			0.40-1.00		29.0-33.0									0.30-0.70						
719	Cu = Ag-Cu, C <0.04	rem			<0.50	0.20-1.00	28.0-33.0	<0.02	<0.015	<0.015		<0.25		<0.05					2.2-3.0		0.01-0.20	0.02-0.35
721.5	Cu = Ag-Cu, C <0.10	rem			<0.10	<0.05	43.0-46.0		<0.05			<0.50		<0.20								
722	Cu = Ag-Cu, C <0.03	rem			0.5-1.0	<1.00	15.0-18.0		<0.05			<0.03		<1.00					0.30-0.70		<0.03	
724	Cu = Ag-Cu	rem		1.5-2.5	<0.10	<1.00	11.0-15.0		<0.05				<0.05	<0.50						0.05-0.40		
724.2	Cu = Ag-Cu, C <0.05	rem		1.0-2.0	0.7-1.2	3.5-5.5	13.5-16.5	<0.01	<0.02	<0.15		<0.15		<0.20					<0.50	<0.05		
725	Cu = Ag-Cu	rem			<0.60	<0.20	8.5-10.5		<0.05				1.8-2.8	<0.50								
726.5	Cu = Ag-Cu	91.0-93.0			<0.20	<0.20	3.5-4.5	<0.05	<0.05				3.5-4.5	<0.50								
726.6	Cu = Ag-Cu	rem			<0.10	<0.10	7.0-8.0		<0.01				4.5-5.7	<0.10						<0.15		
727	Cu = Ag-Cu	rem			<0.25	<0.50	4.0-7.0		<0.10				9.0-15.0									
732	Cu = Ag-Cu	rem			<0.06	<1.00	19.0-23.0		<0.05				3.0-6.0									
735	Cu = Ag-Cu	70.5-73.5			<0.25	<0.50	16.5-19.5		<0.10					rem								
738	Cu = Ag-Cu	68.5-71.5			<0.25	<0.50	11.0-13.0		<0.05					rem								
740	Cu = Ag-Cu	69.0-73.5			<0.25	<0.50	9.0-11.0		<0.10					rem								
743	Cu = Ag-Cu	63.0-66.0			<0.25	<0.50	7.0-9.0		<0.10					rem								
744	Cu = Ag-Cu	62.0-66.0			<0.05				<0.05					rem								
745	Cu = Ag-Cu	63.5-66.5			<0.25	<0.50	9.0-11.0		<0.10					rem								
752	Cu = Ag-Cu	63.5-66.5			<0.25	<0.50	16.5-19.5		<0.05					rem								
754	Cu = Ag-Cu	63.5-66.5			<0.25	<0.50	14.0-16.0		<0.10					rem								
757	Cu = Ag-Cu	63.5-66.5			<0.25	<0.50	11.0-13.0		<0.05					rem								
757.2	Cu = Ag-Cu	60.0-65.0			0.05-0.30	0.05-0.30	11.0-13.0		<0.04					rem								
759	Cu = Ag-Cu	60.0-65.0			<0.25	<0.50	17.0-19.0		<0.10					rem								
760	Cu = Ag-Cu	60.0-63.0			<0.25	<0.50	7.0-9.0		<0.10					rem								
761	Cu = Ag-Cu	59.0-61.0			<0.25	<0.50	7.0-9.0		<0.10					rem								
762	Cu = Ag-Cu	57.0-61.0			<0.25	<0.50	11.0-13.5		<0.10					rem								
763	Cu = Ag-Cu	60.0-64.0			<0.50	<0.50	17.0-19.0		0.50-2.00					rem								
763.9	Cu = Ag-Cu	59.0-63.0			<0.50	<0.50	23.0-26.0		0.8-1.1				0.40-0.60	rem								
764	Cu = Ag-Cu	58.5-61.5			<0.25	<0.50	16.5-19.5		<0.05					rem								
766	Cu = Ag-Cu	55.0-58.0			<0.25	<0.50	11.0-13.5		<0.10					rem								
767	Cu = Ag-Cu	55.0-58.0			<0.25	<0.50	14.0-16.0		<0.10					rem								
770	Cu = Ag-Cu	53.5-56.5			<0.25	<0.50	16.5-19.5		<0.05					rem								
770.1	Cu = Ag-Cu	54.0-56.0			0.05-0.35	0.05-0.35	17.0-19.0		<0.03					rem								
773	Cu = Ag-Cu	46.0-50.0		<0.01	<0.30		9.0-11.0	<0.25	<0.05		0.04-0.25			rem								
773.1	Cu = Ag-Cu	46.0-50.0		<0.01		<0.50	9.0-11.0	<0.25	<0.05		0.04-0.25			rem								
774	Cu = Ag-Cu	43.0-47.0			<0.20	<0.35	12.0-14.0		<0.20				<0.15	rem								
776	Cu = Ag-Cu	42.0-45.0			<0.35	<0.50	7.0-9.0		<0.25					rem								
782	Cu = Ag-Cu	63.0-67.0			<0.25	<0.50	9.0-11.0		1.5-2.5					rem								
788	Cu = Ag-Cu	63.0-67.0			<0.25	<0.50	9.0-11.0		1.5-2.0					rem								
790	Cu = Ag-Cu	63.0-67.0			<0.35	<0.50	11.0-13.0		1.5-2.2					rem								
792	Cu = Ag-Cu	59.5-66.5			<0.25	<0.50	11.0-13.0		0.8-1.4					rem								
793	Cu = Ag-Cu	55.0-59.0			<0.50	<0.50	11.0-13.0		0.50-2.00					rem								
796	Cu = Ag-Cu	43.5-46.5				1.5-2.5	9.0-11.0		0.8-1.2					rem								
796.2	Cu = Ag-Cu	46.0-48.0			<0.25	<0.50	8.0-11.0		0.50-2.00					rem								
798	Cu = Ag-Cu	45.5-48.5			<0.25	1.5-2.5	9.0-11.0		1.5-2.5					rem								
798.1	Cu = Ag-Cu	46.0-48.0			<0.50	<0.50	8.0-11.0		2.0-3.5					rem								
798.2	Ni = Ni-Cu	46.0-48.0			<0.50	<0.50	8.0-11.0		2.0-3.5					rem								
798.3	Ni = Ni-Cu	45.5-47.0			0.15-0.55	9.0-10.5			2.0-2.5					rem								
799	Cu = Ag-Cu	47.5-50.5			<0.25	<0.50	6.5-8.5		1.0-1.5					rem								
801	Cu = Ag-Cu	>99.95																				
803	Cu = Ag-Cu	>99.95																				
804.1	Cu = Ag-Cu	>99.90																				
805	Cu = Ag-Cu	>99.75																				
807	B <0.02	>99.75																				
809		>99.70																				
812		>99.70						0.040-0.065														
813		>98.50																				
814		>98.50																				
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
727	Cu = Ag-Cu	rem			<0.50	0.05-0.30	8.5-10.5	<0.005	<0.005	<0.0025	<0.02	<0.05	<0.05	<0.50	<1.00		<0.001	<0.05		<0.15	<0.01	
728	Cu = Ag-Cu	rem			<0.50	0.05-0.30	8.5-10.5	<0.005	<0.005	<0.0025	<0.02	<0.05	<0.05	<0.50	<1.00		<0.001	<0.05		<0.15	<0.01	
729	Cu = Ag-Cu	rem			<0.50	<0.30	14.5-15.5		<0.02				7.5-8.5	<0.50						<0.15		
729.5	Cu = Ag-Cu	rem			<0.60	<0.60	20.0-22.0		<0.05				4.5-5.7	<0.50								
731.5	Cu = Ag-Cu	rem			<0.25	<0.50	4.0-7.0		<0.10				9.0-15.0									
732	Cu = Ag-Cu	rem			<0.06	<1.00	19.0-23.0		<0.05				3.0-6.0									
735	Cu = Ag-Cu	70.5-73.5			<0.25	<0.50	16.5-19.5		<0.10					rem								
738	Cu = Ag-Cu	68.5-71.5			<0.25	<0.50	11.0-13.0		<0.05					rem								
740	Cu = Ag-Cu	69.0-73.5			<0.25	<0.50	9.0-11.0		<0.10					rem								
743	Cu = Ag-Cu	63.0-66.0			<0.25	<0.50	7.0-9.0		<0.10					rem								
744	Cu = Ag-Cu	62.0-66.0			<0.05				<0.05					rem								
745	Cu = Ag-Cu	63.5-66.5																				

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
815		>98.00	.	<0.10	<0.10	.	.	.	<0.02	.	.	<0.15	<0.10	<0.10	.	.	.	.	0.40-1.50	.	.	.
815.4		>95.10	.	<0.10	<0.15	.	2.0-3.0	.	<0.02	.	.	0.40-0.80	<0.10	<0.10	.	.	.	.	0.40-0.60	.	.	.
817		>94.20	0.80-1.20	.	.	.	0.25-1.50	.	.	.	.	.	.	.	.	0.30-0.55	.	0.25-1.50	.	.	.	.
818		>95.60	0.80-1.20	.	.	.	<0.20	.	<0.02	.	.	<0.15	<0.10	<0.10	.	0.30-0.55	.	1.4-1.7	.	.	.	.
820		>95.00	.	<0.10	<0.10	.	.	.	<0.02	.	.	.	.	.	.	0.45-0.80	.	2.4-2.7	<0.10	.	.	.
821		>95.50	.	.	.	.	0.25-1.50	.	.	.	.	.	.	.	.	0.35-0.80	.	0.25-1.50	.	.	.	.
822		>96.50	.	.	.	.	1.0-2.0	.	.	.	.	.	.	.	.	0.35-0.80	.	.	.	.	.	.
824		>96.40	.	<0.15	<0.20	.	<0.10	.	<0.02	.	.	.	<0.10	<0.10	.	1.65-1.75	.	0.20-0.40	<0.10	.	.	.
825		>95.50	.	<0.15	<0.25	.	<0.20	.	<0.02	.	.	0.20-0.35	<0.10	<0.10	.	1.90-2.15	.	0.35-0.70	<0.10	.	.	.
825.1		>95.50	.	<0.15	<0.25	.	<0.20	.	<0.02	.	.	0.20-0.35	<0.10	<0.10	.	1.90-2.15	.	1.0-2.0	<0.10	.	.	.
826		>95.20	.	<0.15	<0.25	.	<0.20	.	<0.02	.	.	0.20-0.35	<0.10	<0.10	.	2.25-2.45	.	0.35-0.70	<0.10	.	.	.
827		>94.60	.	<0.15	<0.25	.	1.0-1.5	.	<0.02	.	.	<0.15	<0.10	<0.10	.	2.35-2.55	.	.	<0.10	.	.	.
828		>94.80	.	<0.15	<0.25	.	<0.20	.	1.0-2.0	.	.	0.20-0.35	<0.10	<0.10	.	2.50-2.75	.	0.35-0.70	<0.10	.	.	.
833		92.0-94.0	.	.	.	.	.	.	.	.	.	.	1.0-2.0	2.0-6.0	.	.	.	.	.	.	.	.
834		88.0-92.0	.	.	.	.	.	.	<0.50	.	.	.	<0.20	8.0-12.0	.	.	.	.	.	.	.	.
834.1		88.0-91.0	.	<0.005	<0.05	.	<0.05	.	<0.10	.	.	<0.005	1.0-2.0	rem	.	.	.	.	.	.	.	.
834.2		88.0-92.0	.	<0.005	<0.10	.	<0.10	.	<0.50	.	.	<0.25	0.25-0.70	rem	.	.	.	.	.	.	.	.
834.5		87.0-89.0	.	<0.005	<0.30	.	0.8-2.0	<0.03	1.5-3.0	<0.08	.	<0.005	2.0-3.5	5.5-7.5	.	.	.	.	.	.	.	.
835		86.0-88.0	.	<0.008	<0.25	.	0.50-1.00	<0.03	3.5-5.5	<0.08	.	<0.005	5.5-6.5	7.5-9.5	.	.	.	.	.	.	.	.
835.2		rem	.	<0.30	<0.30	.	<1.0	.	3.5-4.5	<0.08	.	<0.25	3.5-4.5	1.5-4.0	.	.	.	.	.	.	.	.
836		84.0-86.0	.	<0.005	<0.30	.	<1.0	<0.05	4.0-6.0	<0.08	.	<0.25	4.0-6.0	4.0-6.0	.	0.05-0.20	.	.	.	.	.	.
837		83.0-88.0	.	<0.005	<0.30	.	<0.30	.	<0.50	<0.08	.	<0.25	<1.00	rem	.	.	.	.	.	.	.	.
838		82.0-83.8	.	<0.005	<0.30	.	<1.0	<0.03	5.0-7.0	<0.08	.	<0.25	3.3-4.2	5.0-8.0	.	.	.	.	.	.	.	.
838.1		rem	.	<0.01	<0.50	.	<2.0	.	4.0-6.0	<0.08	.	<0.30	2.0-3.5	7.5-9.5	.	.	<0.10	.	.	.	.	.
842		78.0-82.0	.	<0.005	<0.40	.	<0.8	<0.05	2.0-3.0	<0.08	.	<0.25	4.0-6.0	10.0-16.0	.	.	.	.	.	.	.	.
844		78.0-82.0	.	<0.005	<0.40	.	<1.0	<0.20	6.0-8.0	<0.08	.	<0.25	2.3-3.5	7.0-10.0	.	.	.	.	.	.	.	.
844.1		rem	.	<0.01	<0.40	.	<1.0	<0.02	7.0-9.0	<0.08	.	<0.20	3.0-4.5	7.0-11.0	.	.	<0.05	.	.	.	.	.
845		77.0-79.0	.	<0.005	<0.40	.	<1.0	<0.02	6.0-7.5	<0.08	.	<0.25	2.0-4.0	10.0-14.0	.	.	.	.	.	.	.	.
848		75.0-77.0	.	<0.005	<0.40	.	<1.0	<0.02	5.5-7.0	<0.08	.	<0.25	2.0-3.0	13.0-17.0	.	.	.	.	.	.	.	.
852		70.0-74.0	.	<0.005	<0.60	.	<1.0	<0.02	1.5-3.8	<0.05	.	<0.20	0.7-2.0	20.0-27.0	.	.	.	.	.	.	.	.
852.1		70.0-75.0	.	<0.005	<0.80	.	<1.0	.	2.0-5.0	.	.	<0.005	1.0-3.0	rem	0.02-0.06	.	.	.	.	.	.	.
853		68.0-72.0	.	<0.01	<0.80	.	<1.0	.	<0.50	.	.	.	<0.50	rem	.	.	.	.	.	.	.	.
853.1		66.0-73.0	.	<0.35	<0.70	.	<1.0	.	2.0-5.0	.	.	<0.05	0.50-1.50	24.0-32.0	.	.	.	.	.	.	.	.
854	Cu = Cu-Ni	65.0-70.0	.	.	<0.20	.	<1.0	.	1.5-3.8	.	.	.	<0.20	rem	.	.	.	.	.	.	.	.
855	Cu = Cu-Ni	59.0-63.0	.	.	<0.20	.	<0.20	.	<0.20	.	.	.	<0.20	rem	.	.	.	.	.	.	.	.
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
856	Cu = Cu-Ni	59.0-63.0	.	<0.8	<0.20	<0.20	<0.20	.	<0.20	.	.	<0.05	<0.20	rem	.	.	.	.	.	.	.	.
857	Cu = Cu-Ni	58.0-64.0	.	0.20-0.80	<0.70	<0.50	<1.0	.	0.8-1.5	.	.	<0.05	0.50-1.50	32.0-40.0	.	.	.	.	.	.	.	.
857.1	Cu = Cu-Ni	58.0-63.0	.	<0.50	<0.80	<0.50	<1.0	.	1.0-2.5	.	.	<0.05	<1.00	rem	.	.	.	.	.	.	.	.
858	Cu = Cu-Ni	>57.00	.	4.5-5.5	2.0-4.0	2.5-5.0	.	<0.01	<1.5	<0.05	.	<1.50	<1.50	31.0-41.0	<0.05	.	.	.	.	.	.	.
861	Cu = Cu-Ni	66.0-68.0	.	.	.	.	.	.	<0.20	.	.	.	.	rem	.	.	.	.	.	.	.	.
862	Cu = Cu-Ni	60.0-66.0	.	3.0-4.9	2.0-4.0	2.5-5.0	<1.0	.	<0.20	.	.	.	<0.20	22.0-28.0	.	.	.	.	.	.	.	.
863	Cu = Cu-Ni	60.0-66.0	.	5.0-7.5	2.0-4.0	2.5-5.0	<1.0	.	<0.20	.	.	.	<0.20	22.0-28.0	.	.	.	.	.	.	.	.
864	Cu = Cu-Ni	56.0-62.0	.	0.50-1.50	0.40-2.00	1.0-1.00	<1.0	.	0.50-1.50	.	.	.	0.50-1.50	34.0-42.0	.	.	.	.	.	.	.	.
865	Cu = Cu-Ni	55.0-60.0	.	0.50-1.50	0.40-2.00	1.0-1.15	<1.0	.	<0.40	.	.	.	<1.00	36.0-42.0	.	.	.	.	.	.	.	.
865.5	Cu = Cu-Ni	>57.00	.	0.50-2.50	0.7-2.0	0.10-3.00	<1.0	.	<0.50	.	.	<1.00	<1.00	rem	.	.	.	.	.	.	.	.
867	Cu = Cu-Ni	53.0-60.0	.	1.0-3.0	1.0-3.0	1.0-3.5	<1.0	.	0.5-1.5	.	.	.	<1.50	30.0-38.0	.	.	.	.	.	.	.	.
868	Cu = Cu-Ni	53.5-57.0	.	<2.0	1.0-2.5	2.5-4.0	2.5-4.0	.	<0.20	.	.	.	<1.00	rem	.	.	.	.	.	.	.	.
872		>89.00	.	<1.5	<2.50	<1.50	.	.	<0.50	.	.	1.0-3.0	<1.00	<5.00	.	.	.	.	.	.	.	.
873		>94.00	.	.	<0.20	0.8-1.5	.	.	<0.20	.	.	3.5-4.5	<0.25	.	.	.	.	.	.	.	.	.
874		>79.00	.	<0.8	.	.	.	.	<1.0	.	.	2.5-4.0	.	12.0-16.0	.	.	.	.	.	.	.	.
874.1		>79.00	.	<0.8	.	.	.	.	<1.0	.	.	2.5-4.0	.	12.0-16.0	0.03-0.06	.	.	.	.	.	.	.
874.2		>79.00	.	<0.8	.	.	.	0.03-0.06	<1.0	.	0.03-0.06	2.5-4.0	.	12.0-16.0	.	.	.	.	.	.	.	.
874.3		>79.00	.	<0.8	.	.	.	.	<1.0	.	.	2.5-4.0	.	12.0-16.0	.	.	.	.	.	.	.	.
875		>79.00	.	<0.5	.	.	.	.	<0.50	.	.	3.0-5.0	.	12.0-16.0	.	.	.	.	.	.	.	.
875.1		>79.00	.	<0.50	.	.	.	.	<0.50	.	.	3.0-5.0	.	12.0-16.0	0.03-0.06	.	.	.	.	.	.	.
875.2		>79.00	.	<0.50	.	.	.	.	<0.50	.	0.03-0.06	3.0-5.0	.	12.0-16.0	.	.	.	.	.	.	.	.
875.3		>79.00	.	<0.50	.	.	.	0.03-0.06	<0.50	.	.	3.0-5.0	.	12.0-16.0	.	.	.	.	.	.	.	.
876		>88.00	.	.	<0.20	<0.25	.	.	<0.50	.	.	3.5-4.5	.	4.0-7.0	.	.	.	.	.	.	.	.
876.1		>80.00	.	<0.15	<0.15	<0.15	<0.20	<0.01	<0.20	<0.05	<0.05	3.0-5.0	<0.25	3.0-5.0	.	.	.	.	.	.	.	.
878		>80.00	.	.	.	.	.	.	<1.0	.	.	2.5-4.0	.	12.0-16.0	.	.	.	.	.	<0.01	.	.
879		>63.00	.	<0.15	<0.40	<0.15	<0.50	<0.01	<0.25	<0.05	<0.05	0.8-1.2	<0.25	30.0-36.0	<0.05	.	.	.	.	.	.	.
893.2		87.0-91.0	.	<0.005	<0.20	.	<1.0	<0.30	<0.09	<0.08	<0.35	<0.005	5.0-7.0	<1.00	.	.	4.0-6.0	.	.	.	.	.
893.25	Misch metal 0.10-1.0	84.0-88.0	.	<0.005	<0.15	.	<1.0	<0.10	<0.10	<0.08	<0.30	<0.005	9.0-11.0	<1.00	.	.	2.7-3.7	.	.	.	.	.
895.1	Se 0.35-0.75	86.0-88.0	.	<0.005	<0.20	.	<1.0	<0.05	<0.25	<0.08	<0.25	<0.005	4.0-6.0	4.0-6.0	.	.	0.5-1.5	.	.	.	.	.
895.2	Se 0.80-1.10	86.0-87.0	.	<0.005	<0.20	.	<1.0	<0.05	<0.25	<0.08	<0.25	<0.005	5.0-6.0	4.0-6.0	.	.	1.6-2.2	.	.	.	.	.
895.5	Se 0.01-0.10	58.0-54.0	.	0.10-0.60	<0.50	.	<1.0	<0.01	<0.10	<0.05	.	.	0.50-1.50	32.0-40.0	.	.	0.6-1.2	.	.	.	.	.
898.31	Misch metal 0.10-1.0	87.0-91.0	.	<0.005	<0.30	.	<1.0	<0.05	<0.10	<0.08	<0.25	<0.005	2.7-3.7	2.0-4.0	.	.	2.0-4.0	.	.	.	.	.
898.33	Misch metal 0.10-1.0	87.0-91.0	.	<0.005	<0.30	.	<1.0	<0.05	<0.10	<0.08	<0.25	<0.005	4.0-6.0	2.0-4.0	.	.	1.7-2.7	.	.	.	.	.
898.35	Misch metal 0.10-1.0	85.0-89.0	.	<0.005	<0.20	.	<1.0	<0.10	<0.10	<0.08	<0.35	<0.005	6.0-7.5	2.0-4.0	.	.	1.7-2.7	.	.	.	.	.
898.37	Misch metal 0.10-1.0	85.0-88.0	.	<0.005	<0.30	.	<1.0	<0.05	<0.10	<0.08	<0.25	<0.005	3.0-4.0	6.0-10.0	.	.	0.7-1.2	.	.	.	.	.
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
958.2		>77.50		9.0-10.0	4.0-5.0	<1.50	4.5-5.8	.	<0.02	.	.	<0.10	<0.20	<0.20	.	.	.	.	.	.	.	.
959		rem		12.0-13.5	3.0-5.0	<1.50	<0.50	.	<0.01	<0.02	.	<0.50	.	.	.	.	.	.	.	.	.	.
962	C <0.15, Nb <0.00	rem		.	1.0-1.8	<1.50	9.0-11.0	<0.02	<0.01	<0.02	.	<0.50	.	.	.	.	.	.	.	.	.	.
963	C <0.15, Nb 0.50-1.50	rem		.	0.50-1.50	0.25-1.50	18.0-22.0	<0.02	<0.01	<0.02	.	<0.50	.	.	.	.	.	.	.	.	.	.
964	C <0.15, Nb 0.50-1.50	rem		.	0.25-1.50	<1.50	28.0-32.0	<0.02	<0.03	<0.02	.	<0.50	.	.	.	.	.	.	.	.	.	.
966		rem		.	0.8-1.1	<1.00	29.0-33.0	.	<0.01	.	.	<0.15	.	.	.	0.40-0.70	.	.	.	.	.	.
967		rem		.	0.7-1.0	<0.70	29.0-33.0	.	<0.01	.	.	<0.15	.	.	.	1.10-1.20	.	.	.	.	.	.
968	Nb 0.10-0.30, B <0.01	rem		<0.10	<0.50	0.05-0.30	9.5-10.5	<0.005	<0.005	<0.0025	<0.02	<0.05	7.5-8.5	<1.00	.	.	<0.001	.	.	0.005-0.15	0.01-0.20	0.1-0.2
969	Nb <0.10	rem		.	<0.50	0.50-0.30	14.5-15.5	.	<0.02	.	.	<0.30	7.5-8.5	<0.50	.	.	.	.	.	<0.15	<0.01	.
969.5	Nb <0.10	rem		.	<0.50	0.05-0.40	11.0-15.5	.	<0.02	.	.	<0.30	5.8-8.5	<0.50	.	.	.	.	.	<0.15	.	.
973		53.0-58.0		<0.005	<1.50	<0.50	11.0-14.0	<0.05	8.0-11.0	<0.08	<0.35	<0.15	1.5-3.0	17.0-25.0	.	.	.	.	.	.	.	.
974		58.0-61.0		.	<1.50	<0.50	15.5-17.0	.	4.5-5.5	<0.08	<0.25	<0.15	2.5-3.5	rem	.	.	.	.	.	.	.	.
976		63.0-67.0		<0.005	<1.50	<1.00	19.0-21.5	<0.05	3.0-5.0	<0.08	<0.20	<0.15	3.5-4.5	3.0-5.0	.	.	.	.	.	.	.	.
978		64.0-67.0		.	<1.50	<1.00	24.0-27.0	<0.05	1.0-2.5	<0.10	<0.50	<0.15	4.0-5.5	1.0-4.0	.	.	.	.	.	.	.	.
982		73.0-79.0		.	<0.70	.	<0.50	<0.10	21.0-27.0	.	<0.50	.	0.6-2.0	<0.50	.	.	.	.	.	.	.	.
984		rem	<1.50	.	<0.70	.	<0.50	<0.10	26.0-33.0	.	<0.50	.	<0.50	<0.50	.	.	.	.	.	.	.	.
986		60.0-70.0	<1.50	.	<0.35	.	.	<0.02	30.0-40.0	.	.	.	<0.50	<0.10	.	.	.	.	.	.	.	.
988		56.5-62.5	<1.50	.	<0.35	.	.	.	37.5-42.5	.	.	.	1.0-5.0	.	.	.	.	.	.	.	.	.
988.2		rem	.	.	<0.35	.	.	.	40.0-44.0	.	.	.	1.0-5.0	.	.	.	.	.	.	.	.	.
988.4		rem	.	.	<0.35	.	.	.	44.0-58.0	.	.	.	1.0-5.0	.	.	.	.	.	.	.	.	.
993	Incramet 800	rem	.	10.7-11.5	0.40-1.00	.	13.5-16.5	.	<0.02	.	.	<0.02	<0.05	.	.	.	.	1.0-2.0	.	.	.	.
993.5		rem	.	9.5-10.5	<1.00	<0.25	14.5-16.0	.	<0.15	.	.	.	.	7.5-9.5	.	.	.	.	.	.	.	.
994		rem	.	0.50-2.00	1.0-3.0	<0.50	1.0-3.5	.	<0.25	.	.	0.50-2.00	.	0.50-5.00	.	.	.	.	.	.	.	.
995		rem	.	0.50-2.00	3.0-5.0	<0.50	3.5-5.5	.	<0.25	.	.	0.50-2.00	.	0.50-2.00	.	.	.	.	.	.	.	.
996	C <0.05	rem	.	1.0-2.8	<0.20	39.0-45.0	<0.20	.	<0.02	.	.	<0.10	<0.10	<0.20	.	.	.	<0.20	.	.	.	.
997	Nb 4.0-6.0	>54.00	.	0.50-3.00	<1.00	11.0-15.0	4.0-6.0	.	<2.0	.	.	.	<1.00	19.0-25.0	.	.	.	.	.	.	.	.
997.5		55.0-61.0	.	0.25-3.00	<1.00	17.0-23.0	<5.0	.	0.50-2.50	.	.	.	0.50-2.50	17.0-23.0	.	.	.	.	.	.	.	.
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr

These are specifications for
reference purpose only,
not samples for sale